



RAPPORTI ISTISAN 17|36

ISSN: 1123-3117 (cartaceo) • 2384-8936 (online)

Natural radioactivity in building materials in the European Union: a database of activity concentrations, radon emanations and radon exhalation rates

C. Nuccetelli, S. Risica, S. Onisei,
F. Leonardi, R. Trevisi



AMBIENTE
E SALUTE

ISTITUTO SUPERIORE DI SANITÀ

**Natural radioactivity in building materials
in the European Union: a database of activity
concentrations, radon emanations
and radon exhalation rates**

Cristina Nuccetelli (a), Serena Risica (b), Silvana Onisei (c),
Federica Leonardi (d), Rosabianca Trevisi (d)

*(a) Centro Nazionale Protezione dalle Radiazioni e Fisica Computazionale,
Istituto Superiore di Sanità, Rome, Italy*

(b) Previously Istituto Superiore di Sanità, Rome, Italy

(c) Department of Materials Engineering, Katholieke Universiteit Leuven, Leuven, Belgium

*(d) Research Sector, Istituto Nazionale per l'Assicurazione contro gli Infortuni
sul Lavoro e le malattie professionali, Monteporzio Catone (Rome), Italy*

ISSN: 1123-3117 (cartaceo) • 2384-8936 (online)

**Rapporti ISTISAN
17/36**

Istituto Superiore di Sanità

Natural radioactivity in building materials in the European Union: a database of activity concentrations, radon emanations and radon exhalation rates.

Cristina Nuccetelli, Serena Risica, Silvana Onisei, Federica Leonardi, Rosabianca Trevisi
2017, 70 p. Rapporti ISTISAN 17/36

A database of activity concentration measurements of natural radionuclides (^{226}Ra , ^{232}Th and ^{40}K) in European building materials is presented. It contains about 23000 samples of bulk materials – bricks, concrete –, their constituents – cement, aggregates, NORM (Naturally occurring Radioactive Material) residues, etc. – and superficial materials used in the construction industry in most European Union Member States and some European Countries. In addition, density and radon emanation and/or exhalation rate information related to approximately 1500 samples of building materials or their components have been collected and organized in one table.

Key words: Building materials; Natural radioactivity; Activity concentration; Radon emanation and exhalation

Istituto Superiore di Sanità

Radioattività naturale nei materiali da costruzione nell'Unione europea: un database di concentrazioni di attività, emanazioni di radon e rateo di esalazione di radon.

Cristina Nuccetelli, Serena Risica, Silvana Onisei, Federica Leonardi, Rosabianca Trevisi
2017, 70 p. Rapporti ISTISAN 17/36 (in inglese)

Viene presentato un database di misure di concentrazione di attività di radionuclidi naturali (^{226}Ra , ^{232}Th e ^{40}K) nei materiali da costruzione utilizzati dall'industria edile nei paesi membri dell'Unione Europea (UE) e in alcuni paesi europei non UE. Il database contiene dati su circa 23000 campioni di materiali strutturali – mattoni, calcestruzzo, ecc. –, dei loro componenti – cemento, aggregati fini e grossolani, residui NORM (Naturally occurring Radioactive Material), ecc. – e di materiali superficiali – mattonelle, pietre. Sono state inoltre raccolte e organizzate in una tabella le informazioni su densità ed emanazione e/o esalazione del radon relative a circa 1500 campioni di materiali da costruzione o di loro componenti.

Parole chiave: Materiali da costruzione; Radioattività naturale; Concentrazione d'attività; Emanazione ed esalazione del radon

Si ringrazia il dott. Marco D'Alessandro (CNR, Italia) per il suo contributo al lavoro di raccolta dati e di sviluppo del database. Si ringrazia altresì la COST Action TU1301 "NORM4BUILDING" per il sostegno a collaborazioni con colleghi europei e, in particolare, per aver finanziato la STSM (Short Term Scientific Mission) della dott.ssa Silvana Onisei presso l'ISS.

Per informazioni su questo documento scrivere a: cristina.nuccetelli@iss.it

Il rapporto è accessibile online dal sito di questo Istituto: www.iss.it.

Citare questo documento come segue:

Nuccetelli C, Risica S, Onisei S, Leonardi F, Trevisi R. *Natural radioactivity in building materials in the European Union: a database of activity concentrations, radon emanations and radon exhalation rates*. Roma: Istituto Superiore di Sanità; 2017. (Rapporti ISTISAN 17/36).

Legale rappresentante dell'Istituto Superiore di Sanità: *Gualtiero Ricciardi*
Registro della Stampa - Tribunale di Roma n. 114 (cartaceo) e n. 115 (online) del 16 maggio 2014

Direttore responsabile della serie: *Paola De Castro*
Redazione: *Paola De Castro* e *Sandra Salinetti*

La responsabilità dei dati scientifici e tecnici è dei singoli autori, che dichiarano di non avere conflitti di interesse.



TABLE OF CONTENTS

| | |
|---|--------|
| Database description | 1 |
| References | 3 |
| Tables of activity concentrations of building materials used in 30 European countries | |
| Table 1 Austria | 7 |
| Table 2 Belgium..... | 7 |
| Table 3 Bulgaria..... | 9 |
| Table 4 Cyprus | 9 |
| Table 5 Czech Republic | 11 |
| Table 6 Denmark..... | 12 |
| Table 7 Estonia..... | 13 |
| Table 8 Finland | 14 |
| Table 9 France..... | 15 |
| Table 10 Germany..... | 17 |
| Table 11 Greece | 20 |
| Table 12 Hungary..... | 23 |
| Table 13 Ireland | 25 |
| Table 14 Italy | 25 |
| Table 15 Latvia | 33 |
| Table 16 Lithuania | 33 |
| Table 17 Luxembourg..... | 33 |
| Table 18 Macedonia..... | 34 |
| Table 19 Netherlands | 34 |
| Table 20 Norway..... | 37 |
| Table 21 Poland..... | 38 |
| Table 22 Portugal | 39 |
| Table 23 Romania | 40 |
| Table 24 Slovakia..... | 41 |
| Table 25 Slovenia..... | 43 |
| Table 26 Spain..... | 43 |
| Table 27 Sweden | 46 |
| Table 28 Switzerland..... | 47 |
| Table 29 Turkey | 48 |
| Table 30 United Kingdom..... | 48 |
| Table of radon emanation and exhalation rate of building materials used in 15 European countries | |
| Table 31 Data on radon emanation and exhalation rate of building materials used in European countries..... | 53 |
| Database references | 64 |

DATABASE DESCRIPTION

Due to their natural origin radionuclide content, building materials can cause significant gamma dose indoors and contribute to the indoor radon concentration. A first database of the activity concentrations of ^{238}U (^{226}Ra), ^{232}Th and ^{40}K in about 10000 samples of building materials used in 25 of 27 European Union Member States (EU MS) was already collected (1) by a wide review of the relevant literature. That database accounted for previous databases. In particular, the 1996 European Commission (EC) publication (2) and a study on Italian building materials conducted in 1999 (3) were considered.

The 1996 EC publication (2) was the data source for the elaboration of the EC technical guidance for the regulatory control of building materials RP112 (4). In the Euratom Basic Safety Standards Directive (5) the RP112 guidance approach and results were the bases to introduce the regulatory control and screening of building materials of radiological concern.

From 2012 to 2017 the database has been significantly enriched. Indeed, now it contains radiological data on 23500 samples from 26 of 28 MS and also radon emanation/exhalation rate information for a subset of samples (about 1100). The collection of data has been further extended to 2 EU candidate countries and 2 non EU countries increasing of about 400 the total number of considered samples.

This new database comprises measurements of natural radionuclide activity concentrations (^{226}Ra ^a, ^{232}Th and ^{40}K) of about 23900 samples used in 26 of 28 EU MS, in 2 EU candidate countries (the former Yugoslav Republic of Macedonia and Turkey) and in 2 non EU countries (Norway and Switzerland) (Table A). Where available, radon emanation/exhalation rate information concerning about 1120 building material samples have been also collected (see Table A). Moreover, for other 370 samples without data concerning activity concentrations only information related to radon emanation/exhalation rate were collected.

The updating procedures have been carried out through a broad review of international and some national literature, including peer reviewed papers, reports and personal communications (*see* Database references).

All data have been carefully checked and validated, mainly in order to avoid mis-classification and multiple counting of identical sets of sample information reported in different papers.

This database includes activity concentration measurements of several categories of building materials, in particular:

- products (bricks, concrete, cements) – about 8400 samples;
- aggregates (sand, gravel, etc.) about 3600 samples
- natural raw materials (tuff, lime, clay, gypsum, etc.) – about 2100 samples – used in bulk amounts and for some superficial application
- industrial by-products: by-product gypsum (434 samples), coal ashes (5908 samples), metallurgical slags (774 samples) and bauxite residues/red mud (71 samples); total about 7190 samples;
- others such as wood, tiles, etc. (about 1550 samples) and natural stones used as superficial products (about 610 samples).

The total number of samples, as already described in a previous paper (1), is certainly an underestimation. Indeed, in some publications only the activity concentration average values are reported, without specifying the number of samples analysed. In these cases, the value 1 was assigned to the number of samples *N*.

^a In the database ^{238}U activity concentration is considered as equivalent to ^{226}Ra one and *vice versa*.

Table A. Summary of all data collected

| Country | Total data | Data with activity concentration | | Data with only emanation/ exhalation rate data |
|--------------------|--------------|----------------------------------|------------------------------------|---|
| | | total | with emanation/ exhalation rate | |
| Austria | 126 | 126 | | |
| Belgium | 250 | 249 | 40 | 1 |
| Bulgaria | 42 | 42 | | |
| Cyprus | 99 | 99 | | |
| Czech Republic | 6745 | 6745 | | |
| Denmark | 326 | 326 | 69 | |
| Estonia | 16 | 16 | | |
| Finland | 530 | 530 | 20 | |
| France | 104 | 104 | 73 | |
| Germany | 1042 | 711 | 27 | 331 |
| Greece | 1455 | 1454 | 198 | 1 |
| Hungary | 1511 | 1511 | | |
| Ireland | 57 | 57 | | |
| Italy | 1112 | 1105 | 285 | 7 |
| Latvia | 3 | 3 | | |
| Lithuania | 9 | 9 | | |
| Luxembourg | 126 | 126 | | |
| Netherlands | 269 | 269 | 124 | |
| Poland | 5729 | 5729 | 58 | |
| Portugal | 145 | 128 | 78 | 17 |
| Romania | 635 | 635 | 4 | |
| Slovakia | 2148 | 2148 | 29 | |
| Slovenia | 7 | 7 | | |
| Spain | 426 | 426 | | |
| Sweden | 648 | 648 | | |
| United Kingdom | 249 | 249 | 17 | |
| Total EU MS | 23809 | 23469 | 1022 | 357 |
| Macedonia | 30 | 30 | | |
| Norway | 219 | 206 | 10 | 13 |
| Switzerland | 86 | 86 | 86 | |
| Turkey | 86 | 86 | | |
| Total | 24230 | 23860 | 1118 | 370 |

It is important to underline that measurements published in literature and collected in the database were generally performed for radiation protection purposes on samples of materials presumed to be among the most active ones, without claim to be representative at national level. Therefore, these data cannot contribute to elaborate a representative snapshot of building materials in the Europe.

In this report, the data on activity concentrations are organized in 30 tables, one for each country. In each table data are divided into categories of building materials and their constituents, with particular attention to the industrial by-products residues (in *italic* in the following list), generally called NORM (Naturally Occurring Radioactive Material) residues:

- Brick;
- Concrete;
- Cement;
- Aggregates;
- Tiles;

- Natural raw materials;
- Natural covering stones;
- Ashes (fly and bottom);
- Bauxite residues/red mud;
- Byproduct Gypsum;
- Metallurgical slag.

Table 31 presents radon emanation and radon exhalation rate data of about 1500 samples from countries with available data. Due to the scarcity of data, this lay out was considered more appropriate. Information about sample density and thickness are also present when reported in the relevant reference. Data in Table 31 are referred both to samples with information on activity concentration in Tables from 1 to 30 (fourth column in Table A), both to a sub set of samples with only information on radon emanation and exhalation rate (fifth column in Table 5). In Tables from 1 to 30 samples with emanation/exhalation rate data in Table 31 are marked with "^". However, for these samples only values about ^{226}Ra are reported in Table 31, since it is the significant activity concentration information regarding radon.

Considered the huge amount of data, in order to reduce the table sizes abbreviations have been introduced to shorten sample names and categories of information reported. In Table B the legend of abbreviations is shown.

Table B. Legend of abbreviations

| Abbreviations | Extended term |
|---------------|---------------------|
| BA | Bottom Ash |
| BFS | Blast Furnace Slag |
| d | Sample Thickness |
| FA | Fly Ash |
| N. | Number Of Samples |
| PZL | Pozzolana |
| PFA | Pulverized Fuel Ash |
| PHG | Phosphogypsum |
| PTL | Portland |
| RM | Red Mud |

References

1. Trevisi R, D'Alessandro M, Risica S, Nuccetelli C. Natural radioactivity in building materials in the European Union: a database and an estimate of radiological significance. *J Environ Radioact* 2012;105:11-20.
2. European Commission. *Radiation Protection 96. Enhanced radioactivity of building materials*. Luxembourg: European Commission; 1997.
3. Risica S, Bolzan C, Nuccetelli C. Radioactivity in building materials: experimental methods, calculations and an overview of the Italian situation, 1999. *Workshop "Radon in the Living Environment" (Athens, 19-23 April 1999)*, p. 415-428 (CD-ROM).
4. European Commission. *Radiation Protection 112. Radiological protection principles concerning the natural radioactivity of building materials*. Luxembourg: European Commission; 1999.
5. Council of the European Union. Council Directive 2013/59/EURATOM of 5 December 2013 laying down basic safety standards for protection against the dangers arising from exposure to ionising radiation, and repealing Directives 89/618/Euratom, 90/641/Euratom, 96/29/Euratom, 97/43/Euratom and 2003/122/Euratom. 2014. *Off J European Union* L 13/1, 17.1.2014.

**Tables of activity concentrations of building materials
used in 30 European countries**

Table 1 Austria
126 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks | 32 | 38 | 71 | 20 | 45 | 112 | 16 | 635 | 880 | 520 | AU1 |
| Concrete | | | | | | | | | | | |
| Concrete | 1 | 15 | 21 | 7 | 14 | 57 | 3 | 164 | 382 | 16 | AU1 |
| Cement | | | | | | | | | | | |
| Cements | 18 | 27 | 49 | 11 | 14 | 26 | 10 | 210 | 286 | 89 | AU1 |
| Aggregates | | | | | | | | | | | |
| Sand gravel | 6 | 14 | 18 | 6 | 15 | 67 | 2 | 171 | 433 | | AU1 |
| Tiles | | | | | | | | | | | |
| Tiles | 5 | 48 | 91 | 18 | 56 | 135 | 13 | 528 | 819 | 343 | AU1 |
| Natural raw materials | | | | | | | | | | | |
| Limestones | 4 | 9 | 19 | 2 | 3 | 5 | 1 | 34 | 63 | | AU1 |
| Others | | | | | | | | | | | |
| Plasters | 7 | 33 | 50 | 10 | 19 | 33 | | 288 | 431 | 12 | AU1 |
| Accessories (glass, asbestos, asphalt, binders etc.) | 3 | 8 | 12 | 5 | 2 | 4 | | 14 | 17 | 5 | AU1 |
| Natural covering stones | | | | | | | | | | | |
| Granites | 22 | 55 | 117 | 10 | 25 | 186 | 16 | 911 | 1320 | 383 | AU1 |
| Basalts | 4 | 23 | 30 | 14 | 30 | 37 | 18 | 307 | 496 | 150 | AU1 |
| Marbles | 8 | 7 | 26 | 1 | 2 | 5 | | 27 | 166 | | AU1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| By-products Gypsum | | | | | | | | | | | |
| Chemical gypsum | 16 | 48 | 315 | 6 | 5 | 12 | 3 | 151 | 226 | | AU1 |

Numbers in Bold Italic= MDA (minimum detection level)

Table 2 Belgium
249 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------|----|-------------------------------|-----|-----------|-------------------------------|-----|-----------|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Facade bricks | 13 | 41 | 73 | 31 | 36 | 44 | 26 | 569 | 810 | 400 | BE1 |
| Building block | 4 | 47 | 62 | 40 | 47 | 50 | 43 | 815 | 980 | 650 | BE1 |
| Brick [^] | 14 | 32 | 85 | 15 | 33 | 52 | 15 | | | | BE2 |
| Brick | 47 | 34 | 85 | 15 | 32 | 63 | 16 | | | | BE3 |
| Concrete | | | | | | | | | | | |
| Casted concrete | 13 | 21 | 28 | 14 | 18 | 26 | 13 | 280 | 460 | 170 | BE1 |
| Concrete blocks | 3 | 15 | 23 | 7 | 9 | 15 | 6 | 115 | 160 | 80 | BE1 |
| Argex block | 3 | 42 | 58 | 22 | 42 | 53 | 22 | 490 | 550 | 430 | BE1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----------|-------------------------------|-----|-----------|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Areated concrete | 4 | 6 | 7 | 5 | 5 | 6 | 5 | 85 | 170 | 30 | BE1 |
| Concrete | 1 | 24 | 30 | 16 | 27 | 40 | 13 | | | | BE2 |
| Concrete blocks | 5 | 31 | 58 | 10 | 34 | 72 | 10 | | | | BE3 |
| Cellular concrete | 2 | 11 | | | 11 | | | | | | BE2 |
| Cement | | | | | | | | | | | |
| Cement | 2 | 62 | 81 | 44 | 76 | 130 | 22 | | | | BE2 |
| Cement p50 | 1 | 37 | | | 22 | | | 190 | | | BE1 |
| Cement p40 | 1 | 53 | | | 31 | | | 110 | | | BE1 |
| Cement hk40 | 1 | 64 | | | 51 | | | 250 | | | BE1 |
| Cement ppz30 | 1 | 51 | | | 43 | | | 470 | | | BE1 |
| Cement | 20 | 47 | 163 | 10 | 54 | 148 | 10 | | | | BE3 |
| Aggregates | | | | | | | | | | | |
| Sand-lime ballast | 1 | 15 | | | 12 | | | 140 | | | BE1 |
| Broken rubble | 1 | 5 | | | 7 | | | 160 | | | BE1 |
| Rolled rubble | 1 | 14 | | | 16 | | | 310 | | | BE1 |
| Porphyry rubble | 1 | 18 | | | 7 | | | 170 | | | BE1 |
| Sand o/2 | 1 | 9 | | | 10 | | | 340 | | | BE1 |
| Sand o/5 | 1 | 10 | | | 12 | | | 380 | | | BE1 |
| Sand, gravel | 3 | 19 | 24 | 13 | 21 | 27 | 13 | | | | BE3 |
| Slag aggregate | 1 | 81 | | | 37 | | | | | | BE2 |
| Natural raw materials | | | | | | | | | | | |
| Stone (11 out of 14 limestone) | 14 | 19 | 50 | 5 | 16 | 84 | 5 | 240 | 1020 | 10 | BE1 |
| Limestone | 1 | 21 | | | 5 | | | | | | BE3 |
| Gypsum | 1 | 10 | | | 10 | | | | | | BE3 |
| Gypsum plasterboard^ | 14 | 11 | | | 11 | | | | | | BE2 |
| Gypsum board | 1 | 10 | | | 30 | | | 5 | | | BE1 |
| Gypsum plaster | 6 | 13 | 43 | 6 | 5 | 5 | 5 | 80 | 120 | 20 | BE1 |
| Natural covering stones | | | | | | | | | | | |
| Schist | 1 | 33 | | | 47 | | | | | | BE3 |
| Phorphyry | 1 | 27 | | | 32 | | | | | | BE3 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Byproduct gypsum | | | | | | | | | | | |
| Sulphogypsum | 3 | 25 | 40 | 10 | 38 | 39 | 10 | | | | BE3 |
| Sulphogypsum powder | 1 | 41 | | | 37 | | | | | | BE2 |
| PHG | 27 | 442 | 848 | 333 | 10 | | | | | | BE3 |
| PHG board^ | 22 | 430 | 520 | 330 | 11 | | | | | | BE2 |
| PHG powder | 7 | 420 | 480 | 370 | 11 | | | | | | BE2 |
| Metallurgical slag | | | | | | | | | | | |
| BFS | 2 | 85 | 91 | 79 | 41 | 44 | 38 | | | | BE3 |

Numbers in Bold Italic= MDA (minimum detection level)

^ Data on emanation and/or exhalation of a subgroup of samples are reported in Table 31

Table 3 Bulgaria
42 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks | 1 | 42 | | | 43 | | | 600 | | | EU2 |
| Concrete | | | | | | | | | | | |
| Concrete | 1 | 19 | | | 17 | | | 200 | | | EU2 |
| Cement | | | | | | | | | | | |
| Cement | 1 | 29 | | | 19 | | | 160 | | | EU2 |
| Aggregates | | | | | | | | | | | |
| Concrete ballast | 1 | 30 | | | 30 | | | 700 | | | EU2 |
| Tiles | | | | | | | | | | | |
| Wall Tiles | 1 | 110 | | | 52 | | | 140 | | | EU2 |
| Stone Tiles | 1 | 19 | | | 9 | | | 100 | | | EU2 |
| Natural raw materials | | | | | | | | | | | |
| Clay | 1 | 30 | | | 50 | | | 180 | | | EU2 |
| Gypsum | 17 | 10 | 14 | 6 | 5 | 20 | 1 | 40 | 61 | 15 | EU1 |
| Gypsum | 1 | 7 | | | 2 | | | | | | EU2 |
| Natural covering stones | | | | | | | | | | | |
| Marble | 11 | 11 | 26 | 1 | 4 | 24 | 1 | 177 | 1400 | 13 | EU1 |
| Marble | 1 | 2 | | | 2 | | | 1 | | | EU2 |
| Granite | 1 | 90 | | | 60 | | | 1100 | | | EU2 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| Coal ash and slag | 1 | 120 | | | 60 | | | 500 | | | EU2 |
| Byproduct Gypsum | | | | | | | | | | | |
| From phosphate rocks | 1 | 400 | | | 9 | | | 5 | | | EU2 |
| From apatite | 1 | 18 | | | 25 | | | 1 | | | EU2 |
| Mineral sand | | | | | | | | | | | |
| Mineral sand | 1 | 60 | | | 36 | | | 700 | | | EU2 |

Table 4 Cyprus
99 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Grey clay (Per Xorio) | 1 | 28 | | | 8 | | | 321 | | | CY1 |
| Grey clay (Tseri) | 2 | 13 | | | 4 | | | 230 | | | CY1 |
| Grey clay brick (Tseri/Ayia Varnara) | 1 | 0.2 | | | 6 | | | 293 | | | CY1 |
| Mixture of red and grey clay for bricks | 1 | 0.2 | | | 5 | | | 192 | | | CY1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Mixture of red and grey clay for bricks | 1 | 4 | | | 4 | | | 165 | | | CY1 |
| Red clay (Levkara) | 1 | 0.1 | | | 2 | | | 59 | | | CY1 |
| Red clay (Levkara/Lythrondonta) | 1 | 14 | | | 4 | | | 102 | | | CY1 |
| Red clay brick (Kornos) | 2 | 0.1 | | | 3 | | | 66 | | | CY1 |
| Cement | | | | | | | | | | | |
| EN 197-1 Cem I 42.5 R | 1 | 23 | | | 9 | | | 161 | | | CY1 |
| EN 197-1 Cem I 52.5 N | 1 | 4 | | | 8 | | | 92 | | | CY1 |
| EN 197-1 Cem II A/L 42.5 N | 1 | 24 | | | 5 | | | 4 | | | CY1 |
| EN 197-1 Cem II/A-M (L-S) 42.5 R | 1 | 37 | | | 12 | | | 209 | | | CY1 |
| EN 197-1 Cem II/A-M (L-S) 52.5 | 1 | 33 | | | 10 | | | 151 | | | CY1 |
| EN 197-1 Cem II/A-P 42.5 N | 1 | 25 | | | 11 | | | 194 | | | CY1 |
| EN 197-1 Cem II/B-M (L-S) 32.5 R | 1 | 20 | | | 10 | | | 207 | | | CY1 |
| EN 197-1 Cem II/A-P 42.5 N | 1 | 32 | | | 12 | | | 199 | | | CY1 |
| Aggregates | | | | | | | | | | | |
| Sand (Mitsero) | 1 | 6 | | | 0 | | | 41 | | | CY1 |
| Tiles | | | | | | | | | | | |
| Red clay (Xylofagou) for tiles | 1 | 34 | | | 16 | | | 377 | | | CY1 |
| Cement tile Mantonella-Lydia | 1 | 12 | | | 2 | | | 4 | | | CY1 |
| Natural raw materials | | | | | | | | | | | |
| Sandstone calcareous (Kellia) | 3 | 40 | | | 4 | | | 73 | | | CY1 |
| Limestone calcareous (Szomenos) | 1 | 31 | | | 6 | | | 147 | | | CY1 |
| Limestone Yfalogenous (Xylofagou) | 4 | 7 | | | 1 | | | 5 | | | CY1 |
| Chalk (Kalo Xorio) | 1 | 34 | | | 6 | | | 119 | | | CY1 |
| Limestone (Androlykou) | 1 | 21 | | | 0.3 | | | 7 | | | CY1 |
| Gypsos (Toxni) (for cement) | 1 | 60 | | | 3 | | | 40 | | | CY1 |
| Chalk (Kalavasos) (for cement) | 1 | 12 | | | 7 | | | 92 | | | CY1 |
| Limestone (Armenoxori) (for cement) | 1 | 37 | | | 1 | | | 8 | | | CY1 |
| Marl (Vasiliko) (for cement) | 1 | 48 | | | 7 | | | 289 | | | CY1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Natural covering stones | | | | | | | | | | | |
| Diabase rock (Stavrovouni) | 6 | 0.8 | | | 0.3 | | | 61 | | | CY1 |
| Diabase rock (Pelendri) | 3 | 0.1 | | | 0.6 | | | 138 | | | CY1 |
| Diabase rock (Sia) | 3 | 1 | | | 0.7 | | | 110 | | | CY1 |
| Diabase rock (Vasa) | 2 | 3 | | | 0.5 | | | 113 | | | CY1 |
| Diabase rock (Pareklissia) | 2 | 3 | | | 1.0 | | | 42 | | | CY1 |
| Diabase rock (Mosfiloti) | 1 | 4 | | | 1.1 | | | 69 | | | CY1 |
| Diabase rock (Pyrga) | 1 | 5 | | | 0.5 | | | 56 | | | CY1 |
| Granite (imported) | 28 | 77 | 588 | 1 | 149 | 906 | 17 | 1215 | 1606 | 50 | GR6 |
| Granite (imported) | 8 | 60 | 215 | 0.2 | 92 | 260 | 2 | 1141 | 1576 | 350 | CY1 |
| Marble (imported) | 10 | 26 | 79 | 0.1 | 0.6 | 2 | 0.1 | 16 | 66 | 0.2 | CY1 |

Numbers in Bold Italic= MDA (minimum detection level)

Table 5 Czech Republic
6745 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|------------------------------|------|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Brick | 209 | 46 | | | 49 | | | 616 | | | CZ1 |
| Refractory brick | 28 | 113 | | | 86 | | | 312 | | | CZ1 |
| Clay brick | 279 | 49 | | | 48 | | | 567 | | | CZ1 |
| Concrete | | | | | | | | | | | |
| Concrete | 491 | 33 | | | 24 | | | 495 | | | CZ1 |
| Areated concrete | 1221 | 88 | | | 54 | | | 455 | | | CZ1 |
| Concrete-BA | 16 | 30 | | | 44 | | | 268 | | | CZ1 |
| Concrete-BA | 28 | 936 | | | 72 | | | 459 | | | CZ1 |
| Cement | | | | | | | | | | | |
| Clinker | 10 | 31 | | | 20 | | | 193 | | | CZ1 |
| Cement | 496 | 46 | | | 19 | | | 237 | | | CZ1 |
| Aggregates | | | | | | | | | | | |
| Aggregates | 1240 | 48 | | | 42 | | | 664 | | | CZ1 |
| Sand | 383 | 22 | | | 21 | | | 624 | | | CZ1 |
| gravel | 154 | 21 | | | 21 | | | 519 | | | CZ2 |
| Natural raw materials | | | | | | | | | | | |
| Limestone | 27 | 9 | | | 5 | | | 76 | | | CZ1 |
| Zircon sand | 2 | 3692 | | | 1344 | | | 62 | | | CZ1 |
| Lime | 73 | 15 | | | 7 | | | 90 | | | CZ1 |
| Clay | 312 | 72 | | | 58 | | | 527 | | | CZ2 |
| Shale | 37 | 174 | | | 131 | | | 493 | | | CZ1 |
| Gypsum | 34 | 19 | | | 12 | | | 168 | | | CZ1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|------|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| BA | 159 | 219 | | | 87 | | | 491 | | | CZ1 |
| FA | 1378 | 146 | | | 86 | | | 669 | | | CZ1 |
| Silica fume | | | | | | | | | | | |
| Silica fume | 42 | 27 | | | 36 | | | 1443 | | | CZ1 |
| Byproduct Gypsum | | | | | | | | | | | |
| PHG | 22 | 115 | | | 31 | | | 95 | | | CZ1 |
| Metallurgical slag | | | | | | | | | | | |
| Metallurgical slag | 104 | 110 | | | 28 | | | 154 | | | CZ1 |

Table 6 Denmark
326 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|----------|-----------------------------|------|-----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Clay Bricks | 79 | 42 | 86 | 23 | 34 | 58 | 21 | 630 | 900 | 340 | DK1 |
| White Bricks (sand-lime) | 4 | 8 | 11 | 6 | 6 | 11 | 4 | 280 | 340 | 160 | DK1 |
| Bricks [^] | 1 | 42 | | | | | | | | | DK1 |
| Concrete | | | | | | | | | | | |
| Ready mix concrete | 6 | 16 | 24 | 13 | 13 | 17 | 9 | 360 | 420 | 280 | DK1 |
| Aerated+Alum Shale | 2 | 670 | | | 53 | | | 1190 | | | DK1 |
| Light weight aggregate | 3 | 40 | 43 | 36 | 45 | 51 | 37 | 910 | 1000 | 860 | DK1 |
| Aerated | 3 | 15 | 25 | 9 | 10 | 12 | 8 | 280 | 320 | 230 | DK1 |
| Concrete (5% FA-cement) [^] | 1 | 10 | | | | | | | | | DK2 |
| Concrete (10% FA-cement) [^] | 1 | 11 | | | | | | | | | DK2 |
| Concrete (15% FA-cement) [^] | 1 | 12 | | | | | | | | | DK2 |
| Concrete (20% FA-cement) [^] | 1 | 13 | | | | | | | | | DK2 |
| Concrete (25% FA-cement) [^] | 1 | 14 | | | | | | | | | DK2 |
| concrEte (30% FA-cement) [^] | 1 | 14 | | | | | | | | | DK2 |
| Concrete (25% FA-PTL cement) [^] | 1 | 15 | | | | | | | | | DK2 |
| Concrete [^] | 1 | 35 | | | | | | | | | DK2 |
| Cement | | | | | | | | | | | |
| Cement | 6 | 20 | 30 | 9 | 12 | 21 | 4 | 90 | 140 | 20 | DK1 |
| Cement (5% FA) [^] | 1 | 28 | | | 22 | | | 140 | | | DK2 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|-----|-------------------------------|-----|----------|-------------------------------|-----|----------|-----------------------------|------|-----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Cement PTL (25% FA) | 1 | 65 | | | 52 | | | 240 | | | DK2 |
| Aggregates | | | | | | | | | | | |
| Concrete ballast (fine+coarse aggregates) | 107 | 19 | 95 | 4 | 13 | 56 | 4 | 360 | 1150 | 240 | DK1 |
| Sand [^] | 1 | 7 | | | 6 | | | 160 | | | DK2 |
| Granite chippings [^] | 1 | 59 | | | | | | | | | DK2 |
| Gravel | 1 | 9 | | | 10 | | | 190 | | | DK2 |
| Natural raw materials | | | | | | | | | | | |
| Lime stone | 5 | 6 | | | 4 | | | 20 | | | DK1 |
| Gypsum | 12 | 8 | 13 | 4 | 4 | 6 | 4 | 20 | 35 | 20 | DK1 |
| Others | | | | | | | | | | | |
| Insulation Material | 5 | 40 | | | 40 | | | 190 | | | DK1 |

INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS

| | | | | | | | | | | | |
|-----------------------|----|-----|-----|-----|-----|-----|-----|-----|------|-----|-----|
| Ashes | | | | | | | | | | | |
| Coal ash [^] | 15 | 140 | 180 | 120 | 78 | 88 | 66 | 570 | 670 | 480 | DK2 |
| Coal ash [^] | 16 | 170 | 200 | 130 | 160 | 190 | 120 | 290 | 430 | 190 | DK2 |
| Coal ash [^] | 14 | 160 | 190 | 130 | 130 | 160 | 100 | 520 | 840 | 260 | DK2 |
| Coal ash [^] | 12 | 150 | 170 | 120 | 79 | 93 | 77 | 710 | 910 | 270 | DK2 |
| Coal ash | 12 | 153 | 210 | 140 | 127 | 170 | 90 | 413 | 660 | 200 | DK2 |
| FA | 1 | 150 | | | 81 | | | 640 | | | DK2 |
| Ash | 10 | 150 | 210 | 110 | 90 | 160 | 74 | 730 | 1030 | 190 | DK1 |

Numbers in Bold Italic= MDA (minimum detection level)

[^] Data on emanation and/or exhalation are reported in Table 31

Table 7 Estonia
16 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|-----------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Aseri brick | 3 | 20 | 21 | 20 | 30 | 31 | 30 | 440 | 449 | 436 | EST1 |
| Misso Light brick | 1 | 13 | | | 13 | | | 145 | | | EST1 |
| Misso Dark brick | 1 | 18 | | | 19 | | | 207 | | | EST1 |
| Ash blocks | 1 | 27.3 | | | 14 | | | 308 | | | EST1 |
| Concrete | | | | | | | | | | | |
| Concrete | 1 | 35 | | | 11 | | | 207 | | | EST1 |
| Cement | | | | | | | | | | | |
| Kunda cement | 1 | 47 | | | 21 | | | 587 | | | EST1 |
| Tiles | | | | | | | | | | | |
| Grosso 311 floor tile | 1 | 64 | | | 82 | | | 344 | | | EST1 |
| Pronto 147 floor tile | 1 | 49 | | | 86 | | | 285 | | | EST1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Natural raw materials | | | | | | | | | | | |
| Clay (Siimusti) | 1 | 69 | | | 82 | | | 678 | | | EST1 |
| Clay (finnish) | 1 | 54 | | | 59 | | | 748 | | | EST1 |
| Clay (german) | 1 | 36 | | | 55 | | | 447 | | | EST1 |
| Stone (Kolumbia) | 1 | 26 | | | 28 | | | 480 | | | EST1 |
| Gypsum board | 1 | 4 | | | 0.8 | | | 7 | | | EST1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| Ash blocks | 1 | 27 | | | 14 | | | 308 | | | EST1 |

Table 8 Finland
530 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------|-----|-------------------------------|-----|-----------|-------------------------------|-----|-----------|-----------------------------|------|-----|------------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Clay bricks | 38 | 80 | 134 | 37 | 62 | 92 | 38 | 986 | 1185 | 780 | FIN2 |
| White bricks (sand-lime) | 4 | 23 | 25 | 20 | 21 | 29 | 15 | 622 | 699 | 537 | FIN2, FIN3 |
| Concrete | | | | | | | | | | | |
| Concrete | 15 | 53 | 70 | 36 | 38 | 53 | 28 | 838 | 960 | 791 | FIN2 |
| Concrete^ | 1 | 42 | | | | | | | | | FIN2 |
| Concrete^ | 1 | 49 | | | | | | | | | FIN2 |
| Concrete ^ | 1 | 60 | | | | | | | | | FIN2 |
| Concrete ^ | 1 | 66 | | | | | | | | | FIN2 |
| Concrete^ | 1 | 60 | | | | | | | | | FIN2 |
| Concrete ^ | 1 | 63 | | | | | | | | | FIN2 |
| Siporex-exp. concrete | 2 | 49 | 53 | 45 | 36 | 40 | 31 | 359 | 385 | 333 | FIN2 |
| Concrete^ | 11 | 33 | 43 | 18 | 34 | 48 | 20 | 800 | 1010 | 490 | FIN3, FIN4 |
| Slag aggregates concrete^ | 1 | 75 | | | 59 | | | 400 | | | FIN2, FIN3 |
| Cement | | | | | | | | | | | |
| Cement | 11 | 40 | 84 | 15 | 20 | 55 | 9 | 251 | 336 | 169 | FIN2 |
| Aggregates | | | | | | | | | | | |
| Concrete ballast | 266 | 34 | 146 | 8 | 39 | 225 | 10 | 964 | 1856 | 394 | FIN2 |
| Natural raw materials | | | | | | | | | | | |
| Stones | 1 | 68 | 210 | 10 | 93 | 370 | 10 | 1188 | 1700 | 250 | EU2 |
| Gypsum | 1 | 7 | | | 2 | | | 25 | | | FIN2 |
| Others | | | | | | | | | | | |
| Insulation wool | 8 | 16 | 31 | 4 | 7 | 14 | 2 | 157 | 275 | 90 | FIN2 |
| Wood | 2 | 0.4 | 0.5 | 0.3 | 0.7 | 2 | 0.2 | 10 | 12 | 8 | FIN2 |
| Natural covering stones | | | | | | | | | | | |
| Anorthosite | 1 | 8 | | | 8 | | | 310 | | | FIN1 |
| Diabase | 1 | 2 | | | 4 | | | 86 | | | FIN1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Gabro | 1 | 21 | | | 19 | | | 400 | | | FIN1 |
| Gneiss | 1 | 25 | | | 68 | | | 860 | | | FIN1 |
| Granite | 13 | 94 | 170 | 12 | 141 | 380 | 23 | 1418 | 1690 | 860 | FIN1 |
| Granodiorite | 1 | 44 | | | 37 | | | 1320 | | | FIN1 |
| Migmatite | 1 | 33 | | | 94 | | | 1700 | | | FIN1 |
| Migmatite | 1 | 20 | | | 22 | | | 650 | | | FIN1 |
| Soap stone | 1 | 17 | | | 2 | | | 20 | | | FIN1 |
| Soap stone | 1 | 1 | | | 1 | | | 27 | | | FIN1 |
| Soap stone | 1 | 2 | | | 4 | | | 14 | | | FIN1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| Coal ash | 25 | 130 | | | 78 | | | 600 | | | FIN4 |
| Peat ash | 33 | 120 | | | 46 | | | 390 | | | FIN4 |
| Byproduct Gypsum | | | | | | | | | | | |
| By-product gypsum [^] | 17 | 306 | 830 | 24 | 23 | 118 | 3 | 17 | 30 | 7 | FIN2 |
| By-product gypsum | 61 | 470 | | | 23 | | | 19 | | | FIN4 |
| Metallurgical slag | | | | | | | | | | | |
| BFS | 5 | 117 | 129 | 105 | 78 | 102 | 32 | 176 | 209 | 97 | FIN2 |

Numbers in **Bold Italic**= MDA (minimum detection level)

[^] Data on emanation and/or exhalation of 2 samples of this group are reported in Table 31

Table 9 France
104 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|-------------------------------------|----|-------------------------------|------|----------|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks [^] | 3 | 54 | 58 | 50 | 44 | 45 | 43 | | | | FR1 |
| Hollow brick [^] | 5 | 42 | 44 | 40 | 37 | 37 | 36 | | | | FR1 |
| Bricks | 1 | 99 | | | 96 | | | 58 | | | FR2 |
| Clay hollow brick | 1 | 133 | | | 106 | | | 118 | | | FR2 |
| Clear solid brick | 1 | 61 | | | 99 | | | 21 | | | FR2 |
| Refractory brick | 1 | 24 | | | 18 | | | 40 | | | FR2 |
| Concrete | | | | | | | | | | | |
| Concrete [^] | 5 | 13 | 13.4 | 12.6 | 13 | 15 | 12 | | | | FR1 |
| Concrete [^] | 3 | 13 | | | 12 | | | | | | FR1 |
| Concrete hollow blocks [^] | 2 | 8 | 12 | 5 | 4 | | | | | | FR1 |
| Concrete block | 1 | 13 | | | 10 | | | 14 | | | FR2 |
| Cellular concrete [^] | 4 | 9 | | | 7 | 8 | 6 | | | | FR1 |
| Siporex | 1 | 26 | | | 24 | | | 20 | | | FR2 |
| Cement | | | | | | | | | | | |
| Cement | 1 | 32 | | | 21 | | | 24 | | | FR2 |
| Cement tile | 1 | 111 | | | 109 | | | 52 | | | FR2 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------|----|-------------------------------|-----|------------|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Aggregates | | | | | | | | | | | |
| Sand | 1 | 13 | | | 11 | | | 22 | | | FR2 |
| Tiles | | | | | | | | | | | |
| Tile (ardesia)^ | 2 | 36 | 39 | 34 | 48 | 48 | 47 | | | | FR1 |
| Tile (faience)^ | 3 | 113 | 114 | 112 | 69 | 70 | 67 | | | | FR1 |
| Tile (faience) | 1 | 189 | | | 88 | | | 89 | | | FR2 |
| Tile (faience) | 1 | 208 | | | 56 | | | 18 | | | FR2 |
| Tile (faience) | 1 | 104 | | | 70 | | | 40 | | | FR2 |
| Tile (faience) | 1 | 218 | | | 101 | | | 48 | | | FR2 |
| Tile (green marble)^ | 3 | <u>1</u> | | | <u>2</u> | | | | | | FR1 |
| Tile (limestone) | 1 | <u>6</u> | | | <u>4</u> | | | 2 | | | FR2 |
| Tile (natural stone) | 1 | <u>10</u> | | | <u>5</u> | | | 1 | | | FR2 |
| Tile (sandstone) | 1 | 176 | | | 69 | | | 68 | | | FR2 |
| Tile (stoneware)^ | 5 | 141 | 142 | 139 | 68 | 69 | 66 | | | | FR1 |
| Tile (stoneware)^ | 4 | 68 | 74 | 62 | 59 | 54 | 63 | | | | FR1 |
| Tile (terracotta)^ | 2 | 61 | 67 | 54 | 66 | 69 | 62 | | | | FR1 |
| Tile (terracotta)^ | 2 | 49 | 52 | 46 | 66 | 68 | 64 | | | | FR1 |
| Tile (terracotta) | 1 | 76 | | | 80 | | | 63 | | | FR2 |
| Tile (terracotta) | 1 | 86 | | | 90 | | | 17 | | | FR2 |
| Tile (white marble)^ | 4 | <u>2</u> | | | <u>2</u> | | | | | | FR1 |
| Tile (white marble) | 1 | <u>5</u> | | | <u>4</u> | | | <u>1</u> | | | FR2 |
| Natural raw materials | | | | | | | | | | | |
| Gypsum | 1 | 15 | | | 8 | | | 8 | | | FR2 |
| Natural covering stones | | | | | | | | | | | |
| Stone slab^ | 3 | | | 3.4 | <u>2.7</u> | 2.7 | 2.6 | | | | FR2 |
| Granite^ | 13 | <u>370</u> | 380 | 360 | <u>672</u> | 570 | 773 | | | | FR1 |
| Ardesia | 1 | 69 | | | 115 | | | 91 | | | FR2 |
| Ardesia artificial | 1 | 54 | | | 29 | | | 7 | | | FR2 |
| Others | | | | | | | | | | | |
| Plaster^ | 2 | 3 | | | 2 | | | | | | FR1 |
| Plaster^ | 6 | <u>11</u> | 14 | 8 | 2 | | | | | | FR1 |
| Plaster^ | 2 | <u>4.9</u> | 5,1 | 4.6 | 3 | | | | | | FR1 |
| Plaster | 1 | 9 | | | 6 | | | 2 | | | FR2 |
| Rockwool | 3 | 121 | 136 | 106 | 65 | 93 | 50 | 23 | 27 | 16 | FR2 |
| Glass wool IBR | 1 | 340 | | | 59 | | | 21 | | | FR2 |
| Glass wool Glasco | 1 | 34 | | | 19 | | | 17 | | | FR2 |
| Glass wool Thermolan | 1 | 30 | | | 22 | | | 25 | | | FR2 |
| Mortar | 1 | 16 | | | 4 | | | 2 | | | FR2 |

Numbers in Bold Italic= MDA (minimum detection level)

Numbers in Bold underline= average from minimum and maximum

^ Data on emanation and/or exhalation of a subgroup of samples are reported in Table 31

Table 10 Germany
711 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|-----|-------------------------------|-----|-----------|-------------------------------|-----|-----------|-----------------------------|------|-----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Clay bricks | 1 | 50 | 200 | 10 | 52 | 200 | 12 | 700 | 2000 | 100 | GE3 |
| Hollow brick | 1 | 40 | 59 | 15 | 25 | 52 | 4 | 320 | 800 | 60 | GE3 |
| Bricks | 132 | 96 | | | 96 | | | 592 | | | EU3 |
| Lime sand bricks | 3 | 8 | 10 | 4 | 6 | 7 | 3 | 115 | 180 | 35 | GE1 |
| Bricks | 27 | 48 | 63 | 38 | 57 | 98 | 37 | 719 | 1200 | 470 | GE1 |
| Red-slime bricks | 23 | 281 | | | 233 | | | 333 | | | EU3 |
| Bricks^ | 1 | 68 | | | 37 | | | | | | GE2 |
| Concrete | | | | | | | | | | | |
| Concrete | 1 | 30 | 92 | 7 | 23 | 71 | 4 | 450 | 1300 | 50 | GE3 |
| Areated concrete | 1 | 15 | 80 | 6 | 10 | 60 | 1 | 200 | 800 | 40 | GE3 |
| Light-weight concrete | 1 | 30 | 90 | 20 | 30 | 80 | 20 | 1100 | 1600 | 700 | GE3 |
| Light-weight concrete with Pumice stone | 1 | 80 | 200 | 20 | 90 | 300 | 30 | 900 | 2000 | 500 | GE3 |
| Light-weight concrete with Expanded clay | 1 | 30 | 80 | 20 | 30 | 60 | 20 | 400 | 700 | 40 | GE3 |
| Light-weight concrete with Slag | 1 | 100 | 700 | 20 | 100 | 200 | 20 | 500 | 1000 | 300 | GE3 |
| Light-weight concrete with crashed bricks | 1 | 40 | 70 | 30 | 60 | 100 | 30 | 500 | 600 | 400 | GE3 |
| Light-weight concrete | 7 | 62 | 98 | 27 | 49 | 83 | 28 | 845 | 850 | 710 | GE1 |
| Aerated concrete | 10 | 18 | 26 | 8 | 12 | 19 | 5 | 193 | 350 | 97 | GE1 |
| Concrete | 69 | 67 | | | 63 | | | 555 | | | EU3 |
| Areated concrete^ | 5 | 19 | | | 30 | | | | | | GE2 |
| Heavy weight concrete^ | 5 | 52 | | | 15 | | | | | | GE2 |
| Cement | | | | | | | | | | | |
| Clinker | 1 | 50 | 200 | 10 | 52 | 200 | 12 | 700 | 2000 | 100 | GE3 |
| Cement | 1 | 97 | 330 | 23 | 20 | 37 | 11 | 320 | 500 | 110 | GE3 |
| PTL cement | 1 | 30 | 50 | 10 | 20 | 40 | 10 | 200 | 700 | 100 | GE3 |
| BFS cement | 1 | 60 | 100 | 20 | 80 | 200 | 30 | 100 | 200 | 40 | GE3 |
| Alluminium cement | 1 | 200 | 200 | 100 | 200 | 200 | 100 | 40 | | | GE3 |
| Cement | 19 | 44 | | | 44 | | | 192 | | | EU3 |
| Cement and mortar | 11 | 22 | 35 | 11 | 15 | 21 | 11 | 230 | 380 | 135 | GE1 |
| Azbest cement | 1 | 20 | 40 | 20 | 20 | 40 | 11 | 100 | 300 | 40 | GE3 |
| Aggregates | | | | | | | | | | | |
| Sand, gravel | 1 | 15 | 39 | 1 | 16 | 64 | 1 | 380 | 1200 | 3 | GE3 |
| Sand, gravel | 50 | 15 | | | 19 | | | 259 | | | EU3 |
| Tiles | | | | | | | | | | | |
| Wall tiles | 1 | 50 | 100 | 15 | 55 | 130 | 25 | 560 | 1000 | 250 | GE3 |
| Tiles and ceramics | 5 | 88 | 110 | 67 | 62 | 97 | 39 | 429 | 620 | 295 | GE1 |
| Stove tiles | 1 | 74 | | | 70 | | | 310 | | | GE3 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------|----|-------------------------------|-----|-----------|-------------------------------|-----|-----|-----------------------------|------|-----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Natural raw materials | | | | | | | | | | | |
| Clay (Schamotte) | 1 | 60 | 100 | 20 | 70 | 200 | 40 | 400 | 600 | 200 | GE3 |
| Tuff | 1 | 100 | 200 | 20 | 100 | 300 | 30 | 1000 | 2000 | 500 | GE3 |
| Tuff (Porphyritic) | 1 | 47 | 52 | 44 | 206 | 239 | 133 | 720 | 1700 | 22 | GE3 |
| Chalk sludge | 1 | 9 | | | 2 | | | 26 | | | GE3 |
| Lime, hydrated lime | 1 | 30 | 60 | 20 | 41 | 93 | 2 | 150 | | 20 | GE3 |
| Gypsum, anhydrite | 1 | 10 | 70 | 2 | 5 | 100 | 2 | 60 | 200 | 7 | GE3 |
| Clay (caolin) | 1 | 90 | 200 | 30 | 100 | 200 | 70 | 600 | 1000 | 200 | GE3 |
| Gypsum product | 5 | 8.6 | 13 | 4 | 3 | 6 | 2 | 51 | 120 | 20 | GE1 |
| Limestone^ | 5 | 9 | | | 15 | | | | | | GE2 |
| Gypsum ^ | 1 | 10 | | | 7 | | | | | | GE2 |
| Gypsum^ | 1 | 41 | | | 15 | | | | | | GE2 |
| Gypsum ^ | 1 | 37 | | | 18 | | | | | | GE2 |
| Limestone and marble | 20 | 19 | | | 19 | | | 37 | | | EU3 |
| Pumice^ | 1 | 48 | | | 30 | | | | | | GE2 |
| Pumice^ | 1 | 107 | | | 96 | | | | | | GE2 |
| Pumice^ | 1 | 48 | | | 22 | | | | | | GE2 |
| Pumice^ | 1 | 63 | | | 96 | | | | | | GE2 |
| Pumice stone | 20 | 111 | | | 126 | | | 1073 | | | EU3 |
| Sandstone^ | 1 | 11 | | | 7 | | | | | | GE2 |
| Clay, slit | 1 | 40 | 90 | 20 | 60 | 200 | 18 | 1000 | 2000 | 300 | GE3 |
| Natural covering stones | | | | | | | | | | | |
| Granite | 1 | 100 | 500 | 30 | 120 | 311 | 17 | 1000 | 4000 | 600 | GE3 |
| Granite | 34 | 96 | | | 81 | | | 1221 | | | EU3 |
| Granodiorite | 1 | 56 | 73 | 40 | 44 | 104 | 37 | 850 | 990 | 380 | GE3 |
| Syenite | 1 | 30 | | | 31 | | | 670 | | | GE3 |
| Dolerite | 1 | 20 | 29 | 10 | 30 | 44 | 8 | 290 | 380 | 22 | GE3 |
| Diabase | 1 | 16 | 25 | 10 | 8 | 12 | 4 | 170 | 210 | 100 | GE3 |
| Basalt | 1 | 26 | 36 | 6 | 29 | 37 | 9 | 270 | 380 | 190 | GE3 |
| Phonolite | 1 | 56 | | | 104 | | | 1270 | | | GE3 |
| Quartzporphyry | 1 | 54 | 56 | 15 | 77 | 98 | 53 | 1300 | 2100 | 1000 | GE3 |
| Quarystone (porphyry)^ | 1 | 44 | | | 44 | | | | | | GE2 |
| Ortophyre | 1 | 17 | | | 22 | | | 1300 | | | GE3 |
| Lamprophyre | 1 | 17 | 30 | 6 | 12 | 21 | 7 | 270 | 330 | 130 | GE3 |
| Augite porphyrite | 1 | 55 | 61 | 46 | 67 | 79 | 57 | 1100 | 1300 | 1000 | GE3 |
| Lava | 1 | 42 | 70 | 20 | 42 | 60 | 25 | 720 | 890 | 490 | GE3 |
| Granulit | 1 | 10 | 16 | 4 | 6 | 11 | 2 | 360 | 730 | 9 | GE3 |
| Amphibolite | 1 | 8 | | | 9 | 9 | 8 | 260 | 310 | 180 | GE3 |
| Serpentinite | 1 | 3 | | | 7 | | | 180 | | | GE3 |
| Schist (hornblende) | 1 | 13 | | | 14 | | | 380 | | | GE3 |
| Schist (fruct-phycides) | 1 | 38 | 45 | 34 | 59 | 73 | 56 | 780 | 930 | 760 | GE3 |
| Marble-limestone | 1 | 24 | 41 | 4 | 5 | 100 | 2 | 90 | 240 | 40 | GE3 |
| Marble-limestone | 20 | 19 | | | 19 | | | 37 | | | EU3 |
| Graywacke | 1 | 41 | 51 | 26 | 35 | 46 | 13 | 760 | 780 | 700 | GE3 |
| Oolite | 1 | 19 | | | 31 | | | 580 | | | GE3 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|------|------|-------------------------------|-----|-----|-----------------------------|------|-----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Travertine | 1 | 4 | | | 19 | | | 20 | | | GE3 |
| Sandstone-quartzite | 1 | 20 | 70 | 13 | 25 | 70 | 15 | 500 | 1100 | 40 | GE3 |
| Flint stone | 1 | 6 | | | 1 | | | 1 | | | GE3 |
| Augite | 1 | 65 | | | 51 | | | 970 | | | GE3 |
| Others | | | | | | | | | | | |
| Mortars | 7 | 27 | 53 | 11 | 19 | 31 | 6 | 226 | 310 | 120 | GE1 |
| Mineral wool | 7 | 35 | 80 | 16 | 22 | 64 | 5 | 155 | 350 | 49 | GE1 |
| Plaster | 19 | 8 | 22 | 2 | 6 | 31 | 1 | 75 | 220 | 12 | GE1 |
| Natural Plaster | 23 | 19 | | | 11 | | | 74 | | | EU3 |
| Floor screed mortars | 5 | 15 | 26 | 11 | 17 | 34 | 11 | 213 | 295 | 210 | GE1 |
| Ceramic raw materials | 15 | 46 | 115 | 15 | 54 | 135 | 20 | 664 | 1700 | 65 | GE1 |
| Wood-wool board | 1 | 21 | 25 | 19 | 12 | 14 | 11 | 210 | 360 | 50 | GE3 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| Lignite filter ash | 1 | 82 | 200 | 4 | 51 | 150 | 6 | 147 | 610 | 12 | GE3 |
| FA | 1 | 200 | 400 | 80 | 100 | 300 | 60 | 700 | 1450 | 300 | GE3 |
| Boiler slag | 1 | 68 | 110 | 24 | 54 | 120 | 7 | 200 | 330 | 20 | GE3 |
| FA | 28 | 211 | | | 130 | | | 703 | | | EU3 |
| Byproduct gypsum | | | | | | | | | | | |
| From apatite | 1 | 60 | 70 | 40 | 20 | | | | | | GE3 |
| From apatite | 2 | 56 | | | 19 | | | 37 | | | EU3 |
| From phosphorite | 1 | 600 | 1000 | 300 | 20 | 160 | 4 | 110 | 300 | 40 | GE3 |
| From phosphorite | 39 | 592 | | | 15 | | | 111 | | | GE3 |
| Unknown origin | 7 | 19 | | | 26 | | | 74 | | | EU3 |
| From desulfur.flue gas | 1 | 20 | 70 | 20 | 20 | | | 20 | | | EU3 |
| Metallurgical slag | | | | | | | | | | | |
| Copper slag (old) | 1 | 1500 | 2100 | 860 | 48 | 78 | 18 | 520 | 730 | 300 | GE3 |
| Copper slag (new) | 1 | 770 | 940 | 490 | 52 | 60 | 41 | 650 | 760 | 530 | GE3 |
| Nickel slag | 1 | 52 | | | 78 | | | 76 | | | GE3 |
| Nickel-manganese slag | 1 | 311 | | | 37 | | | 710 | | | GE3 |
| Aluminium slag | 1 | 14 | 16 | 12 | 8 | 9 | 6 | 750 | 960 | 360 | GE3 |
| Iron-chrom.-silicon slag | 1 | 9 | | | 6 | | | 10 | | | GE3 |
| Tin slag | 1 | 1100 | 1200 | 1000 | 300 | 340 | 230 | 330 | | | GE3 |
| Slagstone^ | 1 | 78 | | | 37 | | | | | | GE2 |
| Siemens-martin slag | 1 | 20 | | | 7 | | | 22 | | | GE3 |
| Lead slag | 1 | 270 | | | 36 | | | 200 | | | GE3 |
| Sulphur dross | 1 | 12 | 15 | 8 | 10 | | | 58 | 85 | 30 | GE3 |
| Steel slag | 1 | 13 | | | 7 | | | 21 | | | GE3 |
| Cupola slag | 1 | 110 | | | 47 | | | 210 | | | GE3 |
| Bessemer slag | 1 | 1000 | 1100 | 980 | 290 | 310 | 260 | | | | GE3 |
| Refining slag | 1 | 19 | 23 | 17 | 6 | 5 | 8 | 20 | 34 | 10 | GE3 |
| BFS | 1 | 100 | 200 | 4 | 100 | 300 | 30 | 500 | 1000 | 200 | GE3 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---------------------------------|----|-------------------------------|------|-----------|-------------------------------|------|-----|-----------------------------|------|-----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Bauxite residues/red mud | | | | | | | | | | | |
| RM | 1 | 200 | 800 | 20 | 400 | 1000 | 50 | 400 | 1000 | 20 | GE3 |
| RM | 1 | 122 | 1600 | 20 | 183 | 1000 | 50 | | | | GE4 |
| RM | 1 | 190 | | | 370 | | | 30 | | | GE5 |
| Other residues | | | | | | | | | | | |
| Waste rock - mining | 1 | 700 | 5900 | 36 | 70 | 100 | 27 | 700 | 1200 | 49 | GE3 |
| Phosphorus slag | 1 | 53 | 86 | 32 | 74 | 82 | 65 | 170 | 270 | 58 | GE3 |
| Process residues | 1 | 170 | 310 | 9 | 84 | 250 | 3 | 130 | 280 | 1 | GE3 |

Numbers in Bold Italic= MDA (minimum detection level)

^ Data on emanation and/or exhalation of a subgroup of samples are reported in Table 31

Table 11 Greece
1454 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|-------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Clay bricks^ | 13 | 37 | 48 | 25 | 42 | 56 | 27 | 686 | 895 | 476 | GR1 |
| Bricks^ | 3 | 36 | 83 | 25 | 52 | 65 | 35 | 732 | 1058 | 539 | GR13 |
| Red brick | 6 | 49 | 80 | 20 | 24 | 33 | 17 | 668 | 968 | 383 | GR2 |
| Brick^ | 3 | 52 | | | 41 | | | 551 | | | GR3 |
| Brick^ | 1 | 93 | | | 41 | | | 640 | | | GR3 |
| Brick^ | 1 | 81 | | | 42 | | | 704 | | | GR3 |
| Brick^ | 1 | 48 | | | 41 | | | 860 | | | GR3 |
| Brick^ | 1 | 63 | | | 42 | | | 659 | | | GR3 |
| Brick^ | 1 | 63 | | | 41 | | | 644 | | | GR3 |
| Clay bricks^ | 50 | 35 | 66 | 18 | 45 | 79 | 5 | 710 | 1050 | 10 | GR4 |
| Brick ^ | 1 | 42 | | | | | | | | | GR10 |
| Brick ^ | 1 | 46 | | | | | | | | | GR10 |
| Brick ^ | 1 | 41 | | | | | | | | | GR10 |
| Brick ^ | 1 | 53 | | | | | | | | | GR10 |
| Brick ^ | 1 | 45 | | | | | | | | | GR10 |
| Pumice stone brick^ | 1 | 48 | | | | | | | | | GR1 |
| Concrete | | | | | | | | | | | |
| Concrete - Thessaloniki | 5 | 46 | 73 | 24 | 7 | 11 | 4 | 246 | 330 | 153 | GR2 |
| Concrete^ | 20 | 14 | 41 | 7 | 3 | 5 | 1 | 70 | 96 | 57 | GR11 |
| Concrete block^ | 3 | 85 | | | 4 | | | 43 | | | GR3 |
| Concrete block^ | 1 | 41 | | | 5 | | | 32 | | | GR3 |
| Concrete block^ | 1 | 25 | | | 3 | | | 23 | | | GR3 |
| Concrete block^ | 2 | 37 | | | 5 | | | 35 | | | GR3 |
| Concrete block^ | 3 | 30 | | | 3 | | | 25 | | | GR3 |
| Concrete block^ | 3 | 26 | | | 4 | | | 30 | | | GR3 |
| Concrete block^ | 3 | 22 | | | 3 | | | 25 | | | GR3 |
| Concrete block^ | 4 | 48 | | | 6 | | | 96 | | | GR3 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|-------------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Concrete block [^] | 2 | 37 | | | 4 | | | 33 | | | GR3 |
| Concrete block [^] | 1 | 30 | | | 3 | | | 26 | | | GR3 |
| Concrete block [^] | 1 | 48 | | | 5 | | | 41 | | | GR3 |
| Concrete block [^] | 15 | 35 | 54 | 8 | 17 | 25 | 10 | 383 | 650 | 150 | GR4 |
| Concrete slab (cement with FA) [^] | 1 | 140 | | | | | | | | | GR1 |
| Concr. block cement Kamari 0%PFA [^] | 1 | 7 | | | | | | | | | GR10 |
| Concr. block cement Thessaloniki 0%PFA [^] | 1 | 8 | | | | | | | | | GR10 |
| Concr. block cement Kamari 10%PFA [^] | 1 | 11 | | | | | | | | | GR10 |
| Concr. block cement Thessaloniki 10%PFA [^] | 1 | 11 | | | | | | | | | GR10 |
| Concr. block cement Kamari 20%PFA [^] | 1 | 17 | | | | | | | | | GR10 |
| Concr. block cement Thessaloniki 20%PFA [^] | 1 | 11 | | | | | | | | | GR10 |
| Cement | | | | | | | | | | | |
| Cement | 4 | 64 | 77 | 38 | 15 | 16 | 11 | 457 | 553 | 330 | GR2 |
| PTL cement | 2 | 40 | 48 | 32 | 14 | 17 | 11 | 195 | 210 | 180 | GR10 |
| Cement black | 83 | 88 | 147 | 29 | 22 | 30 | 13 | 252 | 331 | 172 | GR1 |
| Cement white | 10 | 20 | 26 | 14 | 10 | 13 | 7 | 36 | 67 | 5 | GR1, GR9 |
| Cement [^] | 5 | 218 | 218 | 96 | 11 | | | 330 | | | GR3 |
| Cement [^] | 4 | 215 | | | 26 | | | 222 | | | GR3 |
| Cement [^] | 2 | 96 | | | 22 | | | 200 | | | GR3 |
| PTL cement 6% PFA | 2 | 71 | | | 19 | | | 240 | | | GR10 |
| PTL cement 10% PFA | 4 | 89 | 100 | 78 | 18 | 19 | 16 | 195 | 210 | 180 | GR10 |
| PTL cement 17% PFA | 2 | 99 | | | 41 | | | 320 | | | GR10 |
| PTL cement 20% PFA | 4 | 160 | 118 | | 19 | 19 | 19 | 245 | 260 | 230 | GR10 |
| PTL 3% PZL | 8 | 20 | 25 | 15 | 13 | 16 | 8 | 247 | 320 | 140 | GR4 |
| PTL 20% PZL | 22 | 92 | 140 | 34 | 31 | 46 | 14 | 310 | 390 | 218 | GR4 |
| Pozzolanic cement | 18 | 111 | 142 | 80 | 19 | 27 | 16 | 244 | 291 | 218 | GR5 |
| Cement white | 18 | 28 | 48 | 19 | 16 | 22 | 11 | 32 | 79 | | GR5 |
| Clinker | 2 | 60 | 87 | 32 | 15 | 19 | 11 | 180 | 210 | 150 | GR10 |
| Clinker | 1 | 15 | | | 14 | | | 141 | | | GR5 |
| Aggregates | | | | | | | | | | | |
| Sea sand | 6 | 10 | 13 | 7 | 12 | 16 | 8 | 224 | 302 | 145 | GR1, GR9 |
| Sand | 15 | 18 | 27 | 10 | 17 | 26 | 8 | 367 | 656 | 170 | GR4 |
| Gravel | 15 | 11 | 22 | 2 | 12 | 30 | 1 | 140 | 260 | 5 | GR4 |
| Sand | 20 | 12 | 15 | 7 | 3 | 10 | | | 60 | | GR5 |
| Pearlite | 1 | 46 | | | 56 | | | 1048 | | | GR1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|-----|-------------------------------|------|-----|-------------------------------|-----|-----|-----------------------------|-----------|------|--------------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Rock sand (limestone, sand)^ | 2 | <u>45</u> | 81 | 9 | <u>8</u> | 11 | 4 | <u>71</u> | 100 | 41 | GR3 |
| Sand | 13 | <u>3</u> | 5 | 1 | 3 | | | <u>19</u> | 37 | 1 | GR1 |
| Tiles | | | | | | | | | | | |
| Wall Tile | 1 | 58 | | | 46 | | | 409 | | | GR1 |
| Tile | 5 | 81 | 98 | 52 | 34 | 46 | 26 | 483 | | | GR2 |
| Tile^ | 2 | 89 | | | 41 | | | 885 | | | GR3 |
| Tile^ | 1 | 26 | | | 56 | | | 133 | | | GR3 |
| Tile^ | 2 | 78 | | | 15 | | | 804 | | | GR3 |
| Tile^ | 1 | 26 | | | 52 | | | 130 | | | GR3 |
| Ceramic tile | 8 | 63 | 174 | 25 | 37 | 47 | 29 | 506 | 786 | 411 | EU1 |
| Mosaic | 7 | <u>3</u> | 4 | 1 | <u>2</u> | 3 | 1 | 23 | | | GR1 |
| Granite tile^ | 26 | 67 | 195 | 2 | 95 | 450 | 1 | 1200 | 3800 | 50 | GR4 |
| Natural raw materials | | | | | | | | | | | |
| Sandstone | 1 | 21 | | | 28 | | | 250 | | | GR10 |
| Limestone | 20 | 14 | 21 | 2 | 2 | 2 | | | 25 | | GR5 |
| Limestone | 2 | 10 | 14 | 6 | 4 | 7 | 0 | 65 | 110 | 20 | GR10 |
| Gypsum | 6 | <u>6</u> | 17 | 6 | 10 | | | <u>23</u> | 40 | 5 | GR1, GR9 |
| Gypsum | 2 | 19 | 27 | 11 | 5 | 6 | 3 | 70 | 80 | 60 | GR10 |
| Gypsum | 1 | 109 | | | 11 | | | 24 | | | GR2 |
| Lime (quicklime) | 2 | <u>21</u> | 32 | 9 | 1 | | | | | | GR2 |
| Pumice stone | 5 | <u>462</u> | 874 | 50 | <u>57</u> | 60 | 54 | <u>1103</u> | 1158 | 1048 | GR1 |
| Gypsum | 1 | 7 | | | | | | | | | GR5 |
| Natural covering stones | | | | | | | | | | | |
| Granite | 13 | 42 | 91 | 4 | 42 | 70 | 15 | 630 | 1302 | 24 | EU1 |
| Granite | 16 | 68 | 170 | 2 | 86 | 354 | 30 | 1175 | 1592 | 49 | GR7 |
| PZL | 2 | 87 | 135 | 39 | 107 | 180 | 33 | 510 | 710 | 310 | GR10 |
| Marble Powder | 20 | 1.8 | 3 | | 2 | 3 | 1 | | 25 | | GR1,GR5, GR9 |
| Marble | 18 | 16 | 108 | 1 | 13 | 142 | 0.4 | 171 | 986 | 9 | EU1 |
| Schist | 1 | 36 | | | 31 | | | 490 | | | GR10 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| FA (Thessaloniki) | 4 | 330 | | | 53 | | | 190 | | | GR10 |
| FA (Kamari) | 4 | 800 | | | 53 | | | 290 | | | GR10 |
| FA | 7 | 747 | 850 | 590 | 67 | 73 | 58 | | | | GR12 |
| FA | 1 | 1041 | | | 55 | | | 462 | | | GR5 |
| FA (Megalopolis Unit I) | 35 | 807 | | | 55 | | | 449 | | | GR19 |
| FA (Megalopol. Unit III) | 35 | 845 | | | 56 | | | 502 | | | GR19 |
| FA | 42 | 904 | | | 53 | | | 454 | | | GR8 |
| FA^ | 12 | 929 | 1176 | 663 | | | | | | | GR8 |
| FA | 156 | 912 | | | 54 | | | 460 | | | GR8 |
| FA | 350 | <u>825</u> | 1377 | 273 | <u>53</u> | 65 | 41 | <u>402</u> | 661 | 143 | GR1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---------------------------------|----|-------------------------------|------|------|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| FA | 36 | 366 | 605 | 142 | 50 | 68 | 27 | 297 | 382 | 204 | GR14 |
| FA (Megalopolis Unit I) | 2 | 1038 | 1056 | 1020 | 58 | 59 | 57 | 450 | 453 | 447 | GR15 |
| FA (Megalop. Unit III) | 2 | 1046 | 1063 | 1028 | 59 | 60 | 58 | 442 | 445 | 438 | GR15 |
| BA (Megalopolis Unit I) | 1 | 767 | | | 51 | | | 412 | | | GR15 |
| BA (Megalopolis Unit III) | 1 | 831 | | | 50 | | | 451 | | | GR15 |
| BA (Megalopolis Unit I) | 35 | 546 | | | 44 | | | 406 | | | GR19 |
| BA (Megalopolis Unit III) | 35 | 587 | | | 44 | | | 423 | | | GR19 |
| BA | 42 | 662 | | | 44 | | | 405 | | | GR8 |
| BA [^] | 2 | 617 | 654 | 580 | | | | | | | GR8 |
| BA | 60 | 423 | 743 | 102 | 35 | 49 | 20 | 296 | 480 | 111 | GR1 |
| Bauxite residues/red mud | | | | | | | | | | | |
| RM | 1 | 379 | | | 472 | | | 21 | | | GR16 |
| RM | 1 | 232 | | | 344 | | | 45 | | | GR17 |
| RM | 3 | 122 | 185 | 13 | 276 | 412 | 15 | 105 | 160 | 72 | GR18 |
| Byproduct Gypsum | | | | | | | | | | | |
| PHG | 1 | 642 | | | 8 | | | 26 | | | GR2 |
| PHG | 2 | 547 | 570 | 524 | 2 | 4 | | | | | GR10 |
| Metallurgical slag | | | | | | | | | | | |
| Pyrite slag | 1 | 15 | | | 1 | | | 20 | | | GR10 |

Numbers in **Bold Italic**= MDA (minimum detection level)

Numbers in **Bold underline**= average from minimum and maximum

[^] Data on emanation and/or exhalation are reported in Table 31

Table 12 Hungary
1511 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|----------------------------|-----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks | 176 | 57 | 200 | 30 | 48 | 67 | 33 | 666 | 925 | 444 | H3 |
| Concrete | | | | | | | | | | | |
| Concrete | 95 | 15 | 22 | 7 | 13 | 24 | 7 | 234 | 407 | 148 | H3 |
| Cement | | | | | | | | | | | |
| PTL I | 25 | 27 | | | 23 | | | 172 | | | H2 |
| PTL II | 25 | 8 | | | 15 | | | 213 | | | H2 |
| PTL III | 25 | 11 | | | 13 | | | 133 | | | H2 |
| PTL III S-54 | 25 | 8 | | | 16 | | | 248 | | | H2 |
| PTL IV | 25 | 38 | | | 16 | | | 167 | | | H2 |
| PTL IV S-54 | 25 | 28 | | | 13 | | | 131 | | | H2 |
| PTL V | 25 | 17 | | | 16 | | | 192 | | | H2 |
| PTL cement-FA I 350/10 | 25 | 55 | | | 49 | | | 383 | | | H2 |
| PTL cement-FA I 350/20 | 25 | 55 | | | 53 | | | 402 | | | H2 |
| PTL cement-FA II 350/10 | 25 | 14 | | | 19 | | | 261 | | | H2 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|-----|-------------------------------|------|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| PTL cement-FA IV 350/10 | 25 | 34 | | | 14 | | | 95 | | | H2 |
| PTL BFS cement III 350/20 | 25 | 22 | | | 18 | | | 228 | | | H2 |
| PTL BFS cement III 350/40 | 25 | 40 | | | 19 | | | 229 | | | H2 |
| PTL BFS cement V 450 | 25 | 16 | | | 19 | | | 211 | | | H2 |
| PTL BFS cement V 350/20 | 25 | 23 | | | 53 | | | 201 | | | H2 |
| PTL BFS cement V 350/40 | 25 | 61 | | | 23 | | | 226 | | | H2 |
| Clinker I | 25 | 22 | | | 21 | | | 143 | | | H2 |
| Clinker II | 25 | 10 | | | 14 | | | 285 | | | H2 |
| Clinker III | 25 | 14 | | | 15 | | | 105 | | | H2 |
| Clinker IV | 25 | 21 | | | 11 | | | 132 | | | H2 |
| Clinker V | 25 | 11 | | | 15 | | | 181 | | | H2 |
| Aggregates | | | | | | | | | | | |
| Sand | 50 | 17 | 25 | 9 | 37 | 49 | 25 | 509 | 686 | 331 | H2 |
| Natural raw materials | | | | | | | | | | | |
| Clay | 125 | 18 | 26 | 4 | 36 | 53 | 10 | 497 | 709 | 186 | H2 |
| Limestone I | 25 | 9 | | | 3 | | | 10 | | | H2 |
| Limestone II | 25 | 0.6 | | | | | | | | | H2 |
| Limestone III | 25 | 6 | | | 3 | | | 12 | | | H2 |
| Limestone IV | 25 | 9 | | | 7 | | | 20 | | | H2 |
| Limestone V | 25 | 2 | | | 0.6 | | | | | | H2 |
| Gypsum | 125 | 6 | 16 | 1 | 4 | 15 | 1 | 56 | 187 | | H2 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| Coal slag (Ajka) | 35 | 1962 | 2893 | 578 | 42 | 81 | 16 | 198 | 386 | 45 | H1 |
| Coal slag (Tatabanya) | 35 | 1912 | 2407 | 843 | 83 | 119 | 50 | 352 | 468 | 257 | H1 |
| Coal slag (Tatabanya) | 35 | 298 | 523 | 160 | 40 | 37 | 48 | 273 | 333 | 227 | H1 |
| FA I | 25 | 9 | | | 199 | | | 273 | | | H2 |
| FA II | 25 | 92 | | | 70 | | | 423 | | | H2 |
| FA IV | 25 | 228 | | | 75 | | | 610 | | | H2 |
| Bauxite residues/red mud | | | | | | | | | | | |
| RM Neszmely tailings pond A | 1 | 300 | | | 260 | | | | | | H4 |
| RM Neszmely tailings pond B | 1 | 250 | | | 400 | | | | | | H4 |
| RM Ajka | 47 | 360 | 700 | 150 | 292 | 380 | 285 | 48 | 101 | 5 | H5 |
| RM Almásfüzitő | 11 | 294 | 506 | 102 | 229 | 545 | 87 | 103 | 212 | 47 | H5 |
| Metallurgical slag | | | | | | | | | | | |
| BFS III | 25 | 88 | | | 27 | | | 188 | | | H2 |
| BFS V | 25 | 142 | | | 46 | | | 269 | | | H2 |

Table 13 Ireland
57 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks | 14 | 42 | 139 | 7 | 31 | 50 | 8 | 482 | 1064 | 255 | IRL1 |
| Concrete | | | | | | | | | | | |
| Concrete | 8 | 29 | 68 | 18 | 12 | 43 | 3 | 217 | 1100 | 16 | IRL1 |
| Cement | | | | | | | | | | | |
| Cement | 3 | 60 | 107 | 27 | 11 | 15 | 3 | 131 | 252 | 66 | IRL1 |
| Aggregates | | | | | | | | | | | |
| Aggregate | 9 | 24 | 75 | 10 | 16 | 54 | 1 | 482 | 1977 | 10 | IRL1 |
| Sand | 1 | 8 | | | 10 | | | 443 | | | IRL1 |
| Sand | 1 | 20 | | | 24 | | | 550 | | | IRL1 |
| Sand | 1 | 9 | | | 1 | | | 12 | | | IRL1 |
| Tiles | | | | | | | | | | | |
| Tiles | 9 | 76 | 124 | 44 | 26 | 36 | 20 | 671 | 1282 | 222 | IRL1 |
| Natural raw materials | | | | | | | | | | | |
| Gypsum | 10 | 20 | 29 | 2 | 6 | 11 | 1 | 145 | 259 | 15 | IRL1 |
| Bauxite residues/red mud | | | | | | | | | | | |
| RM | 1 | | 240 | | | 460 | | | | | IRL2 |

Table 14 Italy
1095 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|------------------------|-----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Brick | 10 | 47 | | | 51 | | | 729 | | | IT4 |
| Brick (sandstone) | 2 | 6 | 8 | 3 | 9 | 12 | 5 | 277 | 328 | 225 | IT12 |
| Brick | 5 | 36 | 44 | 20 | 31 | 42 | 20 | 711 | 865 | 509 | IT12 |
| Brick | 2 | 55 | 81 | 29 | 99 | 148 | 49 | 717 | 883 | 550 | IT11 |
| Brick | 1 | 14 | | | 20 | | | 282 | | | IT17 |
| Brick duplex | 4 | 32 | 63 | 8 | 21 | 34 | 3 | 750 | 892 | 577 | IT12 |
| Bricks^ | 124 | 40 | | | 40 | | | 710 | | | IT2 |
| Bricks | 12 | 39 | | | 45 | | | 696 | | | IT6 |
| Bricks^ | 1 | 110 | | | 97 | | | 380 | | | IT13 |
| Bricks^ | 1 | 96 | | | 90 | | | 160 | | | IT13 |
| Bricks^ | 1 | 20 | | | 25 | | | 410 | | | IT13 |
| Bricks^ | 1 | 35 | | | 36 | | | 560 | | | IT13 |
| Bricks^ | 1 | 34 | | | 40 | | | 680 | | | IT13 |
| Bricks^ | 1 | 76 | | | 33 | | | 590 | | | IT13 |
| Bricks^ | 1 | 32 | | | 39 | | | 530 | | | IT13 |
| Clay brick | 8 | 47 | 56 | 32 | 50 | 65 | 40 | 694 | 959 | 365 | IT8 |
| Hollow brick | 10 | 39 | 67 | 10 | 28 | 45 | 9 | 879 | 1169 | 638 | IT12 |
| Hollow brick (poroton) | 6 | 27 | 56 | 3 | 22 | 44 | 12 | 844 | 1117 | 637 | IT12 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Lekablock | 4 | 22 | 28 | 15 | 16 | 26 | 9 | 524 | 869 | 253 | IT12 |
| Ytong | 1 | 4 | | | 5 | | | 198 | | | IT12 |
| Concrete | | | | | | | | | | | |
| Concrete | 7 | 19 | | | 24 | | | 457 | | | IT6 |
| Concrete (brick) | 1 | 17 | | | 3 | | | 58 | | | IT17 |
| Concrete (cement +FA) | 1 | 23 | | | 16 | | | 277 | | | IT4 |
| Concrete (PTL cement) | 10 | 23 | | | 16 | | | 290 | | | IT4 |
| Concrete B** (cement+15% FA South Africa)^ | 1 | 18 | | | | | | | | | IT2, IT2.A |
| Concrete B** (cement +15% FA US)^ | 1 | 13 | | | | | | | | | IT2, IT2.A |
| Concrete B** (cement +26% FA South Africa)^ | 1 | 19 | | | | | | | | | IT2, IT2.A |
| Concrete B** (cement +26% FA US)^ | 1 | 13 | | | | | | | | | IT2, IT2.A |
| Concrete B** (cement +40% FA South Africa)^ | 1 | 19 | | | | | | | | | IT2, IT2.A |
| Concrete B** (cement +40% FA US)^ | 1 | 15 | | | | | | | | | IT2, IT2.A |
| Concrete B** (cement +5% FA South Africa)^ | 1 | 17 | | | | | | | | | IT2, IT2.A |
| Concrete B** (cement +5% FA US)^ | 1 | 13 | | | | | | | | | IT2, IT2.A |
| Concrete B**^ | 1 | 16 | | | | | | | | | IT2, IT2.A |
| Concrete brick | 1 | 15 | | | 17 | | | 474 | | | IT12 |
| Concrete-cement PZL325 | 1 | 21 | | | 38 | | | 200 | | | IT10.A |
| Concrete^ | 1 | 18 | | | 12 | | | 230 | | | IT13 |
| Concrete^ | 1 | 13 | | | 20 | | | 390 | | | IT13 |
| Siporex | 1 | 7 | | | 10 | | | 192 | | | IT17 |
| Cement | | | | | | | | | | | |
| Cement | 1 | 24 | | | 28 | | | 445 | | | IT17 |
| Cement | 4 | 21 | 25 | 10 | 18 | 27 | 9 | 243 | 266 | 208 | IT12 |
| Cement | 1 | 78 | | | 167 | | | 707 | | | IT18 |
| Cement | 1 | 73 | | | 156 | | | 747 | | | IT18 |
| Cement | 1 | 33 | | | 46 | | | 318 | | | IT18 |
| Cement | 1 | 63 | | | 123 | | | 846 | | | IT18 |
| Cement (special use) | 2 | 44 | | | 11 | | | 183 | | | IT4 |
| Cement (with FA) | 1 | 51 | | | 53 | | | 255 | | | IT4 |
| Cement 245 | 1 | 43 | | | 39 | | | 228 | | | IT10.A |
| Cement 325 | 1 | 77 | | | 61 | | | 211 | | | IT10.A |
| Cement powder | 12 | 21 | | | 16 | | | 253 | | | IT6 |
| Cement PTL | 9 | 16 | | | 14 | | | 205 | | | IT4 |
| Cement PTL | 1 | 30 | 40 | 20 | 50 | 80 | 20 | 125 | 150 | 100 | IT3 |
| Cement PTL 325 | 1 | 16 | | | 11 | | | 213 | | | IT4 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|----------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|--------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Cement PTL 425 | 1 | 51 | | | 51 | | | 279 | | | IT10.A |
| Cement PTL 425 | 1 | 16 | | | 27 | | | 270 | | | IT18 |
| Cement PTL 425 | 1 | 13 | | | 10 | | | 199 | | | IT4 |
| Cement PTL 425 | 1 | 48 | | | 31 | | | 247 | | | IT10.A |
| Cement PTL 425 | 1 | 53 | | | 108 | | | 314 | | | IT10.A |
| Cement PTL 425 ARF | 1 | 11 | | | 10 | | | 206 | | | IT4 |
| Cement PTL 525 | 1 | <u>17</u> | 17 | 17 | <u>28</u> | 29 | 27 | <u>262</u> | 270 | 253 | IT11 |
| Cement PTL 525 | 1 | 10 | | | 10 | | | 193 | | | IT4 |
| Cement PTL [^] | 31 | 26 | | | 18 | | | 210 | | | IT2 |
| Cement PZL | 1 | <u>77</u> | 81 | 72 | <u>168</u> | 172 | 164 | <u>637</u> | 667 | 607 | IT11 |
| Cement PZL | 1 | <u>75</u> | 100 | 50 | <u>85</u> | 150 | 20 | <u>425</u> | 700 | 150 | IT3 |
| Cement PZL | 1 | 83 | | | 137 | | | 662 | | | IT4 |
| Cement PZL | 1 | 72 | | | 164 | | | 667 | | | IT18 |
| Cement PZL 325 | 1 | 61 | | | 126 | | | 480 | | | IT10.A |
| Cement PZL 325 | 1 | 69 | | | 136 | | | 551 | | | IT10.A |
| Cement PZL 325 | 1 | 78 | | | 149 | | | 735 | | | IT10.A |
| Cement PZL 325 | 1 | 75 | | | 137 | | | 753 | | | IT10.A |
| Cement PZL 325 | 1 | 98 | | | 240 | | | 788 | | | IT10.A |
| Cement PZL 425 | 1 | 26 | | | 43 | | | 267 | | | IT10.A |
| Cement PZL [^] | 21 | 49 | | | 45 | | | 390 | | | IT2 |
| Cement [^] | 7 | 38 | 40 | 12 | 22 | | | 218 | | | IT15 |
| Cement [^] | 78 | 33 | | | 26 | | | 270 | | | IT2.A |
| Aggregates | | | | | | | | | | | |
| Gravel | 8 | 21 | | | 13 | | | 248 | | | IT4 |
| River gravel | 1 | 13 | | | 15 | | | 145 | | | IT18 |
| River gravel | 1 | 11 | | | 16 | | | 100 | | | IT11 |
| River gravel | 1 | 14 | | | 14 | | | 134 | | | IT11 |
| Sand | 1 | 16 | | | 4 | | | 34 | | | IT17 |
| Sand | 1 | 15 | | | 10 | | | 334 | | | IT17 |
| Sand | 4 | 21 | | | 24 | | | 477 | | | IT4 |
| Sand | 14 | 24 | 113 | 1 | 27 | 88 | 1 | 528 | 1362 | 30 | IT8 |
| Sand | 2 | <u>10</u> | 11 | 8 | <u>17</u> | 20 | 13 | <u>442</u> | 491 | 393 | IT11 |
| Sand | 23 | 18 | | | 24 | | | 539 | | | IT6 |
| Sand | 2 | 23 | | | <u>17</u> | 27 | 6 | <u>611</u> | 750 | 472 | IT12 |
| Sand & gravel [^] | 61 | 15 | | | 17 | | | 390 | | | IT2 |
| Sand and gravel | 1 | 20 | 27 | 13 | 18 | 26 | 9 | 403 | 638 | 168 | IT3 |
| Silicic sand | 6 | 9 | | | 9 | | | 156 | | | IT15 |
| Tiles | | | | | | | | | | | |
| Facing tile | 15 | 55 | | | 18 | | | 783 | | | IT6 |
| Paving tile | 8 | 54 | | | 56 | | | 1026 | | | IT6 |
| Paving tile | 5 | 64 | | | 68 | | | 680 | | | IT4 |
| Roofing tile (red clay) | 1 | 23 | | | 30 | | | 540 | | | IT13 |
| Roofing tile (red clay) | 1 | 24 | | | 36 | | | 590 | | | IT13 |
| Tile (ceramic glazed) | 1 | 48 | | | 42 | | | 460 | | | IT13 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|------|---------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Tile (ceramic glazed) | 1 | 56 | | | 43 | | | 440 | | | IT13 |
| Tile (glazed-double fired) | 1 | 79 | | | 66 | | | 890 | | | IT14 |
| Tile (glazed-single fired) | 1 | 58 | | | 52 | | | 830 | | | IT14 |
| Tile (gres) | 16 | 31 | | | 35 | | | 474 | | | IT12 |
| Tile (gres) | 1 | 230 | | | 76 | | | 650 | | | It13 |
| Tile (gres) | 1 | 50 | | | 59 | | | 520 | | | IT14 |
| Tile (gres)^ | 1 | 150 | | | 56 | | | 410 | | | IT13 |
| Tile (terracotta) | 1 | 12 | | | 9 | | | 150 | | | IT13 |
| Natural raw materials | | | | | | | | | | | |
| Clay | 2 | 46 | 55 | 38 | 30 | 33 | 28 | 1077 | 1158 | 995 | IT12 |
| Clay | 3 | 29 | | | 31 | | | 412 | | | IT4 |
| Clay | 5 | 45 | 52 | 38 | 49 | 54 | 46 | 687 | 767 | 600 | IT8 |
| Clay (caolin) | 1 | 316 | | | 537 | | | 2521 | | | IT5 |
| Clay^ | 7 | 34 | 42 | 21 | 38 | | | 513 | | | IT15 |
| Gypsum | 1 | 16 | | | 3 | | | 104 | | | IT9 |
| Gypsum | 2 | 10 | 16 | 4 | 2 | 3 | 1 | 59 | 104 | 15 | IT8 |
| Gypsum | 1 | 9 | | | 1 | | | 118 | | | IT12 |
| Gypsum (brick) | 1 | 7 | | | 5 | | | 56 | | | IT17 |
| Gypsum - gypsum compound | 3 | 8 | | | 2 | | | 62 | | | IT4 |
| Gypsum board | 8 | 10 | 16 | 3 | 4 | 8 | 2 | 197 | 277 | 128 | IT12 |
| Gypsum^ | 5 | 6 | 13 | 0.6 | 2 | | | 32 | | | IT15 |
| Lime | 1 | 7 | | | 8 | | | 300 | | | IT4 |
| Lime | 1 | 17 | | | 12 | | | 84 | | | IT17 |
| Lime, hydrated lime | 3 | 10 | 15 | 7 | 7 | 8 | 6 | 305 | 312 | 301 | IT12 |
| Lime, hydrated lime^ | 13 | 10 | | | 2 | | | 77 | | | IT2 |
| Limestone^ | 27 | 11 | 30 | 0.4 | 2 | | | 22 | | | IT15 |
| Limestone^ | 1 | 65 | | | 6 | | | 46 | | | IT13 |
| Limestone^ | 1 | 76 | | | 8 | | | 47 | | | IT13 |
| Limestones^ | 4 | 9 | 29 | 1 | 3.0 | | | 45 | | | IT15 |
| Limestone golden-yellow | 1 | 12 | | | 0.7 | | | 5 | | | IT1,IT7 |
| Limestone-Vicenza stone | 1 | 12 | | | 0.8 | | | 5 | | | IT1,IT7 |
| PZL | 1 | 33 | | | 53 | | | 374 | | | IT5 |
| PZL | 1 | 123 | | | 184 | | | 1113 | | | IT5 |
| PZL | 1 | 191 | | | 309 | | | 1170 | | | IT5 |
| PZL | 1 | 168 | | | 305 | | | 1490 | | | IT5 |
| PZL | 15 | 210 | | | 250 | | | 1660 | | | IT2 |
| PZL | 1 | 238 | | | 481 | | | 1888 | | | IT11 |
| PZL (Campania) | 3 | 184 | 230 | 106 | 121 | 135 | 108 | 1840 | 2310 | 1330 | IT8 |
| PZL (Latium) | 6 | 352 | 510 | 176 | 324 | 481 | 170 | 1641 | 1980 | 878 | IT8 |
| Sandstone^ | 1 | 33 | | | 32 | | | 530 | | | IT13 |
| Sandstone^ | 1 | 14 | | | 13 | | | 230 | | | IT13 |
| Stone | 5 | 25 | 38 | 5 | 2 | 4 | 1 | 11 | 29 | 4 | IT8 |
| Tuff | 1 | 273 | | | 241 | | | 1259 | | | IT16 |
| Tuff | 26 | 160 | | | 200 | | | 1640 | | | IT2 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|------|-----------------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Tuff | 8 | 296 | 550 | 160 | 309 | 404 | 163 | 1659 | 2370 | 937 | IT8 |
| Tuff | 3 | 150 | 220 | 101 | 99 | 120 | 85 | 2033 | 2250 | 1900 | IT8 |
| Tuff | 1 | 236 | | | 326 | | | 2229 | | | IT4 |
| Tuff (Avellino) | 1 | 79 | | | 106 | | | 1387 | | | IT17 |
| Tuff (black) | 1 | 316 | | | 387 | | | 2161 | | | IT5 |
| Tuff (black) | 1 | 210 | | | 341 | | | 2180 | | | IT5 |
| Tuff (brick) | 1 | 26 | | | 4 | | | 55 | | | IT17 |
| Tuff (compact yellow) | 1 | 12 | | | 17 | | | 453 | | | IT17 |
| Tuff (friable yellow) | 1 | 67 | | | 80 | | | 1414 | | | IT17 |
| Tuff (green) | 1 | 61 | | | 93 | | | 1625 | | | IT17 |
| Tuff (grey) | 1 | 90 | | | 102 | | | 1945 | | | IT17 |
| Tuff (grey) | 1 | 107 | | | 121 | | | 1740 | | | IT17 |
| Tuff (grey) | 1 | 243 | | | 542 | | | 1925 | | | IT11 |
| Tuff (lithoid red) | 1 | 277 | | | 344 | | | 1822 | | | IT5 |
| Tuff (Neaples yellow) | 1 | 73 | | | 86 | | | 2031 | | | IT17 |
| Tuff (red+black scales) | 1 | 138 | | | 468 | | | 1641 | | | IT18 |
| Tuff (red) | 1 | 185 | | | 302 | | | 1245 | | | IT5 |
| Tuff (red) | 1 | 136 | | | 505 | | | 1468 | | | IT11 |
| Tuff (volcanic)^ | 1 | 92 | | | 138 | | | 1200 | | | IT13 |
| Tuff (volcanic)^ | 1 | 190 | | | 210 | | | 1900 | | | IT13 |
| Tuff (volcanic)^ | 1 | 280 | | | 270 | | | 1900 | | | IT13 |
| Tuff (yellow) | 1 | 68 | | | 99 | | | 1589 | | | IT17 |
| Tuff (yellow) | 1 | 164 | | | 363 | | | 2335 | | | IT5 |
| Natural covering stones | | | | | | | | | | | |
| Antigorio (serizzo) | 2 | 27 | | | 41 | | | 775 | | | IT3 |
| Basalt | 1 | 126 | | | 242 | | | 1973 | | | IT5 |
| Basalt | 1 | 113 | | | 175 | | | 2030 | | | IT5 |
| Basalt | 1 | 494 | | | 733 | | | 2354 | | | IT1,IT7 |
| Basalt | 1 | 41 | | | 26 | | | 340 | | | IT13 |
| Basalt | 1 | 131 | | | 261 | | | 1749 | | | IT16 |
| Beola ghiadonata | 1 | 68 | | | 66 | | | 1208 | | | IT1,IT3, IT7 |
| Beole green | 1 | 34 | | | 82 | | | 1891 | | | IT1,IT3, IT9 |
| Beole grey | 1 | 101 | | | 28 | | | 1431 | | | IT1,IT3, IT7 |
| Beole white | 1 | 49 | | | 14 | | | 1199 | | | IT1,IT3, IT7 |
| Bianco sardo | 1 | 47 | | | 90 | | | 1173 | | | IT7 |
| Black gabbro^ | 1 | 11.7 | | | 19 | | | 240 | | | IT13 |
| Ceppo | 1 | 64 | | | 1 | | | 3 | | | IT1,IT3, IT7 |
| Gneiss (S.Vigilio) | 1 | 80 | | | 12 | | | 1480 | | | IT12 |
| Gneiss | 1 | 126 | | | 112 | | | 1276 | | | IT1 |
| Gneiss granodiorite | 1 | 30 | | | 86 | | | 1285 | | | IT1,IT3, IT7 |
| Gneiss luserna stone | 1 | 125 | | | 114 | | | 1276 | | | IT1,IT7 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|------|-------------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Gneiss tonalite | 1 | 29 | | | 25 | | | 498 | | | IT1,IT3,IT7 |
| Gneiss (Monte Bianco) | 1 | 166 | | | 87 | | | 832 | | | IT1,IT7 |
| Granite | 1 | 27 | | | 41 | | | 927 | | | IT1 |
| Granite | 1 | 40 | | | 61 | | | 942 | | | IT1 |
| Granite | 1 | 38 | | | 58 | | | 974 | | | IT1 |
| Granite | 1 | 44 | | | 60 | | | 974 | | | IT1 |
| Granite | 1 | 38 | | | 62 | | | 1029 | | | IT1 |
| Granite | 1 | 37 | | | 58 | | | 1039 | | | IT1 |
| Granite | 1 | 48 | | | 95 | | | 1137 | | | IT1 |
| Granite | 1 | 29 | | | 87 | | | 1170 | | | IT1 |
| Granite | 1 | 24 | | | 44 | | | 1181 | | | IT1 |
| Granite | 1 | 72 | | | 72 | | | 1258 | | | IT1 |
| Granite | 1 | 28 | | | 36 | | | 1258 | | | IT1 |
| Granite | 1 | 85 | | | 77 | | | 1281 | | | IT1 |
| Granite | 8 | 145 | | | 159 | | | 1560 | | | IT4 |
| Granite (green)^ | 1 | 57 | | | 49 | | | 260 | | | IT13 |
| Granite (pink)^ | 1 | 147 | | | 200 | | | 1200 | | | IT13 |
| Granite (pink)^ | 1 | 33 | | | 44 | | | 1000 | | | IT13 |
| Granite (pink)^ | 1 | 61 | | | 79 | | | 1200 | | | IT13 |
| Granite (red)^ | 1 | 153 | | | 360 | | | 1600 | | | IT13 |
| Granite (serizzo) | 1 | 29 | | | 37 | | | 652 | | | IT3 |
| Granite (serizzo) | 1 | 29 | | | 40 | | | 763 | | | IT1 |
| Granite (serizzo) | 1 | 35 | | | 33 | | | 912 | | | IT1 |
| Granite (serizzo) | 1 | 32 | | | 53 | | | 1014 | | | IT1 |
| Granite (syenite Balma) | 4 | 360 | 384 | 324 | 330 | 358 | 305 | 1255 | 1390 | 1191 | IT3 |
| Granite (white)^ | 1 | 37 | | | 42 | | | 830 | | | IT13 |
| Granite pink (Limbara)^ | 1 | 42 | | | | | | | | | IT1 |
| Granite multicolor | 1 | 29 | | | 89 | | | 1170 | | | IT1,IT3,IT7 |
| Granite pink-Porrino 0.2 water content^ | 1 | 88 | | | | | | | | | IT1 |
| Granite pink-Porrino 0.3 water content^ | 1 | 88 | | | | | | | | | IT1 |
| Granite pink-Porrino^ | 1 | 88 | | | | | | | | | IT1 |
| Granite (serizzo) | 2 | 27 | 42 | 11 | 33 | 54 | 12 | 513 | 626 | 440 | IT3 |
| Lapillo (PZL) | 1 | 73 | | | 110 | | | 1582 | | | IT5 |
| Lapillo (PZL) | 1 | 64 | | | 152 | | | 653 | | | IT5 |
| Lava | 1 | 400 | | | 750 | | | 2350 | | | IT18 |
| Lava (Etna) | 3 | 79 | 85 | 71 | 36 | 40 | 32 | 426 | 487 | 378 | IT8 |
| Lava (Vesuvio) | 2 | 704 | 709 | 699 | 70 | 77 | 63 | 2169 | 2180 | 2159 | IT8 |
| Lava (Vesuvio) | 1 | 438 | | | 93 | | | 2163 | | | IT17 |
| Marble | 2 | 2 | | | 1 | | | 24 | | | IT4 |
| Marble | 1 | 2 | | | 0.2 | | | 2 | | | IT7 |
| Marble^ | 8 | 4 | 10 | 0.6 | 0.9 | | | 16 | | | IT15 |
| Marble (Botticino) | 1 | 13 | | | 0.2 | | | 2 | | | IT1,IT3,IT7 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|------|-------------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Marble (Carrara white) | 1 | 4 | | | 0.4 | | | 4 | | | IT1,IT7 |
| Marble (Morter) | 1 | 0.7 | | | 0.6 | | | 18 | | | IT12 |
| Marble (Nuvolera) | 1 | 2 | | | 0.3 | | | 3 | | | IT1,IT3,IT7 |
| Marble (Portoro) | 1 | 4 | | | 0.3 | | | 5 | | | IT1,IT3,IT7 |
| Marble (Ratschings) | 1 | 2 | | | | | | 14 | | | IT12 |
| Marble (red) | 1 | 1 | | | 4 | | | 20 | | | IT13 |
| Marble (South Tirol) | 1 | 0.7 | | | 0.7 | | | 0.1 | | | IT12 |
| Marble (sparkling white) | 1 | 4 | | | 0.3 | | | 2 | | | IT1,IT7 |
| Marble (veined white) | 1 | 1 | | | 0.2 | | | 5 | | | IT1,IT7 |
| Marble (Verona red) | 1 | 1 | | | 3 | | | 14 | | | IT1,IT3,IT7 |
| Marble (white, statuary) | 1 | 1 | | | 0.3 | | | 5 | | | IT1,IT7 |
| Peperino | 1 | 109 | | | 166 | | | 1312 | | | IT5 |
| Peperino | 4 | 169 | 233 | 127 | 165 | 176 | 155 | 1329 | 1518 | 1167 | IT8 |
| Peperino | 6 | 160 | | | 190 | | | 1420 | | | IT2 |
| Peperino | 1 | 164 | | | 231 | | | 1790 | | | IT5 |
| Peperino | 1 | 168 | | | 224 | | | 2118 | | | IT16 |
| Peperino (grey) | 1 | 242 | | | 152 | | | 1500 | | | IT9 |
| Peperino (grey) | 1 | 123 | | | 162 | | | 1340 | | | IT1,IT7 |
| Peperino (pink) | 1 | 125 | | | 164 | | | 1351 | | | IT1,IT7 |
| Peperino (pink)^ | 1 | 167 | | | | | | | | | IT1 |
| Peperino (red) | 1 | 256 | | | 158 | | | 1483 | | | IT9 |
| Porfido (grey) | 1 | 25 | | | 45 | | | 1549 | | | IT12 |
| Porphyry (red) | 1 | 28 | | | 47 | | | 1633 | | | IT12 |
| Porphyritic schist | 1 | 389 | 477 | 300 | 47 | 51 | 43 | 858 | 900 | 815 | IT9 |
| Porphyry | 1 | 41 | | | 55 | | | 1164 | | | IT1,IT3,IT7 |
| Porphyry | 1 | 51 | | | 71 | | | 1476 | | | IT1,IT3,IT7 |
| Porphyry^ | 1 | 40 | | | 48 | | | 950 | | | IT13 |
| Porphyry^ | 1 | 41 | | | 57 | | | 1050 | | | IT13 |
| Rosa baveno | 2 | 57 | 62 | 51 | 69 | 75 | 62 | 1168 | 1225 | 1100 | IT3 |
| Schist^ | 3 | 52 | 86 | 19 | 50 | | | 925 | | | IT15 |
| Schist^ | 3 | 39 | 42 | 34 | 54 | | | 766 | | | IT15 |
| Syenite | 1 | 270 | | | 175 | | | 1181 | | | IT1 |
| Syenite | 1 | 241 | | | 187 | | | 1206 | | | IT1 |
| Syenite | 1 | 354 | | | 195 | | | 1210 | | | IT1 |
| Syenite | 1 | 366 | | | 251 | | | 1264 | | | IT1 |
| Syenite (polished)^ | 1 | 334 | | | | | | | | | IT1 |
| Syenite (unpolished)^ | 1 | 334 | | | | | | | | | IT1 |
| Slate | 1 | 46 | | | 47 | | | 942 | | | IT1,IT3,IT7 |
| Trachytes | 1 | 41 | | | 41 | | | 1100 | | | IT13 |
| Trachytes (veined yellow) | 1 | 36 | | | 52 | | | 1154 | | | IT1,IT3,IT7 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|---------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Travertine | 1 | 0.1 | | | <i>0.1</i> | | | <i>1</i> | | | IT4 |
| Travertine | 1 | 0.5 | | | <i>0.2</i> | | | <i>2</i> | | | IT1,IT7 |
| Travertine | 1 | 0.8 | | | 0.3 | | | 5 | | | IT13 |
| Travertine | 1 | 0.6 | | | <i>0.2</i> | | | <i>2</i> | | | IT1,IT7 |
| Travertine | 1 | 0.4 | | | <i>0.2</i> | | | <i>2</i> | | | IT1,IT7 |
| Travertine | 1 | <i>0.2</i> | | | <i>0.2</i> | | | <i>2</i> | | | IT1,IT7 |
| Travertine | 1 | 2 | | | 0.9 | | | 9 | | | IT1,IT7 |
| Travertine | 1 | <i>0.2</i> | | | <i>0.2</i> | | | <i>2</i> | | | IT7 |
| Travertine | 1 | <i>1</i> | | | <i>1</i> | | | 7 | | | IT5 |
| Travertine | 1 | <i>1</i> | | | <i>1</i> | | | 18 | | | IT5 |
| Travertine (veined light) | 1 | 0.5 | | | <i>0.2</i> | | | <i>2</i> | | | IT1,IT7 |
| Volcanic ash | 1 | 108 | | | 67 | | | 2000 | | | IT9 |
| Others | | | | | | | | | | | |
| Plaster | 1 | 7 | | | 11 | | | 155 | | | IT10.A |
| Mortar | 1 | 10 | | | 19 | | | 80 | | | IT10.A |
| Mortar for injection | 1 | 19 | | | 25 | | | 161 | | | IT10.A |
| Mortar^ | 1 | 22 | | | 25 | | | 490 | | | IT13 |
| Mortar^ | 1 | 7 | | | 8 | | | 130 | | | IT13 |
| Mortar^ | 1 | 13 | | | 15 | | | 400 | | | IT13 |
| Lime mortar^ | 1 | 16 | | | 21 | | | 400 | | | IT13 |
| Plaster coat^ | 1 | 22 | | | 23 | | | 470 | | | IT13 |
| Plaster coat^ | 1 | 34 | | | 2 | | | 25 | | | IT13 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| FA (US)^ | 71 | 170 | | | 130 | | | 470 | | | IT2 |
| FA (Sud Africa)^ | 70 | 170 | | | 150 | | | 330 | | | IT2 |
| BA^ | 10 | 130 | | | 100 | | | 470 | | | IT2 |
| Bauxite residues/red mud | | | | | | | | | | | |
| RM | 1 | 97 | | | 118 | | | 15 | | | IT19 |
| Metallurgical slag | | | | | | | | | | | |
| BFS | 1 | 70 | | | 30 | | | 97 | | | IT4 |

Concrete A*: limestone as aggregates

Concrete B**: sand and gravel as aggregates

Numbers in Bold Italic= MDA (minimum detection level)

Numbers in Bold underline= average from minimum and maximum

^ Data on emanation and/or exhalation of a subgroup of samples are reported in Table 31

Table 15 Latvia
3 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Cement | | | | | | | | | | | |
| Cement | 1 | <u>28</u> | 51 | 5 | <u>48</u> | 93 | 3 | <u>175</u> | 320 | 29 | LV1 |
| Aggregates | | | | | | | | | | | |
| Sand, gravel | 1 | <u>15</u> | 19 | 10 | <u>13</u> | 21 | 4 | <u>430</u> | 460 | 400 | LV1 |
| Natural covering stones | | | | | | | | | | | |
| Granite | 1 | <u>78</u> | 150 | 5 | <u>114</u> | 210 | 18 | <u>905</u> | 1290 | 520 | LV1 |

Table 16 Lithuania
9 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks | 1 | 40 | | | 32 | | | 754 | | | LT1 |
| Bricks | 1 | 31 | 84 | 10 | 20 | 60 | 5 | 522 | 1140 | 228 | LT2 |
| Concrete | | | | | | | | | | | |
| Concrete | 1 | 32 | | | 17 | | | 426 | | | LT1 |
| Concrete | 1 | 37 | 142 | 6 | 25 | 110 | 4 | 480 | 1220 | 63 | LT2 |
| Cement | | | | | | | | | | | |
| Cement | 1 | 70 | 465 | 4 | 30 | 211 | 3 | 268 | 1510 | 2 | LT2 |
| Aggregates | | | | | | | | | | | |
| Sand and gravel | 1 | 24 | 67 | 2 | 14 | 64 | 1 | 464 | 926 | 1 | LT2 |
| Natural raw materials | | | | | | | | | | | |
| Clay | 1 | 55 | 114 | 9 | 52 | 191 | 7 | 884 | 1280 | 225 | LT2 |
| Expanded clay | 1 | 85 | 100 | 63 | 62 | 77 | 47 | 1135 | 1310 | 809 | LT2 |
| Natural covering stones | | | | | | | | | | | |
| Granite | 1 | 37 | 292 | 5 | 30 | 141 | 3 | 870 | 1620 | 220 | LT2 |

Table 17 Luxembourg
126 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|-------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks | 2 | 83 | 93 | 72 | 147 | 164 | 129 | 597 | 988 | 206 | L1 |
| Bricks Poroton | 1 | 53 | | | 58 | | | 1013 | | | L1 |
| Concrete | | | | | | | | | | | |
| Concrete | 2 | 93 | 98 | 88 | 92 | 93 | 90 | 110 | 146 | 73 | L1 |
| Cellular concrete | 1 | 4 | | | 6 | | | 153 | | | L1 |
| Light concrete (pumice) | 2 | 163 | 180 | 146 | 99 | 99 | 99 | 707 | 730 | 684 | L1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----------|-------------------------------|-----|-----------|-----------------------------|------|-----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Tiles | | | | | | | | | | | |
| Tile | 12 | 100 | 202 | 31 | 74 | 117 | 45 | 669 | 1058 | 87 | L1 |
| Terre cuite | 1 | 70 | | | 58 | | | 620 | | | L1 |
| Natural raw Materials | | | | | | | | | | | |
| Stone | 1 | 90 | | | 52 | | | 916 | | | L1 |
| Natural covering stones | | | | | | | | | | | |
| Granite | 61 | 58 | 160 | 3 | 76 | 262 | 1 | 1156 | 2040 | 44 | L1 |
| Marble | 2 | 12 | 19 | 4 | 0.5 | 0.5 | 0.4 | | | | L1 |
| Marble | 2 | 22 | 34 | 10 | 29 | 48 | 10 | 115 | 209 | 20 | L1 |
| Marble | 1 | 6 | | | | | | 1 | | | L1 |
| Sandstone | 1 | 31 | | | 37 | | | 560 | | | L1 |
| Stone (pierre de pawn) | 1 | 106 | | | 2 | | | 30 | | | L1 |
| Stone (pierre Rosal) | 1 | 23 | | | 1 | | | 28 | | | L1 |
| Stone (pierre Mirabelle) | 1 | 5 | | | 1 | | | 3 | | | L1 |
| Stone (Pierre bleu) | 1 | 65 | | | 2 | | | 7 | | | L1 |
| Schiste Pitangui | 1 | 1691 | | | 77 | | | 53 | | | L1 |
| Others | | | | | | | | | | | |
| Plaster | 25 | 52 | 310 | 1 | 37 | 240 | 1 | 29 | 65 | 2 | L1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Metallurgical slags | | | | | | | | | | | |
| BFS | 1 | 7 | 128 | 142 | 117 | 152 | 185 | 135 | 190 | 234 | L1 |

Numbers in Bold Italic= MDA (minimum detection level)

Table 18 Macedonia
30 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|------------|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Natural raw Materials | | | | | | | | | | | |
| Gypsum | 22 | 32 | 67 | 5 | 70 | 188 | 0.5 | 144 | 264 | 22 | EU1 |
| Natural covering stones | | | | | | | | | | | |
| Marble | 8 | 12 | 46 | 1 | 6 | 32 | 0.4 | 165 | 945 | 11 | EU1 |

Numbers in Bold Italic= MDA (minimum detection level)

Table 19 Netherlands
269 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|------|-------------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Brick (Fire clay light-weight - Poriso) | 1 | 71 | 72 | 71 | 74 | 74 | 73 | 1020 | 1030 | 1010 | NL2 |
| Bricks (fire clay) | 14 | 39 | 47 | 29 | 41 | 49 | 35 | 560 | 655 | 415 | NL2, NL3 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|-------------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick, 20% FA [^] | 1 | 76 | | | | | | | | | NL3, NL4 |
| Brick Porous 20% FA | 6 | 72 | 80 | 67 | 73 | 76 | 71 | 1030 | | | NL3, NL4 |
| Bricks | 1 | 41 | | | 49 | | | 415 | | | EU2 |
| Bricks (clay) | 1 | 43 | 77 | 35 | 42 | 84 | 34 | 540 | 637 | 393 | EU2 |
| Bricks (sand-lime) | 1 | 8 | 9 | 7 | 8 | 10 | 7 | 280 | 300 | 260 | NL2 |
| Bricks (sand-lime) | 1 | 8 | 18 | 7 | 8 | 14 | 5 | 150 | 211 | 121 | EU2 |
| Bricks [^] | 1 | 39 | | | | | | | | | NL4 |
| Bricks (sand-lime) [^] | 22 | 10 | 17 | 4 | 9 | 13 | 3 | 230 | 360 | 70 | NL1 |
| Bricks (clay) [^] | 16 | 39 | 45 | 27 | 41 | 50 | 36 | 500 | 630 | 300 | NL1 |
| Bricks (clay) [^] | 5 | 74 | 75 | 71 | 82 | 84 | 79 | 720 | 750 | 690 | NL1 |
| Concrete | | | | | | | | | | | |
| Aerated concrete | 1 | 21 | 13 | 9 | 6 | 8 | 7 | 150 | 229 | 111 | EU2 |
| Aerated concrete [^] | 14 | 11 | 16 | 6 | 8 | 12 | 5 | 170 | 210 | 120 | NL1 |
| Aerated concrete block | 4 | 21 | 24 | 18 | 6 | 7 | 6 | 150 | | | NL3 |
| Aerated concrete [^] | 1 | 22 | | | | | | | | | NL4 |
| Aerated concrete [^] | 1 | 18 | | | | | | | | | NL4 |
| Aerated concrete-FA [^] | 1 | 58 | | | 47 | | | 511 | | | EU2, NL4 |
| Concrete | 1 | 22 | 29 | 15 | 22 | 23 | 14 | 150 | 150 | 72 | EU2 |
| Concrete | 3 | 14 | 17 | 11 | 16 | 23 | 10 | 130 | | | NL3 |
| Concrete [^] | 28 | 24 | 36 | 11 | 18 | 31 | 6 | 160 | 230 | 120 | NL1 |
| Concrete (bims-pumice) | 2 | 115 | 123 | 107 | 132 | 133 | 130 | 870 | | | NL3 |
| Concrete (BFS+FA) [^] | 1 | 19 | | | | | | | | | NL4 |
| Concrete (PTL+phopshoslag) [^] | 1 | 710 | | | | | | | | | NL4 |
| Concrete A (PTL) [^] | 1 | 10 | | | 10 | | | 111 | | | NL3, NL4 |
| Concrete B (BFS cement) [^] | 1 | 16 | | | 22 | | | 137 | | | NL3, NL4 |
| Concrete C (FA cement) | 1 | 14 | | | 15 | | | 140 | | | NL3, NL4 |
| Concrete D (sintered FA grains) [^] | 1 | 55 | | | 38 | | | 328 | | | NL3, NL4 |
| Concrete Portland/FA | 1 | 15 | | | 15 | | | 141 | | | EU2 |
| Concrete PTL-Lytag | 1 | 67 | | | 41 | | | 283 | | | EU2 |
| Concrete Slag cement | 1 | 19 | | | 27 | | | 164 | | | EU2 |
| Concrete Slag cement Lytag | 1 | 78 | | | 74 | | | 305 | | | EU2 |
| Cement | | | | | | | | | | | |
| PTL cement | 6 | 27 | 49 | 10 | 19 | 28 | 14 | 230 | | | NL3 |
| BFS cement | 6 | 82 | 116 | 49 | 120 | 223 | 43 | 260 | | | NL3 |
| PTL/FA cement | 4 | 60 | 77 | 41 | 44 | 51 | 36 | 290 | | | NL3 |
| Aggregates | | | | | | | | | | | |
| Coarse aggregate | 1 | 10 | 10 | 10 | 12 | 13 | 11 | 140 | 175 | 100 | NL2 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Sand | 4 | 8 | 8 | 8 | 11 | 12 | 10 | 200 | | | NL3 |
| Gravel | 4 | 10 | 10 | 10 | 13 | 14 | 11 | 140 | | | NL3 |
| Lyttag aggregate (sintered FA grains) | 3 | 121 | 145 | 90 | 77 | 81 | 74 | 460 | | | NL3 |
| Aardelite (artificial gravel, 50-75% FA) | 1 | 90 | | | 81 | | | 274 | | | EU2 |
| Tiles | | | | | | | | | | | |
| Tiles | 8 | 61 | 87 | 36 | 66 | 80 | 51 | 600 | | | NL3 |
| Roof tiles | 1 | 49 | 54 | 43 | 55 | 59 | 52 | 580 | 630 | 530 | NL2 |
| Roof tiles | 6 | 43 | 54 | 30 | 43 | 57 | 20 | 480 | | | NL3 |
| Natural raw materials | | | | | | | | | | | |
| Limestone | 1 | 28 | | | 2 | | | 35 | | | EU2 |
| Sand-lime stone | 10 | 8 | 9 | 7 | 8 | 9 | 7 | 280 | | | NL3 |
| Sandstone | 1 | 30 | | | 41 | | | 1020 | | | EU2 |
| Gypsum panels | 1 | 3 | 3 | 2 | 3 | | | 17 | 20 | 13 | NL2 |
| Gypsum blocks | 1 | 18 | 30 | 5 | 28 | 54 | 1 | 31 | 80 | 11 | NL2 |
| Gypsum board | 5 | 4 | 6 | 2 | 4 | | | 20 | | | NL3 |
| Gypsum blocks | 4 | 7 | 10 | 5 | 6 | | | 28 | | | NL3 |
| Gypsum^ | 1 | 10 | | | | | | | | | NL4 |
| Gypsum^ | 1 | 5 | | | | | | | | | NL4 |
| Gypsum^ | 1 | 2 | | | | | | | | | NL4 |
| Gypsum^ | 1 | 6 | | | | | | | | | NL4 |
| Gypsum^ | 1 | 4 | | | | | | | | | NL4 |
| Gypsum^ | 10 | 8 | 14 | 3 | 2 | 6 | 0.6 | 10 | 17 | 3 | NL1 |
| Natural covering stones | | | | | | | | | | | |
| Granite | 1 | 32 | | | 35 | | | 990 | | | EU2 |
| Basalt | 1 | 19 | | | 29 | | | 350 | | | EU2 |
| Others | | | | | | | | | | | |
| Wood | 2 | 10 | 11 | 9 | 4 | | | 19 | | | NL3 |
| Glass/rock wool | 3 | 34 | 37 | 31 | 78 | 81 | 76 | 130 | | | NL3 |
| Mortar^ | 6 | 12 | 18 | 7 | 9 | 14 | 6 | 150 | 190 | 100 | NL1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| Coal FA | 14 | 181 | 316 | 112 | 150 | 277 | 88 | 730 | | | NL3 |
| Byproduct Gypsum | | | | | | | | | | | |
| By-prod. gypsum (board)^ | 3 | 450 | 700 | 320 | 8.7 | 10 | 5.7 | 120 | | | NL3 |
| Gypsum block (Kolafosf.) | 3 | 28 | 30 | 26 | 48 | 52 | 40 | 16 | | | NL3 |
| PHG (possible)^ | 1 | 26 | | | | | | | | | NL4 |
| Phospogypusm^ | 1 | 103 | | | | | | | | | NL4 |
| Phospogypusm ^ | 1 | 330 | | | | | | | | | NL4 |
| Phospogypusm ^ | 1 | 700 | | | | | | | | | NL4 |
| Gypsum plaster | 13 | 200 | 600 | 4 | 19 | 53 | 0.4 | 25 | | | NL3 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|-----------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Other residues | | | | | | | | | | | |
| Phosphorous slag | 1 | 1200 | | | 60 | | | 100 | | | EU2 |

Numbers in Bold Italic= MDA (minimum detection level)

^ Data on emanation and/or exhalation are reported in Table 31

Table 20 Norway
206 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|-----|-------------------------------|------|-----|-------------------------------|-------|-----|-----------------------------|------|-----|----------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks | 18 | 63 | | | 74 | | | 1136 | | | NW2 |
| Bricks | 1 | 104 | | | 63 | | | 1037 | | | EU2 |
| Concrete | | | | | | | | | | | |
| Concrete | 137 | 28 | 37 | 11 | 36 | 54 | 21 | 650 | 884 | 355 | NW2 |
| Concrete | 1 | 26 | | | 37 | | | 741 | | | EU2 |
| Aerated | 12 | 52 | | | 56 | | | 811 | | | NW2 |
| Light weight | 1 | 46 | | | 47 | | | 638 | | | EU2 |
| Cement | | | | | | | | | | | |
| Cement [^] | 5 | <u>32</u> | 33 | 30 | <u>20</u> | 22 | 18 | <u>269</u> | 278 | 260 | EU2, NW3 |
| Cement | 1 | 30 | | | 19 | | | 259 | | | EU2 |
| FA cement [^] | 1 | 85 | | | 59 | | | 296 | | | EU2, NW3 |
| Clinker | 1 | 96 | | | 59 | | | 815 | | | EU2 |
| Natural raw materials | | | | | | | | | | | |
| Gypsum | 1 | 11 | | | 4 | | | 11 | | | EU2 |
| Natural covering stones | | | | | | | | | | | |
| Red Rock | 12 | 160 | 550 | 44 | 4000 | 12000 | 170 | 150 | 600 | | NW1 |
| Rauhaugite | 4 | 130 | 290 | 20 | 560 | 7000 | 160 | 190 | 430 | 20 | NW1 |
| Sovite | 6 | 310 | 1400 | 10 | 310 | 780 | 10 | 380 | 1600 | 10 | NW1 |
| Fenite | 1 | 7 | | | 185 | | | <u>1</u> | | | NW1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| FA (imported) [^] | 4 | 174 | 222 | 126 | 136 | 215 | 93 | 622 | | | NW3 |

Numbers in Bold Italic= MDA (minimum detection level)

Numbers in Bold underline= average from minimum and maximum

^ Data on emanation and/or exhalation are reported in Table 31

Table 21 Poland
5729 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|------|-------------------------------|-----|----------|-------------------------------|-----|----------|-----------------------------|------|----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Red clay bricks [^] | 3 | 20 | 22 | 19 | 33 | 44 | 22 | 825 | 944 | 707 | PL4 |
| Silicon-sand-lime bricks [^] | 3 | 11 | 15 | 7 | 6 | 7 | 4 | 204 | 278 | 130 | PL4 |
| Concrete | | | | | | | | | | | |
| Concrete light weight cellul. | 640 | 80 | 200 | 22 | 54 | 220 | 1 | 492 | 893 | 183 | PL3 |
| Concrete | 37 | 65 | 171 | 14 | 36 | 65 | 18 | 500 | 974 | 179 | PL3 |
| Concrete | 1 | 200 | | | 127 | | | 1005 | | | PL2 |
| Cement | | | | | | | | | | | |
| Cement | 339 | 48 | 154 | 4 | 20 | 38 | 1 | 204 | 430 | 1 | PL3 |
| Cement [^] | 4 | 19 | 26 | 7 | 39 | 67 | 11 | 246 | 304 | 189 | PL4 |
| Clinker | 85 | 37 | 115 | 13 | 14 | 41 | 2 | 190 | 534 | 7 | PL3 |
| Cement | 1 | 154 | | | 138 | | | 608 | | | PL2 |
| Aggregates | | | | | | | | | | | |
| Sand | 72 | 8 | 17 | 1 | 9 | 76 | 1 | 231 | 446 | 34 | PL3 |
| Tiles | | | | | | | | | | | |
| Ceramics | 1190 | 52 | 190 | 1 | 49 | 120 | 1 | 724 | 1410 | 60 | PL3 |
| Natural raw materials | | | | | | | | | | | |
| Lime | 88 | 24 | 47 | 1 | 3 | 13 | 1 | 46 | 331 | 1 | PL3 |
| Marl | 24 | 21 | 36 | 12 | 14 | 27 | 5 | 257 | 396 | 128 | PL3 |
| Clay | 35 | 48 | 160 | 22 | 49 | 427 | 25 | 624 | 938 | 161 | PL3 |
| Limestone | 97 | 17 | 34 | 1 | 3 | 23 | 1 | 74 | 540 | 1 | PL3 |
| Sand | 17 | 12 | 32 | 3 | 5 | 13 | 1 | 105 | 295 | 24 | PL3 |
| Chalk | 104 | 15 | 54 | 1 | 5 | 30 | 1 | 84 | 279 | 13 | PL3 |
| Gypsum | 1 | 64 | | | 30 | | | 279 | | | PL2 |
| Gypsum | 88 | 24 | 47 | 1 | 3 | 13 | 1 | 46 | 331 | 1 | PL3 |
| Natural covering stones | | | | | | | | | | | |
| Marble | 9 | 4 | 10 | 1 | 2 | 7 | 1 | 30 | 51 | 7 | PL3 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| FA | 1524 | 127 | 329 | 4 | 82 | 181 | 6 | 676 | 1180 | 58 | PL3 |
| FA | 278 | 241 | | | 93 | | | 636 | | | PL1 |
| FA | 106 | 337 | 611 | 63 | 178 | 322 | 33 | 1082 | 1778 | 385 | PL4 |
| FA [^] | 33 | 96 | 144 | 63 | | | | | | | PL4 |
| BA-boiler Slag | 476 | 95 | 275 | 2 | 58 | 121 | 1 | 491 | 1018 | 1 | PL3 |
| Byproduct Gypsum | | | | | | | | | | | |
| PHG | 23 | 358 | 620 | 19 | 15 | 48 | 4 | 109 | 680 | 1 | PL3 |
| PHG | 17 | 61 | | | 7 | | | 41 | | | PL1 |
| Byproduct gypsum [^] | 4 | 512 | 736 | 26 | 28 | 44 | 11 | 65 | 119 | 11 | PL4 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---------------------------|-----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Metallurgical slag | | | | | | | | | | | |
| Metallurgical Slag | 160 | 110 | 351 | 33 | 30 | 102 | 12 | 170 | 825 | 44 | PL3 |
| Copper Slag | 23 | 295 | 336 | 237 | 45 | 76 | 26 | 902 | 1251 | 615 | PL3 |
| Slag | 42 | <u>239</u> | 459 | 19 | <u>307</u> | 592 | 22 | <u>1227</u> | 2227 | 226 | PL4 |
| Slag [^] | 11 | 67 | 144 | 37 | | | | | | | PL4 |
| Slag | 282 | 511 | | | 52 | | | 844 | | | PL1 |

Numbers in ***Bold Italic***= MDA (minimum detection level)

Numbers in **Bold underline**= average from minimum and maximum

[^] Data on emanation and/or exhalation are reported in Table 31

Table 22 Portugal
128 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks [^] | 10 | <u>64</u> | 90 | 37 | <u>52</u> | 72 | 31 | <u>786</u> | 1098 | 473 | POR1 |
| Concrete | | | | | | | | | | | |
| Concrete block [^] | 11 | <u>53</u> | 98 | 8 | <u>47</u> | 86 | 7 | <u>404</u> | 529 | 278 | POR1 |
| Cement | | | | | | | | | | | |
| Cement [^] | 7 | <u>40</u> | 59 | 21 | <u>23</u> | 34 | 11 | <u>235</u> | 250 | 220 | POR1 |
| Cement | 1 | 22 | | | 15 | | | 276 | | | POR2 |
| Aggregates | | | | | | | | | | | |
| Aggregates | 27 | 62 | 167 | 1 | 50 | 152 | 1 | 761 | 1450 | 11 | POR2 |
| Washed sand Company D | 1 | 6 | | | 8 | | | 490 | | | POR2 |
| Washed sand Company E | 1 | 10 | | | 10 | | | 148 | | | POR2 |
| Sand | 1 | 96 | | | 81 | | | 1213 | | | POR2 |
| Sand powder | 1 | 135 | | | 93 | | | 1253 | | | POR2 |
| Sand [^] | 32 | <u>102</u> | 2 | 202 | <u>83</u> | 4 | 161 | <u>1132</u> | 123 | 2140 | POR1 |
| Gravel [^] | 11 | <u>70</u> | 10 | 130 | <u>29</u> | 2 | 56 | <u>380</u> | 190 | 569 | POR1 |
| Natural covering stones | | | | | | | | | | | |
| Granite | 1 | 258 | | | 96 | | | 1342 | | | POR2 |
| Slate (ardesia) | 1 | 33 | | | 36 | | | 817 | | | POR2 |

INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS

Ashes

| | | | | | | | | | | | |
|----|---|----|----|-----|---|-----|-----|---|----|-----|------|
| FA | 1 | 14 | 75 | 171 | 8 | 157 | 169 | 5 | 69 | 338 | POR2 |
|----|---|----|----|-----|---|-----|-----|---|----|-----|------|

Byproduct Gypsum

| | | | | | | | | | | | |
|-------------------|---|-------------------|-----|-----|-----------------|----|-----------------|----|----|-----------------|------|
| PHG [^] | 7 | 166 | 705 | 12 | 6 | 12 | <u>2</u> | 40 | 90 | <u>2</u> | POR1 |
| Artificial gypsum | 2 | <u>489</u> | 568 | 410 | <u>6</u> | 7 | 5 | | | | POR2 |

Numbers in ***Bold Italic***= MDA (minimum detection level)

Numbers in **Bold underline**= average from minimum and maximum

[^] Data on emanation and/or exhalation are reported in Table 31

Table 23 Romania
635 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|----------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Red brick | 5 | 48 | 105 | 22 | 66 | 108 | 40 | 669 | 760 | 588 | RO1 |
| Red Brick | 32 | 36 | 100 | | 32 | 59 | | 493 | 833 | | RO2 |
| ACC brick | 3 | 8 | 12 | 5 | 12 | 14 | 11 | 264 | 279 | 233 | RO1 |
| Brick (clay, red refractory) | 1 | 50 | | | 52 | | | 652 | | | RO3 |
| Brick (slate and burnt) | 1 | 37 | | | 51 | | | 1038 | | | RO4 |
| Coal-cinder bricks | 11 | 139 | | | 57 | | | 196 | | | RO3, RO4 |
| Clinker bricks | 23 | 52 | | | 56 | | | 531 | | | RO3, RO4 |
| Concrete | | | | | | | | | | | |
| Concrete | 16 | 28 | 79 | | 20 | 39 | | 201 | 452 | | RO2 |
| Concrete: ballast, pumice, foamed, aerated and light weight, heavy | 43 | 69 | | | 77 | | | 918 | | | RO3, RO4 |
| Aerated alum schist concrete | 1 | 118 | | | 556 | | | 615 | | | RO3 |
| Blast furnace cinder concrete | 1 | 106 | | | 91 | | | 477 | | | RO4 |
| Autoclaved aerated concrete | 7 | 17 | 32 | | 16 | 37 | | 163 | 277 | | RO2 |
| Autoclaved cellular concrete, white | 32 | 114 | | | 115 | | | 357 | | | RO4 |
| Autoclaved cellular concrete, grey | 35 | 95 | | | 90 | | | 485 | | | RO4 |
| Cement | | | | | | | | | | | |
| Cement dust | 2 | 4 | 4 | 4 | 16 | 16 | 16 | 421 | 633 | 209 | RO1 |
| Alumina cement | 1 | 178 | | | 206 | | | 133 | | | RO3 |
| Asbestos-cement | 3 | 7 | 9 | 4 | 12 | 14 | 11 | 50 | 57 | 47 | RO1 |
| Asbestos-cement | 1 | 44 | | | 14 | | | 79 | | | RO3 |
| Cement | 25 | 34 | 66 | | 18 | 97 | | 152 | 504 | | RO2 |
| Cement [^] | 1 | 27 | | | 22 | | | 228 | | | RO5 |
| Cement with FA 50% [^] | 1 | 154 | | | 76 | | | 315 | | | RO5 |
| Cement with FA 33% [^] | 1 | 107 | | | 52 | | | 298 | | | RO5 |
| Cement with FA 11% [^] | 1 | 58 | | | 39 | | | 295 | | | RO5 |
| Cement PA | 21 | 74 | | | 27 | | | 281 | | | RO3, RO4 |
| Aggregates | | | | | | | | | | | |
| Sand | 5 | 7 | 12 | 2 | 22 | 32 | 14 | 507 | 662 | 370 | RO1 |
| Sand, gravel | 14 | 8 | 30 | | 27 | 92 | | 557 | 870 | | RO2 |
| Tiles | | | | | | | | | | | |
| Tiles | 4 | 46 | 59 | 30 | 58 | 67 | 50 | 792 | 892 | 706 | RO1 |
| Natural raw materials | | | | | | | | | | | |
| Lime | 8 | 13 | 41 | | 8 | 19 | | 68 | 167 | | RO2 |
| Gypsum | 14 | 18 | 43 | | 10 | 27 | | 103 | 277 | | RO2 |
| Gypsum | 1 | 41 | | | 40 | | | 199 | | | RO3 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|-----|-------------------------------|----------|----------|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Natural covering stones | | | | | | | | | | | |
| Tufa (travertino) | 1 | 11 | | | 10 | | | 180 | | | RO1 |
| Others | | | | | | | | | | | |
| Mortar | 4 | 6 | 8 | | 6 | 12 | | 426 | 611 | | RO2 |
| Wood | 3 | 5 | 7 | 3 | 2 | 3 | 2 | 75 | 140 | 41 | RO1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| FA | 18 | 155 | 219 | | 89 | 126 | | 569 | 945 | | RO2 |
| Ash from CFPPs | 1 | 224 | | | 80 | | | 646 | | | RO3 |
| FA | 120 | 276 | 460 | 140 | 244 | 501 | 79 | 547 | 1265 | 170 | RO4 |
| FA | 2 | 118 | 122 | 114 | 87 | 97 | 77 | 673 | 729 | 617 | RO1 |
| FA I Oradea | 4 | 160 | 246 | 72 | 85 | 175 | 38 | 475 | 520 | 384 | RO5 |
| Escaping FA | 34 | 380 | 558 | 149 | 114 | 360 | 41 | 660 | 1390 | 205 | RO4 |
| (Slag) BA | 76 | 94 | 121 | 21 | 49 | 129 | 15 | 514 | 1100 | 280 | RO4 |
| Slag from CFPPs | 1 | 122 | | | 62 | | | 394 | | | RO3 |
| Byproduct Gypsum | | | | | | | | | | | |
| PHG | 54 | 702 | 970 | | 23 | 42 | | 113 | 116 | | RO2 |
| PHG | 1 | 634 | | | 9 | | | 44 | | | RO3 |
| Metallurgical slag | | | | | | | | | | | |
| Blast furnace ash | 1 | 110 | | | 62 | | | 438 | | | RO3 |
| Blast furnace cinders | 1 | 181 | | | 50 | | | 270 | | | RO3 |

Numbers in Bold Italic= MDA (minimum detection level)

^ Data on emanation and/or exhalation are reported in Table 31

Table 24 Slovakia
2148 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|-----------------------|-----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Bricks | 1 | 49 | 64 | 28 | 44 | 70 | 22 | 695 | 820 | 477 | EU2 |
| Bricks | 25 | 71 | 265 | 12 | 80 | 252 | 13 | 590 | 887 | 72 | SK3 |
| Bricks+ slate | 137 | 129 | 247 | 11 | 132 | 252 | 11 | 627 | 1181 | 72 | SK1 |
| Concrete | | | | | | | | | | | |
| Concrete | 1 | 42 | 71 | 8 | 36 | 61 | 6 | 392 | 557 | 171 | EU2 |
| Concrete (B7.5 325R)^ | 3 | 10 | | | 6 | | | 247 | | | SK2 |
| Concrete (B20 325R) | 3 | 10 | | | 6 | | | 238 | | | SK2 |
| Concrete (B35 325R)^ | 3 | 13 | | | 7 | | | 250 | | | SK2 |
| Concrete (B7.5 325HS) | 3 | 10 | | | 7 | | | 266 | | | SK2 |
| Concrete (B20 325HS) | 3 | 10 | | | 7 | | | 240 | | | SK2 |
| Concrete (B35 325HS)^ | 3 | 11 | | | 5 | | | 251 | | | SK2 |
| Concrete (B7.5 250LL) | 3 | 10 | | | 7 | | | 245 | | | SK2 |
| Concrete (B20 250LL) | 3 | 12 | | | 10 | | | 254 | | | SK2 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|-----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Concrete (B35 250LL) | 3 | 15 | | | 11 | | | 270 | | | SK2 |
| Concrete with broken bricks BBC/325HS^ | 2 | 46 | | | 39 | | | 653 | | | SK2 |
| Concrete with broken bricks BBC/325R^ | 2 | 44 | | | 40 | | | 644 | | | SK2 |
| Concrete with broken bricks BBC/325LL | 2 | 45 | | | 41 | | | 664 | | | SK2 |
| Cellular concrete SS^ | 3 | 16 | | | 8 | | | 214 | | | SK2 |
| Cellular concrete SE^ | 3 | 50 | | | 41 | | | 372 | | | SK2 |
| Cellular concrete BA^ | 1 | 69 | | | 38 | | | 347 | | | SK2 |
| Concrete | 29 | 60 | 127 | 10 | 36 | 70 | 5 | 336 | 652 | 96 | SK2 |
| Concrete | 80 | 107 | 207 | 6 | 37 | 74 | 1 | 328 | 651 | 4 | SK1 |
| Concrete | 1 | 42 | 71 | 8 | 36 | 61 | 6 | 392 | 557 | 171 | EU2 |
| Cement | | | | | | | | | | | |
| Cement | 1 | 23 | 36 | 12 | 15 | 20 | 7 | 198 | 295 | 104 | EU2 |
| Cement 250 LL | 3 | 47 | | | 19 | | | 253 | | | SK2 |
| Cement 325 R | 1 | 42 | | | 19 | | | 190 | | | SK2 |
| Cement 325 HS | 1 | 28 | | | 18 | | | 251 | | | SK2 |
| Cement | 288 | 61 | 118 | 4 | 39 | 77 | 1 | 215 | 425 | 5 | SK1 |
| Cement | 88 | 42 | 116 | 16 | 21 | 37 | 12 | 249 | 352 | 161 | SK3 |
| Clinker | 1 | 57 | 91 | 20 | 67 | 113 | 34 | 613 | 819 | 435 | EU2 |
| Aggregates | | | | | | | | | | | |
| Aggregates (fine and coarse) | 348 | | 252 | | | 115 | | 1713 | 3426 | 1 | SK1 |
| Gravel | 1 | 10 | 15 | 4 | 13 | 18 | 3 | 152 | 271 | 152 | EU2 |
| Gravel | 2 | 6 | | | 3 | | | 189 | | | SK2 |
| Sand | 3 | 9 | | | 5 | | | 282 | | | SK2 |
| Sand | 1 | 8 | 15 | 3 | 9 | 15 | 7 | 193 | 328 | 65 | EU2 |
| Sand | 14 | 28 | 258 | 4 | 21 | 142 | 1 | 339 | 912 | 5 | SK3 |
| Sand | 141 | 21 | 41 | 1 | 33 | 67 | 0.3 | 516 | 1030 | 2 | SK1 |
| Tiles | | | | | | | | | | | |
| Ceramics | 1 | 31 | 41 | 20 | 37 | 41 | 19 | 507 | 770 | 271 | EU2 |
| Natural raw materials | | | | | | | | | | | |
| Limestone | 1 | 10 | 14 | 5 | 4 | 8 | 2 | 63 | 137 | 28 | EU2 |
| Azbestos | 1 | 9 | 13 | 5 | 14 | 19 | 7 | 191 | 230 | 118 | EU2 |
| Stone | 96 | 16 | 106 | 1 | 16 | 133 | 1 | 342 | 2441 | 2 | SK3 |
| Stone | 286 | 67 | 132 | 2 | 198 | 395 | 0.3 | 1221 | 2441 | 1 | SK1 |
| Natural covering stones | | | | | | | | | | | |
| Granites | 1 | 58 | 101 | 10 | 59 | 137 | 17 | 680 | 1043 | 383 | EU2 |
| Pearlites | 1 | 53 | 67 | 39 | 76 | 87 | 66 | 1149 | 1172 | 1125 | EU2 |
| Marbles | 1 | 13 | 15 | 11 | 5 | 8 | 3 | 137 | 165 | 103 | EU2 |
| Marble | 7 | 14 | 41 | 1 | 37 | 95 | 0 | 590 | 887 | 72 | SK3 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| FA | 1 | 83 | 129 | 38 | 68 | 109 | 32 | 496 | 832 | 194 | EU2 |
| FA | 92 | 102 | 318 | 34 | 70 | 159 | 21 | 458 | 937 | 33 | SK3 |
| FA | 133 | 185 | 336 | 34 | 90 | 159 | 21 | 1353 | 2685 | 22 | SK1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Metallurgical slag | | | | | | | | | | | |
| Slag | 17 | 86 | 158 | 44 | 64 | 106 | 39 | 287 | 575 | 149 | SK3 |
| Dross | 5 | 163 | 257 | 75 | 37 | 51 | 14 | 295 | 650 | 76 | SK3 |
| Slag+dross | 43 | 233 | 436 | 10 | 33 | 56 | 10 | 363 | 650 | 76 | SK1 |

Numbers in Bold underline= average from minimum and maximum

^ Data on emanation and/or exhalation are reported in Table 31

Table 25 Slovenia
7 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mea | max | min | mea | max | min | mea | max | min | |
| Brick | | | | | | | | | | | |
| Clay red brick | 1 | 69 | | | 72 | | | 454 | | | SLO1 |
| Coal ash brick | 1 | 93 | | | 101 | | | 898 | | | SLO1 |
| Concrete | | | | | | | | | | | |
| Concrete brick | 1 | 20 | | | 11 | | | 105 | | | SLO1 |
| Aerated concrete | 1 | 22 | | | 10 | | | 143 | | | SLO1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| Coal-ashes plaster | 1 | 190 | | | 33 | | | 360 | | | SLO1 |
| Coal ash aggregate | 1 | 309 | | | 40 | | | 406 | | | SLO1 |
| Byproduct Gypsum | | | | | | | | | | | |
| PHG plaster | 1 | 500 | | | 10 | | | 41 | | | SLO1 |

Table 26 Spain
426 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Brick | 1 | 34 | | | 99 | | | 666 | | | SP2 |
| Brick | 3 | 55 | | | 44 | | | 747 | | | SP3 |
| Brick | 8 | 73 | | | 60 | | | 292 | | | SP3 |
| Concrete | | | | | | | | | | | |
| Concrete | 24 | 30 | | | 32 | | | 204 | | | SP3 |
| PC Concrete | 4 | 21 | 29 | 16 | 18 | 22 | 11 | 283 | 363 | 221 | SP4 |
| CAC Concrete | 5 | 38 | 42 | 10 | 23 | 27 | 20 | 246 | 456 | 176 | SP4 |
| Cement | | | | | | | | | | | |
| Cement | 1 | 48 | 135 | 5 | 32 | 90 | 5 | 316 | 651 | 31 | EU2 |
| Cement | 1 | 75 | | | 30 | | | 239 | | | SP2 |
| Cement I | 3 | 25 | | | 20 | | | 59 | | | SP3 |
| Cement II | 7 | 422 | | | 266 | | | 599 | | | SP3 |
| Cement III | 5 | 95 | | | 67 | | | 44 | | | SP3 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Cement IV | 4 | 23 | | | 19 | | | 85 | | | SP3 |
| Cement V | 5 | 52 | | | 41 | | | 403 | | | SP3 |
| Cement VI | 6 | 36 | | | 30 | | | 204 | | | SP3 |
| Cement VII | 7 | 54 | | | 38 | | | 275 | | | SP3 |
| Cement - Albasete | 1 | 32 | | | 31 | | | 315 | | | SP3 |
| Cement - Alicante | 8 | 31 | | | 23 | | | 245 | | | SP3 |
| Cement - Almeria | 3 | 73 | | | 45 | | | 287 | | | SP3 |
| Cement - Asturias | 5 | 60 | | | 30 | | | 408 | | | SP3 |
| Cement - Barcelona | 18 | 46 | | | 37 | | | 273 | | | SP3 |
| Cement - Cantabria | 5 | 56 | | | 30 | | | 378 | | | SP3 |
| Cement - Cordoba | 1 | 74 | | | 19 | | | 341 | | | SP3 |
| Cement - Guipuzcoa | 6 | 56 | | | 31 | | | 315 | | | SP3 |
| Cement - Huelva | 3 | 28 | | | 27 | | | 234 | | | SP3 |
| Cement - Huesca | 3 | 92 | | | 41 | | | 330 | | | SP3 |
| Cement - Jaen | 5 | 44 | | | 35 | | | 382 | | | SP3 |
| Cement - Leon | 3 | 93 | | | 42 | | | 509 | | | SP3 |
| Cement - Lugo | 2 | 29 | | | 45 | | | 439 | | | SP3 |
| Cement - Malaga | 6 | 56 | | | 47 | | | 357 | | | SP3 |
| Cement - Mallorca | 1 | 29 | | | 43 | | | 302 | | | SP3 |
| Cement - Madrid | 9 | 39 | | | 26 | | | 330 | | | SP3 |
| Cement - Murcia | 8 | 57 | | | 35 | | | 305 | | | SP3 |
| Cement - Navarra | 6 | 43 | | | 31 | | | 350 | | | SP3 |
| Cement - Sevilla | 2 | 24 | | | 16 | | | 170 | | | SP3 |
| Cement - Tarragona | 4 | 33 | | | 15 | | | 290 | | | SP3 |
| Cement - Toledo | 8 | 43 | | | 31 | | | 338 | | | SP3 |
| Cement - Valencia | 11 | 32 | | | 23 | | | 285 | | | SP3 |
| Cement - Vizcaya | 10 | 54 | | | 40 | | | 272 | | | SP3 |
| Cement - Zaragoza | 4 | 75 | | | 33 | | | 387 | | | SP3 |
| CEM I 52,5 R | 1 | 37 | | | 25 | | | 245 | | | SP4 |
| CEM II/BL 32,5 N | 1 | 27 | | | 13 | | | 211 | | | SP4 |
| CEM III/A 42,5 N/SR | 1 | 109 | | | 38 | | | 240 | | | SP4 |
| CEM IV/B (V) 32,5 N | 1 | 97 | | | 41 | | | 373 | | | SP4 |
| CAC Electroland molins | 1 | 75 | | | 128 | | | 22 | | | SP4 |
| CAC Aluminite | 1 | 84 | | | 136 | | | 44 | | | SP4 |
| CAC Ciment Fondu Lafarge | 1 | 98 | | | 128 | | | 30 | | | SP4 |
| CAC Secar 51 Lafarge | 1 | 208 | | | 220 | | | 95 | | | SP4 |
| CAC Gorkal 70 Gorka | 1 | 7 | | | 2 | | | 12 | | | SP4 |
| Aggregates | | | | | | | | | | | |
| Sea sand | 6 | 6 | | | 4 | | | 56 | | | SP3 |
| Sand I | 4 | 30 | | | 28 | | | 31 | | | SP3 |
| Sand II | 7 | 7 | | | 3 | | | 12 | | | SP3 |
| Sand | 1 | 14 | | | 17 | | | 267 | | | SP2 |
| Gravels | 1 | 23 | | | | | | 47 | | | SP3 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Natural raw materials | | | | | | | | | | | |
| Gypsum | 1 | 3 | | | 9 | | | 224 | | | SP2 |
| Gypsum | 3 | 10 | | | 4 | | | 56 | | | SP3 |
| Gypsum | 5 | 36 | | | 26 | | | 155 | | | SP3 |
| Gypsum | 7 | 51 | | | 34 | | | 167 | | | SP3 |
| Gypsum | 5 | 11 | | | 7 | | | 70 | | | SP3 |
| Natural covering stones | | | | | | | | | | | |
| Granite | 1 | 87 | 282 | 7 | 44 | 133 | 2 | 1021 | 1869 | 234 | EU2 |
| Granite | 1 | 74 | | | 97 | | | 1378 | | | IT1 |
| Granite Avila | 2 | 86 | 113 | 60 | 68 | 75 | 62 | 1206 | 1309 | 1104 | SP3 |
| Granite Badajoz | 23 | 66 | 144 | 7 | 41 | 107 | 3 | 958 | 1362 | 234 | SP3 |
| Granite Caceres | 10 | 78 | 104 | 37 | 44 | 133 | 9 | 997 | 1236 | 629 | SP3 |
| GraniteLa Coruña | 3 | 92 | 114 | 78 | 65 | 101 | 44 | 1329 | 1424 | 1225 | SP3 |
| Granite Huelva | 1 | 33 | | | 2 | | | 337 | | | SP3 |
| Granite Huesca | 1 | 282 | | | | | | 712 | | | SP3 |
| Granite Lugo | 6 | 93 | 169 | 42 | 33 | 63 | 11 | 951 | 1324 | 454 | SP3 |
| Granite Madrid | 13 | 91 | 172 | 44 | 42 | 60 | 11 | 976 | 1283 | 567 | SP3 |
| Granite Orense | 5 | 78 | 98 | 43 | 43 | 81 | 12 | 1251 | 1869 | 754 | SP3 |
| Granite Pontevedra | 12 | 112 | 198 | 36 | 45 | 124 | 6 | 1112 | 1394 | 453 | SP3 |
| Granite Salamanca | 3 | 61 | 82 | 44 | 38 | 54 | 26 | 1112 | 1180 | 1022 | SP3 |
| Granite Segovia | 3 | 127 | 166 | 90 | 58 | 67 | 49 | 1049 | 1123 | 1007 | SP3 |
| Granite Sevilla | 1 | 30 | | | 111 | | | 790 | | | SP3 |
| Granite Toledo | 1 | 191 | | | 74 | | | 1253 | | | SP3 |
| Granite Zamora | 3 | 74 | 95 | 59 | 47 | 74 | 2 | 987 | 1318 | 578 | SP3 |
| Marble | 1 | 33 | | | 1 | | | 10 | | | IT1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| Coal FA | 1 | 160 | | | 62 | | | 459 | | | SP4 |
| Ashes (Asturias) | 68 | 91 | 106 | 80 | 89 | 104 | 77 | 1059 | 1223 | 895 | SP1 |
| Ashes (Galicia) | 1 | 90 | | | 91 | | | 1039 | | | SP1 |
| Metallurgical slag | | | | | | | | | | | |
| BFS | 1 | 167 | | | 48 | | | 232 | | | SP4 |

Numbers in **Bold Italic**= MDA (minimum detection level)

Table 27 Sweden
648 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|----------------------------------|-----|-------------------------------|------|-----|-------------------------------|-----|----------|-----------------------------|------|----------|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Brick | 21 | 96 | | | 126 | | | 925 | | | EU3 |
| Brick | 12 | 96 | 152 | 41 | 127 | 178 | 100 | 960 | 1090 | 560 | S3 |
| Brick (clay) | 35 | 98 | 164 | 40 | 116 | 180 | 71 | 888 | 1108 | 548 | S1 |
| Brick (sand-limestone) | 3 | 10 | 15 | 7 | 7 | 10 | 4 | 162 | 440 | 22 | S1 |
| Concrete | | | | | | | | | | | |
| Concrete | 19 | 46 | 63 | 31 | 74 | 127 | 46 | 714 | 932 | 573 | S1 |
| Concrete° | 1 | 52 | 67 | 44 | 74 | 89 | 59 | 630 | 670 | 590 | S2 |
| Concrete° | 1 | 44 | 159 | 8 | 63 | 389 | 6 | 696 | 1225 | 115 | EU2 |
| Concrete iron ore ballast | 2 | 26 | | | 32 | | | 68 | | | S1 |
| Concrete-hoforsit ballast | 3 | 3 | | | 6 | | | 32 | | | S1 |
| Concrete-hoforsit ballast | 1 | 3 | | | 3 | | | 20 | | | S1 |
| Concrete for radiation shielding | 1 | 8 | | | 14 | | | 133 | | | S1 |
| Aerated+light weight concrete | 4 | 551 | 2200 | 14 | 100 | 190 | 15 | 734 | 1100 | 260 | S2 |
| Aerated concrete (sand based) | 36 | 42 | 132 | 3 | 49 | 157 | 4 | 276 | 505 | 21 | S1 |
| Aerated concrete (alum shale)°° | 70 | 1300 | 2620 | 620 | 67 | 115 | 30 | 770 | 1062 | 618 | S3 |
| Heavy concrete | 15 | 48 | | | 85 | | | 703 | | | EU3 |
| Aerated with alum shale | 22 | 56 | | | 70 | | | 333 | | | EU3 |
| Aerated with alum shale | 13 | 425 | 559 | 272 | 31 | 39 | 24 | 506 | 566 | 445 | S1 |
| Cement | | | | | | | | | | | |
| Cement | 1 | 56 | 190 | 22 | 72 | 110 | 33 | 196 | 370 | 22 | S2 |
| Cement | 1 | 56 | 185 | 22 | 48 | 74 | 33 | 233 | 370 | 22 | EU2 |
| Cement | 20 | 44 | 168 | 21 | 41 | 92 | 24 | 235 | 378 | 21 | S1 |
| Cement | 8 | 56 | | | 56 | | | 233 | | | EU3 |
| Aggregates | | | | | | | | | | | |
| Gravel | 157 | 44 | 78 | 15 | 56 | 463 | 21 | 820 | 1206 | 180 | S1 |
| Shingels | 113 | 52 | 99 | 22 | 89 | 178 | 29 | 821 | 1199 | 311 | S1 |
| Macadam ballast | 57 | 52 | 167 | 7 | 86 | 283 | 3 | 814 | 1317 | 137 | S1 |
| Lightweight aggregate | 10 | 144 | | | 159 | | | 999 | | | EU3 |
| Concrete Ballast | 1 | 54 | 56 | 52 | 80 | 93 | 67 | 720 | 740 | 700 | S2 |
| Natural raw materials | | | | | | | | | | | |
| Gypsum plaster | 1 | 3 | | | 1 | | | 22 | | | EU3 |
| Gypsum | 2 | 10 | | | 21 | | | 170 | | | S1 |
| Gypsum board | 8 | 4 | 9 | 2 | 4 | 12 | 1 | 28 | 68 | 3 | S1 |
| Natural covering stones | | | | | | | | | | | |
| Balmoral Red Granite | 1 | 154 | | | 289 | | | 1265 | | | IT1 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--------------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Baltic Bronze Granite (Granodiorite) | 1 | 69 | | | 74 | | | 1305 | | | IT1 |
| Swedish black Gabro | 1 | 4 | | | 4 | | | 335 | | | IT1 |
| Imperial Red Granite | 1 | 128 | | | 184 | | | 1301 | | | IT1 |
| Diorite | 1 | 1 | | | 0.2 | | | 55 | | | IT1 |

INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS

Byproduct Gypsum

| | | | | | | | | | | | |
|------------------|---|----|--|--|----|--|--|----|--|--|----|
| Byproduct gypsum | 3 | 22 | | | 55 | | | 24 | | | S1 |
|------------------|---|----|--|--|----|--|--|----|--|--|----|

Metallurgical slag

| | | | | | | | | | | | |
|------|---|-----|--|--|-----|--|--|-----|--|--|----|
| Slag | 2 | 118 | | | 148 | | | 141 | | | S1 |
|------|---|-----|--|--|-----|--|--|-----|--|--|----|

° calculated from ballast (sand, gravel) and cement assuming mixing ratio 79:14:7 for ballast:cement:water. IN RP 96

°° no production since 1975

Numbers in Bold Italic= MDA (minimum detection level)

Numbers in Bold underline= average from minimum and maximum

Table 28 Switzerland
86 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|-------------------------------|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Clay brick [^] | 18 | 47 | 62 | 32 | | | | | | | SW1 |
| Concrete | | | | | | | | | | | |
| Concrete brick [^] | 2 | <u>12</u> | 12 | 11 | | | | | | | SW1 |
| Aerated concrete [^] | 2 | <u>19</u> | 28 | 9 | | | | | | | SW1 |
| Pumice concrete [^] | 5 | 149 | 249 | 28 | | | | | | | SW1 |
| Cement | | | | | | | | | | | |
| Cement [^] | 10 | 20 | 29 | 11 | | | | | | | SW1 |
| Tiles | | | | | | | | | | | |
| Gravel [^] | 12 | 25 | 50 | 9 | | | | | | | SW1 |
| Sand [^] | 22 | 20 | 56 | 9 | | | | | | | SW1 |
| Rhenice pumice [^] | 5 | 237 | 415 | 121 | | | | | | | SW1 |
| Natural raw materials | | | | | | | | | | | |
| Lime [^] | 3 | <u>17</u> | 22 | 11 | | | | | | | SW1 |
| Sand-lime stone [^] | 2 | <u>13</u> | 15 | 11 | | | | | | | SW1 |
| Gypsum [^] | 5 | 15 | 18 | 13 | | | | | | | SW1 |

Numbers in Bold Italic= MDA (minimum detection level)

Numbers in Bold underline= average from minimum and maximum

[^] Data on emanation and/or exhalation are reported in Table 31

Table 29 Turkey
86 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|------|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Red brick | 11 | 31 | 49 | 25 | 37 | 51 | 27 | 776 | 1092 | 587 | TR1 |
| White brick | 4 | 70 | 75 | 66 | 70 | 79 | 53 | 923 | 1080 | 723 | TR1 |
| Lightweight brick | 3 | 9 | 13 | 4 | 10 | 17 | 6 | 208 | 326 | 148 | TR1 |
| Concrete | | | | | | | | | | | |
| Concrete | 5 | 16 | 27 | 7 | 9 | 22 | 1 | 151 | 465 | 45 | TR1 |
| Light concrete | 6 | 17 | 24 | 12 | 25 | 37 | 14 | 527 | 879 | 405 | TR1 |
| Cement | | | | | | | | | | | |
| Grey cement | 37 | 40 | 82 | 18 | 26 | 49 | 8 | 317 | 476 | 169 | TR1 |
| White cement | 5 | 33 | 38 | 28 | 16 | 23 | 8 | 99 | 128 | 62 | TR1 |
| Sulphate resistant cement | 7 | 22 | 33 | 15 | 14 | 18 | 11 | 176 | 230 | 147 | TR1 |
| Natural raw materials | | | | | | | | | | | |
| Gypsum | 7 | 5 | 15 | 1 | 5 | 18 | 1 | 59 | 186 | 2 | TR1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Bauxite residues/red mud | | | | | | | | | | | |
| RM | 1 | 210 | | | 539 | | | 112 | | | TR2 |

Table 30 United Kingdom
249 samples

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|--|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Brick | | | | | | | | | | | |
| Clay brick | 23 | 52 | | | 44 | | | 620 | | | GB2 |
| Granite brick (reformite) | 3 | 11 | | | 13 | | | 590 | | | GB2 |
| Granite brick | 7 | 89 | | | 81 | | | 1000 | | | GB2 |
| Calcium silicate (rock aggregate) brick | 3 | 52 | | | 4 | | | 790 | | | GB2 |
| Calcium silicate brick (gravel aggregate) | 5 | 7 | | | 3 | | | 350 | | | GB2 |
| Calcium silicate brick (flint aggregate) | 5 | 2 | | | 5 | | | 12 | | | GB2 |
| Clay brick [^] | 6 | 65 | | | 48 | | | | | | GB1 |
| Silica brick [^] | 1 | 33 | | | 15 | | | | | | GB1 |
| Flint brick [^] | 1 | 70 | | | 52 | | | | | | GB1 |
| Oil shale brick [^] | 1 | 76 | | | 43 | | | | | | GB1 |
| Crushed granite bricks and blocks [^] | 3 | 40 | | | 39 | | | | | | GB1 |
| Expanded clay blocks [^] | 2 | 94 | | | 57 | | | | | | GB1 |
| Concrete | | | | | | | | | | | |
| Concrete | 4 | 74 | | | 30 | | | 519 | | | EU2 |

| BUILDING MATERIALS | N. | Ra-226 (Bq kg ⁻¹) | | | Th-232 (Bq kg ⁻¹) | | | K-40 (Bq kg ⁻¹) | | | Ref. |
|---|----|-------------------------------|-----|-----|-------------------------------|-----|-----|-----------------------------|-----|-----|---------|
| | | mean | max | min | mean | max | min | mean | max | min | |
| Concrete blocks - PFA | 3 | 66 | | | 37 | | | 433 | | | GB2 |
| Aerated concrete | 2 | 89 | | | 13 | | | 650 | | | GB2 |
| Light weight concrete | 10 | 59 | | | 26 | | | 370 | | | GB3 |
| Concrete block [^] | 1 | 18 | | | 42 | | | | | | GB1 |
| Building blocks - PFA [^] | 2 | 54 | | | 43 | | | 490 | | | EU2 |
| Cement | | | | | | | | | | | |
| Cement | 6 | 22 | | | 18 | | | 160 | | | GB2 |
| Cement-natural gypsum | 2 | <u>109</u> | 210 | 7 | <u>28</u> | 55 | | | | | GB2 |
| Aggregate | | | | | | | | | | | |
| Sand and gravel | 10 | 4 | | | 7 | | | 33 | | | GB2,GB3 |
| Natural raw materials | | | | | | | | | | | |
| Gypsum | 73 | 22 | | | 7 | | | 148 | | | GB3 |
| Natural covering stones | | | | | | | | | | | |
| Granite | 7 | 89 | | | 81 | | | 111 | | | GB3 |
| Vermiculite | 1 | 93 | | | 0 | | | 1400 | | | GB2 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | | | | |
| Ashes | | | | | | | | | | | |
| PFA | 1 | 89 | | | 68 | | | 900 | | | EU2 |
| Byproduct gypsum | | | | | | | | | | | |
| PHG | 6 | 790 | | | 17 | | | 62 | | | GB2 |
| PHG from carbonatite | 1 | 120 | | | 23 | | | | | | GB2 |
| PHG | 60 | 629 | | | 19 | | | 41 | | | GB3 |

Numbers in Bold underline= average from minimum and maximum

[^] Data on emanation and/or exhalation are reported in Table 31

Table of radon emanation and exhalation rate of building materials used in 15 European countries

Table 31 Data on radon emanation and exhalation rate of building materials used in European countries.*Numbers in Bold Italic= MDA (minimum detection level)***Numbers in Bold underline= average from minimum and maximum**

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|--|-----------------|-----------|----------------------------------|------------------|--------------------------|--------------------------------------|---|------|
| BELGIUM (40 samples from TABLE 2 + 1 sample with only emanation/exhalation rate data) | | | | | | | | |
| Brick | | | | | | | | |
| Brick ^b | 4 | | | 0.7 (0.1-2) | 35 (22-72) | mBq m ⁻² h ⁻¹ | 59 (40-85) | BE2 |
| | | 6 | | 0.1 | 22 | mBq m ⁻² h ⁻¹ | 85 | BE2 |
| | | 6 | | 0.1 | 22 | mBq m ⁻² h ⁻¹ | 70 | BE2 |
| | | 5 | | 0.3 | 22 | mBq m ⁻² h ⁻¹ | 40 | BE2 |
| | | 9 | | 2 | 72 | mBq m ⁻² h ⁻¹ | 40 | BE2 |
| Natural raw materials | | | | | | | | |
| Plasterboard | 14 | 0.9 | | | 28 | mBq m ⁻² h ⁻¹ | 11 | BE2 |
| Gypsum blocks | 1 | | | | 24 | mBq m ⁻² h ⁻¹ | | BE2 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| By-products Gypsum | | | | | | | | |
| PHG board | 22 ^c | | | 14 | 1548 | mBq m ⁻² h ⁻¹ | 430 (330-520) | BE2 |
| DENMARK (69 samples from TABLE 6) | | | | | | | | |
| Brick | | | | | | | | |
| Bricks | 1 | | | 0.2 | 0.6 | mBq kg ⁻¹ h ⁻¹ | 42 | DK2 |
| Concrete | | | | | | | | |
| Concrete (5% FA-cement) | 1 | | | 11 | 9 | mBq kg ⁻¹ h ⁻¹ | 10 | DK2 |
| Concrete (10% FA-cement) | 1 | | | 10 | 9 | mBq kg ⁻¹ h ⁻¹ | 11 | DK2 |
| Concrete (15% FA-cement) | 1 | | | 9 | 8 | mBq kg ⁻¹ h ⁻¹ | 12 | DK2 |
| Concrete (20% FA-cement) | 1 | | | 8 | 8 | mBq kg ⁻¹ h ⁻¹ | 13 | DK2 |
| Concrete (25% FA-cement) | 1 | | | 9 | 9 | mBq kg ⁻¹ h ⁻¹ | 14 | DK2 |
| Concrete (30% FA-cement) | 1 | | | 8 | 9 | mBq kg ⁻¹ h ⁻¹ | 14 | DK2 |
| Concrete (25% FA-PTL cem.) | 1 | | | 9 | 10 | mBq kg ⁻¹ h ⁻¹ | 15 | DK2 |
| Concrete | 1 | | | 6 | 17 | mBq kg ⁻¹ h ⁻¹ | 35 | DK2 |
| Cement | | | | | | | | |
| Cement (5% FA) | 1 | | | 0.7 | 15 | mBq kg ⁻¹ h ⁻¹ | 28 | DK2 |
| Aggregates | | | | | | | | |
| Sand | 1 | | | 5 | 25 | mBq kg ⁻¹ h ⁻¹ | 7 | DK2 |
| Granite chippings | 1 | | | 2 | 10 | mBq kg ⁻¹ h ⁻¹ | 59 | DK2 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| Ashes | | | | | | | | |
| Coal ash | 15 | | | 0.5 | 5 | mBq kg ⁻¹ h ⁻¹ | 140 (120-180) | DK2 |
| Coal ash | 16 | | | 0.4 | 49 | mBq kg ⁻¹ h ⁻¹ | 170 (130-200) | DK2 |
| Coal ash | 14 | | | 0.4 | 49 | mBq kg ⁻¹ h ⁻¹ | 160 (130-190) | DK2 |
| Coal ash | 12 | | | 0.9 | 10 | mBq kg ⁻¹ h ⁻¹ | 150 (120-170) | DK2 |

^b Exhalation rate measured on 4 out of 14 samples^c Emanation and exhalation rate refer to unknown number of samples

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|---|----------------|-----------|----------------------------------|------------------|--------------------------|--|---|---------------|
| FINLAND (20 samples from TABLE 8) | | | | | | | | |
| Concrete | | | | | | | | |
| Slag aggregate concrete | 1 ^d | 15 | 1800 | | 11067 (10000-12000) | mBq m ⁻² h ⁻¹ | 75 | FIN2, FIN3 |
| Concrete | 1 | 20 | | | 19700 | mBq m ⁻² h ⁻¹ | 42 | FIN2 |
| Concrete | 1 | 20 | | | 21700 | mBq m ⁻² h ⁻¹ | 49 | FIN2 |
| Concrete | 1 | 20 | | | 22200 | mBq m ⁻² h ⁻¹ | 60 | FIN2 |
| Concrete | 1 | 18 | | | 27000 | mBq m ⁻² h ⁻¹ | 66 | FIN2 |
| Concrete | 1 | 15 | | | 23200 | mBq m ⁻² h ⁻¹ | 63 | FIN2 |
| Concrete | 1 ^e | | | | | | | FIN2 |
| | | 20 | | | 31500 | mBq m ⁻² h ⁻¹ | 60 | FIN2 |
| | | 15 | | | 24000 | mBq m ⁻² h ⁻¹ | 60 | FIN2 |
| | | 10 | | | 15900 | mBq m ⁻² h ⁻¹ | 60 | FIN2 |
| | | 2.5 | | | 1900 | mBq m ⁻² h ⁻¹ | 60 | FIN2 |
| Concrete | 11 | 15 | 2350 | | 0.4 | Bq m ⁻² h ⁻¹ /Bq kg ⁻¹ | 33 (18-43) | FIN3 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| By-product gypsum | | | | | | | | |
| By-product gypsum | 1 | 6.7 | | | 13900 | mBq m ⁻² h ⁻¹ | 319 | FIN2 |
| By-product gypsum | 1 ^f | | | | | | | FIN2 |
| | | 20 | | | 42300 | mBq m ⁻² h ⁻¹ | 482 | FIN2 |
| | | 15 | | | 31200 | mBq m ⁻² h ⁻¹ | 482 | FIN2 |
| | | 10 | | | 20300 | mBq m ⁻² h ⁻¹ | 482 | FIN2 |
| | | 7.5 | | | 18600 | mBq m ⁻² h ⁻¹ | 482 | FIN2 |
| | | 5 | | | 10100 | mBq m ⁻² h ⁻¹ | 482 | FIN2 |
| | | 2.5 | | | 4700 | mBq m ⁻² h ⁻¹ | 482 | FIN2 |
| FRANCE (73 samples from TABLE 9) | | | | | | | | |
| Bricks | | | | | | | | |
| Bricks | 3 | | | | 245 | mBq m ⁻² h ⁻¹ | <u>54</u> (50-58) | FR1 |
| Hollow brick | 5 | | | | 184 | mBq m ⁻² h ⁻¹ | <u>42</u> (40-44) | FR1 |
| Concrete | | | | | | | | |
| Concrete | 5 | | | | 1130 | mBq m ⁻² h ⁻¹ | <u>13</u> (12.6-13.4) | FR1 |
| Concrete | 3 | | | | 1883 | mBq m ⁻² h ⁻¹ | 13 | FR1 |
| Concrete hollow blocks | 2 | | | | 1105 | mBq m ⁻² h ⁻¹ | <u>8</u> (5-12) | FR1 |
| Cellular concrete | 4 | | | | 254 | mBq m ⁻² h ⁻¹ | <u>9</u> | FR1 |
| Tile | | | | | | | | |
| Tile (ardesia) | 2 | | | | 194 | mBq m ⁻² h ⁻¹ | <u>36</u> (34-39) | FR1 |
| Tile (faience) | 3 | | | | 122 | mBq m ⁻² h ⁻¹ | <u>113</u> (112-114) | FR1 |
| Tile (green marble) | 3 | | | | 108 | mBq m ⁻² h ⁻¹ | <u>1</u> | FR1 |

^d 3 measurements of the same sample

^e 4 measurements of the same sample with 4 different thickness

^f 6 measurements of the same sample with 6 different thickness

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | Exhalation rate unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|--|-----|-----------|----------------------------------|------------------|---------------------------------|-------------------------------------|---|------|
| Tile (stoneware) | 5 | | | | 119 | mBq m ⁻² h ⁻¹ | <u>141</u> (139-142) | FR1 |
| Tile (stoneware) | | | | | 94 | mBq m ⁻² h ⁻¹ | <u>68</u> (62-74) | FR1 |
| Tile (terracotta) | 2 | | | | 281 | mBq m ⁻² h ⁻¹ | <u>61</u> (54-67) | FR1 |
| Tile (terracotta) | 2 | | | | 112 | mBq m ⁻² h ⁻¹ | <u>49</u> (46-52) | FR1 |
| Tile (white marble) | 4 | | | | 119 | mBq m ⁻² h ⁻¹ | <u>2</u> | FR1 |
| Natural covering stones | | | | | | | | |
| Granite | 13 | | | | 49 | mBq m ⁻² h ⁻¹ | <u>370</u> (360-380) | FR1 |
| Stone slab | 3 | | | | 259 | mBq m ⁻² h ⁻¹ | <u>3</u> | FR2 |
| Other | | | | | | | | |
| Plaster | 2 | | | | 130 | mBq m ⁻² h ⁻¹ | <u>3</u> | FR1 |
| Plaster | 6 | | | | 497 | mBq m ⁻² h ⁻¹ | <u>11</u> (8-14) | FR1 |
| Plaster | 2 | | | | 248 | mBq m ⁻² h ⁻¹ | <u>5</u> (4.6-5.1) | FR1 |
| GERMANY (27 samples from TABLE 10 + 331 samples with only emanation/exhalation rate data) | | | | | | | | |
| Bricks | | | | | | | | |
| Bricks | 180 | | | 1.3 (0.01-15) | | | | GE3 |
| Sandstone bricks | 7 | | | 12 | | | | GE3 |
| Bricks | 1 | 10-15 | 2200 | 0.7 | 180 | mBq m ⁻² h ⁻¹ | 68 | GE2 |
| Concrete | | | | | | | | |
| Areated concrete | 3 | | | 11(6-20) | | | | GE3 |
| Areated concrete | 1 | | | | 1000 | mBq m ⁻² h ⁻¹ | | EU2 |
| Areated concrete | 5 | | 520 | 24 | 972 (432-1836) | mBq m ⁻² h ⁻¹ | 19 | GE2 |
| Concrete | 1 | | | | 1100 | mBq m ⁻² h ⁻¹ | | EU2 |
| Concrete | 63 | | | 14 (4-41) | | | | GE3 |
| Heavy weight concrete | 5 | | 2300 | 4 | 1260 (180-1980) | mBq m ⁻² h ⁻¹ | 52 | GE2 |
| Precast concrete | 20 | | | 33 (11-40) | | | | GE3 |
| Cement | | | | | | | | |
| Cement | 9 | | | 2 (0.8-3) | | | 97 (23-330) | GE3 |
| Aggregates | | | | | | | | |
| Sand, gravel | 24 | | | 13 (7-41) | | | | GE3 |
| Natural raw materials | | | | | | | | |
| Pumice | 4 | 10-15 | | | 2.6 (0.6-6.3) | Bq m ⁻² h ⁻¹ | | GE2 |
| | | | 1350 | 6 | | | 48 | |
| | | | 1020 | 5 | | | 107 | |
| | | | 800 | 7 | | | 48 | |
| | | | 1340 | 2 | | | 63 | |
| Gypsum | 4 | 10-15 | | | 2.8 (0.2-18.4 ^g) | Bq m ⁻² h ⁻¹ | | GE2 |
| | | | 850 | 5 | | | 10 ^h | GE2 |

^g This value is referred to chemical gypsum^h In table 10 are reported as a single sample for a total of 3 samples

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | Exhalation rate unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|---|-----------------|--------|-------------------------------|------------------|-----------------------|--------------------------------------|--|------|
| | | | 1280 | 5 | | | 10 ⁹ | GE2 |
| | | | 900 | 3 | | | 41 | GE2 |
| | | | 1250 | 14 | | | 37 | GE2 |
| Limestone | 5 | 10-15 | 1840 | 28 | 4.8 (1.3-10.8) | Bq m ⁻² h ⁻¹ | 9 | GE2 |
| Limestone/ marble | 10 | | | 10 (1- 29) | | | | GE3 |
| Sandstone | 1 | 10-15 | 2200 | 19 | 936 | mBq m ⁻² h ⁻¹ | 11 | GE2 |
| Natural covering stones | | | | | | | | |
| Marble | 1 | | | | 180 | mBq m ⁻² h ⁻¹ | | GE2 |
| Quarystone (porphyry) | 1 | 10-15 | 2700 | 16 | 2052 | mBq m ⁻² h ⁻¹ | 44 | GE2 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| Ashes | | | | | | | | |
| Fly ash | 9 | | | 2 (0.06-11) | | | | |
| Slag | 3 | | | 0.4 (0.3-0.4) | | | | |
| Slagstone | 1 | | 1930 | 2 | 648 | mBq m ⁻² h ⁻¹ | 78 | GE2 |
| GREECE (253 samples from Table 11 + 1 sample with only emanation/exhalation rate data) | | | | | | | | |
| Bricks | | | | | | | | |
| Brick | 3 | | | 51 | | | 52 | GR3 |
| Brick | 1 | | | 67 | | | 93 | GR3 |
| Brick | 1 | | | 65 | | | 81 | GR3 |
| Brick | 1 | | | 17 | | | 48 | GR3 |
| Brick | 1 | | | 54 | | | 63 | GR3 |
| Brick | 1 | | | 52 | | | 63 | GR3 |
| Brick | 3 | | | 3 (0.5-12) | 8 (1.3-35) | mBq kg ⁻¹ h ⁻¹ | 36 (25-83) | GR13 |
| Brick (Alatini) | 1 | | | | 1 | mBq kg ⁻¹ h ⁻¹ | 45 | GR10 |
| Brick (Dragofina) | 1 | | | | 4 | mBq kg ⁻¹ h ⁻¹ | 41 | GR10 |
| Brick (Kalochoi) | 1 | | | | 2 | mBq kg ⁻¹ h ⁻¹ | 53 | GR10 |
| Brick (Kokkinogenis) | 1 | | | | 27 | mBq kg ⁻¹ h ⁻¹ | 42 | GR10 |
| Brick (Lamia) | 1 | | | | 6 | mBq kg ⁻¹ h ⁻¹ | 46 | GR10 |
| Clay brick | 13 | 20 | | | 360 | mBq m ⁻² h ⁻¹ | 37 (25-48) | GR1 |
| Clay brick | 13 ⁱ | 20 | | 3 (max 8) | 210 (max 420) | mBq m ⁻² h ⁻¹ | 35 (18-66) | GR4 |
| Pumice stone brick | 1 | | | | 2880 | mBq m ⁻² h ⁻¹ | 48 | GR1 |
| Concrete | | | | | | | | |
| Concrete | 20 | | | 13 | 12 (4-24) | mBq kg ⁻¹ h ⁻¹ | 14 (7-41) | GR11 |
| Concrete block | 3 | | | 85 | | | 85 | GR3 |
| Concrete block | 1 | | | 75 | | | 41 | GR3 |
| Concrete block | 1 | | | 73 | | | 25 | GR3 |
| Concrete block | 2 | | | 82 | | | 37 | GR3 |
| Concrete block | 3 | | | 76 | | | 30 | GR3 |
| Concrete block | 3 | | | 70 | | | 26 | GR3 |
| Concrete block | 3 | | | 75 | | | 22 | GR3 |
| Concrete block | 4 | | | 75 | | | 48 | GR3 |
| Concrete block | 2 | | | 81 | | | 37 | GR3 |

ⁱ Radiometric measure on 50 samples

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|--|-----------------|-----------|----------------------------------|------------------|--------------------------|--------------------------------------|---|------|
| Concrete block | 1 | | | 82 | | | 30 | GR3 |
| Concrete block | 1 | | | 14 | | | 48 | GR3 |
| Concrete block | 15 | 15-20 | | 14 (10-20) | 3.5 (1-6.7) | Bq m ⁻² h ⁻¹ | 35 (8-54) | GR4 |
| Concrete block cement Kamari 0% PFA | 1 | | | | 10 | mBq kg ⁻¹ h ⁻¹ | 7 | GR10 |
| Concrete block cement Kamari 10% PFA | 1 | | | | 23 | mBq kg ⁻¹ h ⁻¹ | 11 | GR10 |
| Concrete block cement Kamari 20% PFA | 1 | | | | 38 | mBq kg ⁻¹ h ⁻¹ | 17 | GR10 |
| Concrete block cement Thessaloniki 0% PFA | 1 | | | | 18 | mBq kg ⁻¹ h ⁻¹ | 8 | GR10 |
| Concrete block cement Thessaloniki 10% PFA | 1 | | | | 72 | mBq kg ⁻¹ h ⁻¹ | 11 | GR10 |
| Concrete block cement Thessaloniki 20% PFA | 1 | | | | 30 | mBq kg ⁻¹ h ⁻¹ | 11 | GR10 |
| Concrete slab (FA cement) | 1 | | | | 17.6 (13-22.3) | Bq m ⁻² h ⁻¹ | 140 | GR1 |
| Cement | | | | | | | | |
| Cement | 5 | | | 56 | | | 218 | GR3 |
| Cement | 4 | | | 53 | | | 215 | GR3 |
| Cement | 2 | | | 55 | | | 96 | GR3 |
| Aggregates | | | | | | | | |
| Rock sand (limestone, sand) | 2 | | | 63 | | | 45 (9-81) | GR3 |
| Tile | | | | | | | | |
| Tile | 2 | | | 50 | | | 89 | GR3 |
| Tile | 1 | | | 36 | | | 26 | GR3 |
| Tile | 2 | | | 43 | | | 78 | GR3 |
| Tile | 1 | | | 50 | | | 26 | GR3 |
| Granite tile | 1 | | | | 10.8 | Bq m ⁻² h ⁻¹ | | GR1 |
| Granite tile | 26 | 1 | | 8 (max 13) | 1240 (max 3540) | mBq m ⁻² h ⁻¹ | 67 (2-195) | GR4 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| Ashes | | | | | | | | |
| Fly ash | 12 | | | | 176 (43-421) | mBq kg ⁻¹ h ⁻¹ | 929 (663-1176) | GR8 |
| BA | 2 | | | | 176 (133-220) | mBq kg ⁻¹ h ⁻¹ | 61 (580-654) | GR8 |
| ITALY (285 samples from Table 14 + 7 sample with only emanation/exhalation rate data) | | | | | | | | |
| Brick | | | | | | | | |
| Bricks | 30 ^j | | | 2 | 5 | mBq kg ⁻¹ h ⁻¹ | 40 | IT2 |
| Bricks | 1 | | | 2 | 137 | mBq kg ⁻¹ h ⁻¹ | 110 | IT13 |
| Bricks | 1 | | | 2 | 16 | mBq kg ⁻¹ h ⁻¹ | 96 | IT13 |
| Bricks | 1 | | | 18 | 28 | mBq kg ⁻¹ h ⁻¹ | 20 | IT13 |
| Bricks | 1 | | | 4 | 70 | mBq kg ⁻¹ h ⁻¹ | 35 | IT13 |
| Bricks | 1 | | | 2 | 8 | mBq kg ⁻¹ h ⁻¹ | 34 | IT13 |
| Bricks | 1 | | | 3 | 9 | mBq kg ⁻¹ h ⁻¹ | 76 | IT13 |
| Bricks | 1 | | | 2 | 7 | mBq kg ⁻¹ h ⁻¹ | 32 | IT13 |

^j Radiometric measure on 124 samples
Concrete A*: white limestone as aggregate

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|--|-----------------|-----------|----------------------------------|------------------|--------------------------|--------------------------------------|---|-------|
| Concrete | | | | | | | | |
| Concrete | 1 | | | 7 | 9 | mBq kg ⁻¹ h ⁻¹ | 18 | IT13 |
| Concrete | 1 | | | 16 | 16 | mBq kg ⁻¹ h ⁻¹ | 13 | IT13 |
| Concrete A* | 1 | 10 | | | 11 | mBq kg ⁻¹ h ⁻¹ | | IT2.A |
| Concrete A* (cement+5%FA South Africa) | 1 | 10 | | | 9 | mBq kg ⁻¹ h ⁻¹ | | IT2.A |
| Concrete A* (cement+15% FA South Africa) | 1 | 10 | | | 12 | mBq kg ⁻¹ h ⁻¹ | | IT2.A |
| Concrete A* (cement+26% FA South Africa) | 1 | 10 | | | 13 | mBq kg ⁻¹ h ⁻¹ | | IT2.A |
| Concrete A* (cement+5% FA US) | 1 | 10 | | | 8 | mBq kg ⁻¹ h ⁻¹ | | IT2.A |
| Concrete A* (cement+15% FA US) | 1 | 10 | | | 11 | mBq kg ⁻¹ h ⁻¹ | | IT2.A |
| Concrete A* (cement+26% FA US) | 1 | 10 | | | 10 | mBq kg ⁻¹ h ⁻¹ | | IT2.A |
| Concrete B** | 1 | 10 | | | 20 | mBq kg ⁻¹ h ⁻¹ | 16 | IT2 |
| Concrete B** (cement+5% FA South Africa) | 1 | 10 | | | 20 | mBq kg ⁻¹ h ⁻¹ | 17 | IT2 |
| Concrete B** (cement+15% FA South Africa) | 1 | 10 | | | 22 | mBq kg ⁻¹ h ⁻¹ | 18 | IT2 |
| Concrete B** (cement+26% FA South Africa) | 1 | 10 | | | 24 | mBq kg ⁻¹ h ⁻¹ | 19 | IT2 |
| Concrete B** (cement+40% FA South Africa) | 1 | 10 | | | 26 | mBq kg ⁻¹ h ⁻¹ | 19 | IT2 |
| Concrete B** (cement+5% FA US) | 1 | 10 | | | 21 | mBq kg ⁻¹ h ⁻¹ | 13 | IT2 |
| Concrete B** (cement+15% FA US) | 1 | 10 | | | 21 | mBq kg ⁻¹ h ⁻¹ | 13 | IT2 |
| Concrete B** (cement+26% FA US) | 1 | 10 | | | 24 | mBq kg ⁻¹ h ⁻¹ | 13 | IT2 |
| Concrete B** (cement+40% FA US) | 1 | 10 | | | 25 | mBq kg ⁻¹ h ⁻¹ | 15 | IT2 |
| Cement | | | | | | | | |
| Cement | 7 | | 1400-1600 | 15 | 10 (4.1-16) | Bq m ⁻² h ⁻¹ | 38 (12-40) | IT15 |
| Cemento ptl | 21 ^k | | | 5 | 8 | mBq kg ⁻¹ h ⁻¹ | 26 | IT2 |
| Cement -pz | 15 ^l | | | 9 | 32 | mBq kg ⁻¹ h ⁻¹ | 49 | IT2 |
| Cement | 37 ^m | | | 7 | 18 | mBq kg ⁻¹ h ⁻¹ | 33 | IT2.A |
| Aggregates | | | | | | | | |
| Sand & gravel | 31 ⁿ | | | 8 | 8 | mBq kg ⁻¹ h ⁻¹ | 15 | IT2 |
| Natural raw materials | | | | | | | | |
| Clay | 7 | | 2000-2700 | 4 | 5 (2.7-7.4) | Bq m ⁻² h ⁻¹ | 34 (21-42) | IT15 |
| Limestone | 27 | | 1100-2000 | 23 | 11.1 (0.2-22) | Bq m ⁻² h ⁻¹ | 11 (0.4-30) | IT15 |
| Limestone | 4 | | 1100-2400 | 23 | 13.2 (0.4-26) | Bq m ⁻² h ⁻¹ | 9 (1-29) | IT15 |

^k Radiometric measure on 31 samples

^l Radiometric measure on 21 samples

^m Radiometric measure on 78 samples

ⁿ Radiometric measure on 61 samples

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|---|-----------------|-----------|----------------------------------|------------------|--------------------------|--------------------------------------|---|------|
| Lime, hydrated lime | 6 ^o | | | 9 | 4 | mBq kg ⁻¹ h ⁻¹ | 10 | IT2 |
| Limestone | 1 | | | 7 | 36 | mBq kg ⁻¹ h ⁻¹ | 65 | IT13 |
| Limestone | 1 | | | 6 | 34 | mBq kg ⁻¹ h ⁻¹ | 76 | IT13 |
| Sandstone | 1 | | | 6 | 14 | mBq kg ⁻¹ h ⁻¹ | 33 | IT13 |
| Sandstone | 1 | | | 9 | 10 | mBq kg ⁻¹ h ⁻¹ | 14 | IT13 |
| Tuff (volcanic) | 1 | | | 6 | 41 | mBq kg ⁻¹ h ⁻¹ | 14 | IT13 |
| Tuff (volcanic) | 1 | | | 7 | 103 | mBq kg ⁻¹ h ⁻¹ | 25 | IT13 |
| Tuff (volcanic) | 1 | | | 8 | 170 | mBq kg ⁻¹ h ⁻¹ | 34 | IT13 |
| Gypsum | 5 | | 2000-2400 | 8 | <u>2.1</u> (0.2-4.1) | Bq m ⁻² h ⁻¹ | 6 (1-13) | IT15 |
| Natural covering stones | | | | | | | | |
| Granite Limbara Pink | 1 | 3 | | | 468 | Bq m ⁻² h ⁻¹ | 42 | IT1 |
| Peperino Pink | 1 | 3 | | | 482 | Bq m ⁻² h ⁻¹ | 167 | IT1 |
| Sienites (unpolished) | 1 | 3 | | | 846 | Bq m ⁻² h ⁻¹ | 334 | IT1 |
| Sienites (polished) | 1 | 3 | | | 526 | Bq m ⁻² h ⁻¹ | 334 | IT1 |
| Granite pink- Porrino | 1 | 3 | | | 695 | Bq m ⁻² h ⁻¹ | 88 | IT1 |
| Granite pink- Porrino 0.2 water content | 1 | 3 | | | 850 | Bq m ⁻² h ⁻¹ | 88 | IT1 |
| Granite pink- Porrino 0.3 water content | 1 | 3 | | | 1253 | Bq m ⁻² h ⁻¹ | 88 | IT1 |
| Marble | 8 | | 2400-3000 | 0.5 | 130 (10-250) | mBq m ⁻² h ⁻¹ | 4 (0.6-10) | IT15 |
| Schist | 3 | | 2600-3000 | 2 | 12.3 (8.7-16) | Bq m ⁻² h ⁻¹ | 52 (19-86) | IT15 |
| Schist | 3 | | 2600-3000 | 2 | 3.5 (2.9-4.1) | Bq m ⁻² h ⁻¹ | 39 (34-42) | IT15 |
| Granite (green) | 1 | | | 19 | 82 | mBq kg ⁻¹ h ⁻¹ | 57 | IT13 |
| Granite (red) | 1 | | | 21 | 250 | mBq kg ⁻¹ h ⁻¹ | 153 | IT13 |
| Granite (pink) | 1 | | | 2 | 129 | mBq kg ⁻¹ h ⁻¹ | 147 | IT13 |
| Granite (pink) | 1 | | | 5 | 12 | mBq kg ⁻¹ h ⁻¹ | 33 | IT13 |
| Granite (pink) | 1 | | | 15 | 69 | mBq kg ⁻¹ h ⁻¹ | 61 | IT13 |
| Granite (white) | 1 | | | 2 | 4 | mBq kg ⁻¹ h ⁻¹ | 37 | IT13 |
| Black gabbro | 1 | | | 7 | 7 | mBq kg ⁻¹ h ⁻¹ | 12 | IT13 |
| Porphyry | 1 | | | 2 | 7 | mBq kg ⁻¹ h ⁻¹ | 40 | IT13 |
| Porphyry | 1 | | | 12 | 38 | mBq kg ⁻¹ h ⁻¹ | 41 | IT13 |
| Other | | | | | | mBq kg ⁻¹ h ⁻¹ | | |
| Mortar | 1 | | | 9 | 15 | mBq kg ⁻¹ h ⁻¹ | 22 | IT13 |
| Mortar | 1 | | | 23 | 12 | mBq kg ⁻¹ h ⁻¹ | 7 | IT13 |
| Mortar | 1 | | | 13 | 13 | mBq kg ⁻¹ h ⁻¹ | 13 | IT13 |
| Lime mortar | 1 | | | 3 | 4 | mBq kg ⁻¹ h ⁻¹ | 16 | IT13 |
| Plaster coat | 1 | | | 10 | 17 | mBq kg ⁻¹ h ⁻¹ | 22 | IT13 |
| Plaster coat | 1 | | | 1 | 3 | mBq kg ⁻¹ h ⁻¹ | 34 | IT13 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| Ashes | | | | | | | | |
| FA (USA) | 10 ^p | | | 2 | 23 | mBq kg ⁻¹ h ⁻¹ | 170 | IT2 |

- ^o Radiometric measure on 13 samples
Concrete A*: white limestone as aggregate
Concrete B**: sand and gravel as aggregate
- ^p Radiometric measure on 71 samples

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|---|-----------------|-----------|----------------------------------|-------------------|--------------------------|--------------------------------------|---|-------------|
| FA (Sud Africa) | 19 ^q | | | 1 | 16 | mBq kg ⁻¹ h ⁻¹ | 170 | IT2 |
| BA | 5 ^r | | | 3 | 24 | mBq kg ⁻¹ h ⁻¹ | 130 | IT2 |
| NETHERLANDS (124 samples from Table 19) | | | | | | | | |
| Brick | 1 | 10 | 1680 | 1 | 290 | mBq m ⁻² h ⁻¹ | 39 | NL4 |
| Brick (clay) | 16 | 10 | 1670 (1370-2000) | 0.3 (0.03-1) | 4 (0.1-4) | mBq kg ⁻¹ h ⁻¹ | 39 (27-45) | NL1 |
| Brick (clay) | 5 | 10 | 1370 (1350-1390) | 0.2 (0.07-0.3) | 4 (0.4-1) | mBq kg ⁻¹ h ⁻¹ | 74 (71-75) | NL1 |
| Brick (sand-lime) | 22 | 10 | 1820 (1720-1910) | 10 (6-15) | 8 (3-14) | mBq kg ⁻¹ h ⁻¹ | 10 (4-17) | NL1 |
| Brick 20% FA | 1 | 7 | 1490 | 0.7 | 200 | mBq m ⁻² h ⁻¹ | 76 | NL3,NL4 |
| Concrete | | | | | | | | |
| Aerated concrete | 14 | | | 13 (5-17) | 10 (5-22) | mBq kg ⁻¹ h ⁻¹ | 11 (6-16) | NL1 |
| Aerated concrete | 1 | 10 | 570 | 18 | 850 | mBq m ⁻² h ⁻¹ | 22 | NL4 |
| Aerated concrete | 1 | 10 | 790 | 22 | 1200 | mBq m ⁻² h ⁻¹ | 18 | NL4 |
| Aerated concrete with FA | 1 | 10 | 810 | 21 | 3800 | mBq m ⁻² h ⁻¹ | 58 | EU2, NL4 |
| Concrete | 28 | | | 14 (6-26) | 25 (4-40) | mBq kg ⁻¹ h ⁻¹ | 24 (11-36) | NL1 |
| Concrete (BFS+FA) | 1 | | 2300 | 9 | 1510 | mBq m ⁻² h ⁻¹ | 19 | NL4 |
| Concrete (PTL+ phosphoslag) | 1 | | 2390 | 1 | 6200 | mBq m ⁻² h ⁻¹ | 710 | NL4 |
| Concrete A (PTL) | 1 | 10 | 2360 | 26 ^s | 2350 ^s | mBq m ⁻² h ⁻¹ | 10 ^s | NL3, NL4 |
| Concrete B (BFS cement) | 1 | 10 | 2360 | 26 ^s | 3550 ^s | mBq m ⁻² h ⁻¹ | 16 ^s | NL3, NL4 |
| Concrete C (FA cement) | 1 | 10 | 2330 | 17 ^s | 2500 ^s | mBq m ⁻² h ⁻¹ | 14 ^s | NL3, NL4 |
| Concrete D (sintered FA grains) | 1 | 10 | 1900 | 6 ^s | 2350 ^s | mBq m ⁻² h ⁻¹ | 55 ^s | NL3, NL4 |
| Natural raw materials | | | | | | | | |
| Gypsum | 1 | 7 | 960 | 13 | 340 | mBq m ⁻² h ⁻¹ | 10 | NL4 |
| Gypsum | 1 | 7 | 990 | 9 | 130 | mBq m ⁻² h ⁻¹ | 5 | NL4 |
| Gypsum | 1 | 1 | 760 | | 50 | mBq m ⁻² h ⁻¹ | 2 | NL4 |
| Gypsum | 1 | 1 | 910 | 19 | 33 | mBq m ⁻² h ⁻¹ | 6 | NL4 |
| Gypsum | 1 | 1 | 820 | | 20 | mBq m ⁻² h ⁻¹ | 4 | NL4 |
| Gypsum | 10 | 1-10 | 900 (700-1200) | 13 (5-17) | 6 (4-10) | mBq kg ⁻¹ h ⁻¹ | 8 (3-14) | NL1 |
| Others | | | | | | | | |
| Mortar | 6 | 4 | 1830 (1740-1890) | 26 (20-34) | 25 (11-47) | mBq kg ⁻¹ h ⁻¹ | 12 (7-18) | NL1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| By-product gypsum | | | | | | | | |
| PHG | 1 | 7 | 960 | 18 | 4800 | mBq m ⁻² h ⁻¹ | 103 | NL4 |
| PHG | 1 | 7 | 960 | 19 | 15800 | mBq m ⁻² h ⁻¹ | 330 | NL4 |
| PHG | 1 | 1 | 840 | 13 | 2500 | mBq m ⁻² h ⁻¹ | 700 | NL4 |
| PHG (possible) | 1 | 7 | 900 | 3 | 200 | mBq m ⁻² h ⁻¹ | 26 | NL4 |
| Chemical gypsum (board) | 3 | 7 | | 7 | 9.6 | Bq m ⁻² h ⁻¹ | 450 (320-700) | NL3 |

^q Radiometric measure on 70 samples

^r Radiometric measure on 10 samples

^s Average value between data from NL3 e NL4

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|--|----|-----------|----------------------------------|------------------|--------------------------|---|---|-------------|
| NORWAY (10 samples from Table 20 + 13 samples with only emanation/exhalation rate data) | | | | | | | | |
| Concrete | | | | | | | | |
| Concrete | 7 | | | | 4 (3-6) | mBq h ⁻¹ /Bq kg ⁻¹ | | NW3 |
| Concrete with FA | 3 | | | | 61 (50-71) | mB qh ⁻¹ | | NW3 |
| Concrete without FA | 3 | | | | 91 (84-102) | mB qh ⁻¹ | | NW3 |
| Cement | | | | | | | | |
| Cement | 5 | | | 2-5 | | | 30-33 | EU2, NW3 |
| FA cement | 1 | | | 2 | | | 85 | EU2, NW3 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| Ashes | | | | | | | | |
| FA (imported) | 4 | | | 0.5-1.5 | | | 174 (126-222) | NW3 |
| POLAND (58 samples from Table 21) | | | | | | | | |
| Bricks | | | | | | | | |
| Red clay bricks | 3 | | | | | | | PL4 |
| | | 9 | | 2.2 | | | 19 | |
| | | 9 | | 2.3 | | | 19 | |
| | | 9 | | 5 | | | 19 | |
| Silicon (sand-lime) bricks | 3 | | | | | | | PL4 |
| | | 9 | | 16 | | | 7 | |
| | | 9 | | 3 | | | 7 | |
| | | 9 | | 0.8 | | | 15 | |
| Cement | | | | | | | | |
| Cement | 4 | | | | | | | PL4 |
| Cement | | 9 | | 5 | | | 9 | |
| Cement | | 9 | | 4 | | | 24 | |
| Cement | | 9 | | 0.8 | | | 26 | |
| Cement | | 9 | | 9 | | | 19 | |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| Ashes | | | | | | | | |
| Fly ash | 33 | | | 0.5 (0.2-1.2) | | | 96 (63-144) | PL4 |
| By product gypsum | | | | | | | | |
| By product gypsum | 4 | | | | | | | PL4 |
| | | 9 | | 4 | | | 26 | |
| | | 9 | | 13 | | | 699 | |
| | | 9 | | 21 | | | 736 | |
| | | 9 | | 20 | | | 585 | |
| Metallurgical Slags | | | | | | | | |
| Slag | 11 | 9 | | 0.7 (0.2-1.5) | | | 67 (37-144) | PL4 |
| PORTUGAL (78 samples from Table 22) | | | | | | | | |
| Bricks | | | | | | | | |
| Bricks | 10 | | | | <u>6.1</u> (1.8-10.4) | Bq m ⁻² h ⁻¹ | <u>64</u> (37-90) | POR1 |
| Concrete | | | | | | | | |
| Concrete block | 11 | | | | <u>7</u> (1.1-13) | Bq m ⁻² h ⁻¹ | <u>53</u> (8-98) | POR1 |

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | Exhalation rate unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|---|----|--------|-------------------------------|-----------------|-----------------------|--------------------------------------|--|------|
| Cement | | | | | | | | |
| Cement | 7 | | | | <u>2.5</u> (1.8-3.2) | Bq m ⁻² h ⁻¹ | <u>40</u> (21-59) | POR1 |
| Aggregates | | | | | | | | |
| Sand | 32 | | | | <u>61.4</u> (0.4-122) | Bq m ⁻² h ⁻¹ | <u>102</u> 2-202 | POR1 |
| Gravel | 11 | | | | <u>3.6</u> (0.4-6.8) | Bq m ⁻² h ⁻¹ | <u>70</u> (10-130) | POR1 |
| INDUSTRIAL BY-PRODUCTS IN BUILDING MATERIALS | | | | | | | | |
| By-product gypsum | | | | | | | | |
| PHG | 7 | | | | 18.2 (4-74.2) | Bq m ⁻² h ⁻¹ | 166 (12-705) | POR1 |
| ROMANIA (4 samples from Table 23) | | | | | | | | |
| Cement | | | | | | | | |
| Cement | 1 | 15 | 1700 | | 520 | mBq m ⁻² h ⁻¹ | 27 | RO5 |
| Cement-FA 50% | 1 | 15 | 1700 | | 2970 | mBq m ⁻² h ⁻¹ | 154 | RO5 |
| Cement-FA 33% | 1 | 15 | 1700 | | 2070 | mBq m ⁻² h ⁻¹ | 107 | RO5 |
| Cement-FA 11% | 1 | 15 | 1700 | | 1120 | mBq m ⁻² h ⁻¹ | 58 | RO5 |
| SLOVAKIA (29 samples from Table 24) | | | | | | | | |
| Concrete | | | | | | | | |
| Concrete b7.5/325R | 3 | 7.5 | 2210 | 3 | 3 | mBq kg ⁻¹ h ⁻¹ | 10 | SK2 |
| Concrete b7.5/325R+2mm plaster | 3 | 7.5 | 2210 | | 1 | mBq kg ⁻¹ h ⁻¹ | 10 | SK2 |
| Concrete b35/325 R | 3 | 7.5 | 2295 | 9 | 9 | mBq kg ⁻¹ h ⁻¹ | 13 | SK2 |
| Concrete b35/325 R+2mm plaster | 3 | 7.5 | 2295 | | 5 | mBq kg ⁻¹ h ⁻¹ | 13 | SK2 |
| Concrete b35/325 HS | 3 | 7.5 | 2200 | 4 | 3 | mBq kg ⁻¹ h ⁻¹ | 11 | SK2 |
| Concrete b35/325 HS+2 mm plaster | 3 | 7.5 | 2200 | | 3 | mBq kg ⁻¹ h ⁻¹ | 11 | SK2 |
| Concrete with broken bricks BBC/325HS | 2 | | 1600 | 4 | 3 | mBq kg ⁻¹ h ⁻¹ | 46 | SK2 |
| Concrete with broken bricks BBC/325R | 2 | | 1545 | 6 | 6 | mBq kg ⁻¹ h ⁻¹ | 44 | SK2 |
| Cellular concrete SS | 3 | 7.5 | 535 | 9 | 10 | mBq kg ⁻¹ h ⁻¹ | 16 | SK2 |
| Cellular concrete SE | 3 | 7.5 | 500 | 12 | 49 | mBq kg ⁻¹ h ⁻¹ | 50 | SK2 |
| Cellular concrete BA | 1 | 7.5 | 580 | 11 | 57 | mBq kg ⁻¹ h ⁻¹ | 69 | SK2 |
| SWITZERLAND (86 samples from Table 28) | | | | | | | | |
| Brick | | | | | | | | |
| Clay brick | 18 | | | 3 (0.4-16) | 11 (0.7-49) | mBq kg ⁻¹ h ⁻¹ | 47 (32-62) | SW1 |
| Concrete | | | | | | | | |
| Concrete brick | 2 | | | <u>6</u> (2-10) | <u>6</u> (2-9) | mBq kg ⁻¹ h ⁻¹ | <u>12</u> (11-12) | SW1 |
| Aerated concrete | 2 | | | <u>6</u> (3-10) | <u>6</u> (5.8-6.5) | mBq kg ⁻¹ h ⁻¹ | <u>19</u> (9-28) | SW1 |
| Pumice concrete | 5 | | | 5 (3-22) | 49 (18-87) | mBq kg ⁻¹ h ⁻¹ | 149 (28-249) | SW1 |
| Cement | | | | | | | | |
| Cement | 10 | | | 15 (2-50) | 22 (4-69) | mBq kg ⁻¹ h ⁻¹ | 20 (11-29) | SW1 |
| Aggregates | | | | | | | | |
| Gravel | 12 | | | 20 (3-47) | 33 (5-150) | mBq kg ⁻¹ h ⁻¹ | 25 (9-50) | SW1 |

| BUILDING MATERIALS | N. | d (cm) | Density (kg m ⁻³) | Emanation (%) | Exhalation rate value | unit | ²²⁶ Ra (Bq kg ⁻¹) | Ref. |
|--|----|-----------|----------------------------------|----------------------|--------------------------|--------------------------------------|---|------|
| Sand | 22 | | | 19 (2-63) | 31 (1-146) | mBq kg ⁻¹ h ⁻¹ | 20 (9-56) | SW1 |
| Rhenice pumice | 5 | | | 1 (0.4-2) | 21 (9-35) | mBq kg ⁻¹ h ⁻¹ | 237 (121-415) | SW1 |
| Natural Raw Materials | | | | | | | | |
| Lime | 3 | | | 15 (3-26) | 14 (5-21) | mBq kg ⁻¹ h ⁻¹ | 17 (11-22) | SW1 |
| Sand-lime stone | 2 | | | 35 (34-36) | 34 (32-37) | mBq kg ⁻¹ h ⁻¹ | 13 (11-15) | SW1 |
| Gypsum | 5 | | | 24 (14-40) | 26 (18-87) | mBq kg ⁻¹ h ⁻¹ | 15 (13-18) | SW1 |
| UNITED KINGDOM (17 samples from Table 30) | | | | | | | | |
| Brick | | | | | | | | |
| Clay brick | 6 | | | 0.5 | 50 | mBq m ⁻² h ⁻¹ | 65 | GB1 |
| Silica brick | 1 | | | 3 | 180 | mBq m ⁻² h ⁻¹ | 33 | GB1 |
| Flint brick | 1 | | | 0.9 | 133 | mBq m ⁻² h ⁻¹ | 70 | GB1 |
| Oil shale brick | 1 | | | 8 | 1166 | mBq m ⁻² h ⁻¹ | 76 | GB1 |
| Crushed granite bricks and blocks | 3 | | | 11 | 1800 | mBq m ⁻² h ⁻¹ | 40 | GB1 |
| Expanded clay blocks | 2 | | | 0.8 | 14 | mBq m ⁻² h ⁻¹ | 94 | GB1 |
| Concrete | | | | | | | | |
| Building blocks with PFA | 2 | | | | 610 (160-1480) | mBq m ⁻² h ⁻¹ | 54 | EU2 |
| Concrete block | 1 | | | 4 | 324 | mBq m ⁻² h ⁻¹ | 18 | GB1 |

DATABASE REFERENCES

- [AU1] Sorantin H, Steger F. Natural Radioactivity of building materials in Austria. *Radiat Prot Dosim* 1984;7(1-4):59-61.
- [BE1] Poffijn A, personal communication from FANC Report in Dutch.
- [BE2] Poffijn A, Bourgoignie R, Marijins R, Uyttenhove J, Janssens A, Jacobs R. Laboratory measurements of radon exhalation and diffusion. *Radiat Prot Dosim* 1984;7(1-4):77-9.
- [BE3] Poffijn A, Marijins R, Vanmarcke H, Uyttenhove J. Results of a preliminary survey on radon in Belgium. *Sci. Tot. Environ.* 1985. 45, 335-342.
- [CY1] Michael F, Parpottas Y, Tsertos H. Gamma radiation measurements and dose rates in commonly used building materials in Cyprus. *Radiat Prot Dosimetry* 2010;142(2-4):282-91. I dati coincidono con: Panicos Demetriades, Personal communication.
- [CZ1] Breda M. "Prirodni radioaktivita ve stavebnictvi" 1990
- [DK1] Ulbak K. Radioaktive stoffer i danske byggematerialer. SIS, State Institute of Radiation Hygiene & The National Health Service of Denmark, p.6+app. (1980). Partially translated in: Ulbak K. Natural radioactivity in building materials in Denmark. In: Proceedings of the "Seminar on the radiological burden of man from natural radioactivity in the countries of the European Communities". 4-6 December 1979, Le Vesinet, Paris, France 1979.
- [DK2] Ulbak K. En stralehygiejnisk vurdering af brugen af flyveaske i byggeindustrien. SIS, State Institute of Radiation Hygiene & The National Health Service of Denmark, p. 13 1984.
- [EST1] Lust M, Realo E. Assessment of natural radiation exposure from building materials in Estonia. Proceedings of the "Estonian Academy of Sciences", 2012, 61, 2, 107-112 doi: 10.3176/proc.2012.2.03
- [EU1] Krstic D, Nikezic D, Stevanovic N, Vucic D. Radioactivity of some domestic and imported building materials from South Eastern Europe. *Radiat Meas* 2007;42:1731-6.
- [EU2] European Commission. *Enhanced radioactivity of building materials. Radiation Protection 96*. Luxembourg: European Commission; 1997.
- [EU3] United Nations. *Sources and effects of ionizing radiation. united nations scientific committee on the effects of atomic radiation. Report to the General Assembly, with annexes*. New York: United Nations; 1977.
- [FIN1] Turtiainen T, Weltner A. Assessment of dose during the life cycle of natural stone production. *Radiation Protection Dosimetry* 2007;124(2):167-71.
- [FIN2] Mustonen R. Natural radioactivity in and radon exhalation from Finnish building materials. *Health Phys* 1984;46(6):1195-203.
- [FIN3] Mustonen R. Methods for Evaluation of radiation from building materials. *Rad Prot Dos* 1984;7(1-4):235-8.
- [FIN4] Mustonen R. *Building materials as sources of indoor exposure to ionizing radiation. STUK-A105*. Helsinki Finnish centre for Radiation and Nuclear Safety; 1992.
- [FR1] Dupuis M, Ameon R, Alcalde G, Diez O. *Les matériaux de construction, source secondaire de radon dans les bâtiments*. Fontanay-aux-Roses: Institut de Radioprotection et de Sureté Nucleaire; 2008 (IRSN/DEL/SARG/2008-008).
- [FR2] Pasquier JL, Lemaître N. *Radioprotection et matériaux de construction*. Le Vésinet: Office de Protection contre les Rayonnements Ionisants; 1999. (Rapport O.P.R.I – 22/06/99).

- [GB1] Cliff KD, Green BMR, Miles JCH. The levels of radioactive materials in some common UK building materials. *Sci Total Environ* 1985;45:181-6.
- [GB2] Cliff KD, Miles JCH, Brown K. *The incidence and origin of radon and its decay products in buildings*. Chilton: National Radiological Protection Board; 1984. (NRPB-R159)
- [GB3] O’Riordan MC, Hunt GJ. Radiological controls for construction materials. In: Proceedings of the 4th International Congress of IRPA, 24-30 April 1977, Paris, France, vol. 3, p. 1053-6.
- [GE1] Gehrcke K, Hoffmann B, Schkade Y, Schmidt V, Wichterey K. Radiation exposure from the use of NORM in building materials in Germany. IAEA Library Cataloguing in Publication Data Naturally occurring radioactive material (NORM VI): proceedings of the “Sixth International Symposium on naturally occurring radioactive material” organized by the Hassan II University of Mohammedia and the Cadi Ayyad University of Marrakesh in cooperation with the International Atomic Energy Agency and held in Marrakesh, Morocco, 22-26 March 2010. Vienna: International Atomic Energy Agency, 2011. p. 443-53.
- [GE2] Folkerts KH, Keller G, Muth H. An experimental study on diffusion and exhalation of ^{222}Rn and ^{220}Rn from building materials. *Radiation Protection Dosimetry* 1984;9(1):27-34.
- [GE3] Lehman R. Strahlenbelastung durch natürliche Radionuklide in Baumaterialien, fossilen Brennstoffen und Düngemitteln. In: Siehl A. (Hrsg.) *Umweltradioaktivität*. Ernst & Sohn Verlag, Berlin, Germany, 1996,135-156.
- [GE4] Von Philipsborn H, Kuhnast E. Gamma spectrometric characterisation of industrially used African and Australian bauxites and their red mud tailings. *Radiat Prot Dosim* 1992;45(1-4 Suppl.):741-3.
- [GE5] Döring J, Beck T, Beyermann M, Gerler J, Henze G, Mielcarek J, Schkade UK. Exposure and radiation protection for work areas with enhanced natural radioactivity. In: *Proceedings of the Fifth International Symposium on Naturally Occurring Radioactive Material*. Seville, 19-22 March 2007. 399-407. IAEA, Vienna 2008.
- [GR1] Petropoulos NP, Anagnostakis MJ, Simopoulos SE. Photon attenuation, natural radioactivity content and radon exhalation rate of building materials. *J Environ Radioact* 2002;61:257-69.
- [GR2] Papastefanou C, Manolopolou M, Charalambous S. Exposure from radioactivity in building materials. *Health Phys* 1984;47:775-83.
- [GR3] Pakou AA, Assimakopoulos PA, Prapidis M. Natural radioactivity and radon emanation factors in building material used in Epirus (north-western Greece). *Sci Total Environ* 1994;144:255-60.
- [GR4] Stoulos S, Manolopolou M, Papastefanou C. Assessment of natural radiation exposure and radon exhalation from building materials in Greece. *J Environ Radioact* 2003;69:225-40.
- [GR5] Papaefthymiou H, Gouseti O. Natural radioactivity and associated radiation hazards in building materials used in Peloponnese, Greece. *Radiat Meas* 2008;43:1453-7.
- [GR6] Tzortzis M, Tsertos H, Christofides S, Christodoulides G. Gamma radiation measurements and dose rates in commercially-used natural tiling rocks (granites). *J Environ Radioact* 2003;70:223-35.
- [GR7] Pavlidou S, Koroneos A, Papastefanou C, Christofides G, Stoulos S, Vavelides M. Natural radioactivity of granites used as building materials. *J Environ Radioact* 2006;89:48-60.
- [GR8] Karangelos DJ, Petropoulos NP, Anagnostakis MJ, Hiniš EP, Simopoulos SE. Radiological characteristics and investigation of the radioactive equilibrium in the ashes produced in lignite-fired power plants. *J Environ Radioact* 2004;77:233-46.
- [GR9] Louizi A, Proukakis C, Petropoulos NP, Simopoulos SE. Natural radioactivity content and radon exhalation rates of Greek building materials. In: Morawska L, Bofinger ND, Maroni M (Ed.). *Indoor air – an integrated approach*. Oxford: Elsevier; 1995. p. 131-5.

- [GR10] Siotis I, Wrixon AD. Radiological consequences of the use of fly ash in building materials in Greece. *Radiat Prot Dosim* 1984;7:101-5.
- [GR11] Savidou A, Raptis C, Kritidis P. Natural radioactivity and radon exhalation from building materials used in Attica region, Greece. *Radiat Prot Dosim* 1995;59(4):309-12.
- [GR12] Maraziotis EA. Gamma activity of the fly ash from Greek power plant and properties of fly ash cement. *Health Phys* 1985;49(2):302-3.
- [GR13] Savidou A, Raptis C, Kritidis P. Study of Natural Radionuclides and Radon Emanation in Bricks used in the Attica Region, Greece. *J Environ Radioact* 1996;31:21-8.
- [GR14] Papastefanou C. Escaping radioactivity from coal-fired power plants (CPPs) due to coal burning and the associated hazards: a review. *J Environ Radioact* 2010;101:191-200.
- [GR15] Papaefthymiou H, Symeopoulos BD, Soupioni M. Neutron activation analysis and natural radioactivity measurements of lignite and ashes from Megalopolis basin, Greece. *J Radioanal Nucl Chem* 2007;274:123-30.
- [GR16] Pontikes Y, Vangelatos I, Boufounos D, Fafoutis D, Angelopoulos GN. Environmental aspects on the use of Bayer's process bauxite residue in the production of ceramics. *Adv Sci Technol* 2006;45:2176-81.
- [GR17] Papatheodorou G, Papaefthymiou H, Maratou A, Ferentinos G. Natural radionuclides in bauxitic tailings (red-mud) in the Gulf of Corinth, Greece. *Radioprotection* 2005;40:S549-S555.
- [GR18] Samouhos M, Taxiarchou M, Tsakiridis PE, Potiriadis K. Greek "red mud" residue: a study of microwave reductive roasting followed by magnetic separation for a metallic iron recovery process. *J Hazard Mater* 2013;254-255:193-205.
- [GR19] Simopoulos SE, Angelopoulos MG. Natural radioactivity releases from lignite power plants in Greece. *J. Environ. Radioact.* 1987. 5(5), 379-389.
- [H1] Somlai J, Jobbágy V, Németh C, Gorjánác Z, Kávási N, Kovács T. Radiation dose from coal slag used as building material in the Transdanubian region of Hungary. *Radiat Prot Dosim* 2006;118(1):82-7.
- [H2] Gallyas M, Torok I. Natural radioactivity of raw materials and products in the cement industry. *Radiat Prot Dosim* 1984;7(1-4):69-71.
- [H3] Toth A, Feher I, Novotny Lakatos S, Koszorus L, Keszthely B. Distribution of natural radioactive isotopes concentrations and emanation factors measured on concrete and brick samples produced in Hungary. In: *Proceedings of Symposium "Natural Radiation Environment III"*. April 1978, Houston Springfield, NTIS, 1980. p.1396-406.
- [H4] IBES, International Bureau for Environmental Studies. Final report INTAILRISK (assessment of environmental risk for use of radioactively contaminated industrial tailings); 2011.
- [H5] Jobbágy V, Somlai J, Kovács J, Szeiler G, Kovács T. Dependence of radon emanation of red mud bauxite processing wastes on heat treatment. *Journal of Hazardous Materials* 2009;172:1258-63.
- [IRL1] Lee EM, Menezes G, Finch EC. Natural radioactivity on building materials in the Republic of Ireland. *Health Phys* 2004;86(4):378-83.
- [IRL2] Organo C, Fenton D. *Radiological assessment of NORM Industries in Ireland – Radiation doses to workers and members of the public*. Dublin: Radiation Protection Institute of Ireland; 2008.
- [IT1] Carrera G, Garavaglia M, Magnoni S, Valli G, Vecchi R. Natural Radioactivity and Radon Exhalation in Stony Materials. *J Environ Radioact* 1997;34(2):149-59.
- [IT2] Battaglia A, Capra D, Queirazza G, Sampaolo A. Rn exhalation rates from building materials and fly ash-containing concretes. In: *Proceeding of IRPA 8*, Montreal 1992. p. 1578-81.

- [IT2.A] Battaglia A, Capra D, Queirazza G, Sampaolo A. Emanazione di radon da ceneri di carbone e da materiali edili. In: *Atti del "XXVII Congresso Nazionale AIRP"*, 16-18 settembre 1991, Ferrara, Italia, 1991. p. 533-41.
- [IT3] Bonetti R, Capra L, Facchini U, Valli G, Carreri V, Anversa A, Blanco G, Gualdi R, Sgorbati G, De Crescenzo S. Development of Radon Surveys in Lombardia, Italy. In: *Proceedings of "Indoor Air '90"*, 29 July-3 August 1990, Toronto, Canada, 1990. p. 53-8.
- [IT4] Trotti F, Lanciai M, Lucchese R, Mozzo P, Predicatori F, Tacconi A. Radioattività naturale nei materiali da costruzione utilizzati in provincia di Verona. In: *Atti del "XXVII Congresso Nazionale AIRP"*, 16-18 settembre 1991, Ferrara, Italia, 1991. p. 597-604.
- [IT5] Orlando P, Massari P, Paoletti C, Trenta R, Trevisi R, Amici M, Benvenuti F, Altieri A, Catano F. La radioattività nei materiali da costruzione nel Lazio. In: *Rapporti ISTISAN 98/3, Atti del Convegno nazionale "Aria '96"*, 12-14 giugno 1996, Roma, Italia. 1998. p. 303-13.
- [IT6] Battaglia A, Bazzano E, Bonfanti G. Indoor dose in Milano (Italy). *Sci Total Environ* 1983;45:365-71.
- [IT7] Valli G, Vecchi R, Piardi S, Gregorini E. Concentrazione di radioelementi naturali in materiali lapidei usati nell'edilizia. In: *Atti del Convegno nazionale "La qualità dell'aria negli ambienti interni, Aria '92"*, 28-29 ottobre 1992, Pisa, Italia. 1992. p. 60-66.
- [IT8] Sciocchetti G, Scacco F, Baldassini PG, Monte L, Sarao R. Indoor measurements of airborne natural radioactivity in Italy. *Radia. Prot Dosim* 1984;7(1-4):347-51.
- [IT9] Sciocchetti G, Clemente GF, Ingrao G, Scacco F. Results of a survey on radioactivity of building materials in Italy. *Health Phys* 1983;45(2):385-8.
- [IT10] Campos Venuti G, Esposito A, Grisanti A, Grisanti G, Pelliccioni M, Risica S. Studio della radioattività naturale in rocce e cementi, ai fini della costruzione del laboratorio del Gran Sasso dell'INFN. In: *atti del XXIII congresso nazionale dell'associazione italiana di protezione contro le radiazioni (AIRP)*. Capri 5-8 ottobre 1983
- [IT10.A] Campos Venuti G, Esposito A, Grisanti A, Grisanti G, Pelliccioni M, Risica S. *Studio della radioattività naturale in rocce e cementi, ai fini della costruzione del laboratorio del Gran Sasso dell'INFN*. Frascati: Istituto Nazionale di Fisica Nucleare; 1982. (LNF-82/78(R)).
- [IT11] Campos Venuti G, Colilli S, Grisanti A, Grisanti G, Monteleone G, Risica S, Antonini A, Borio R, Gobbi G, Leogrande MP. Methodology and Results of a Natural Radioactivity Assessment in a Region of Central Italy. In: *Proceedings of the "6th International Congress IRPA"*, May 7-12 1984, Berlin, Germany, 1984. p. 84-87.
- [IT12] Minach L, Brunner P. Radioattività nei materiali da costruzione (in Alto Adige). In: *Misurazioni della radioattività in Alto Adige*. Bolzano: Provincia Autonoma di Bolzano; 1990. P. 48-53.
- [IT13] Righi S, Bruzzi L. Natural radioactivity and radon exhalation in building materials used Italian dwellings. *J Environ Radioact* 2006;88:158-70.
- [IT14] Bruzzi L, Baroni M, Mazzotti G, Mele R, Righi S. Radioactivity in raw materials and end products in the Italian ceramics industry. *J Environ Radioact* 2000;47:171-81.
- [IT15] Rizzo S, Brai M, Basile S, Bellia S, Hauser S. Gamma activity and geochemical features of building materials: estimation of gamma dose rate and indoor radon levels in Sicily. *Applied Radiation and Isotopes* 2001;55:259-65.
- [IT16] Ianni A, Cavariani F, Lucci F, Morgia A, Nobili C, Sandri S, Vasselli R. Natural radiation in building materials from the volcanic area of the Italian Lazio region - Occupational Safety. In: Peter J, Schneider G, Bayer A (Ed). *Proceedings of "High levels of natural radiation and radon areas: radiation dose and health effects"*. Munich (Germany); 4-7 Sep 2000. Salzgitter: Bundesamt fuer Strahlenschutz; 2002. p. 351-4.

- [IT17] Sabbarese C, Inghima I, D'Onofrio A, Roca V, Ermice A, Lubritto C, Terrasi F, Plamieri A, Casa G, Migliore G. Radioattività nei materiali da costruzione utilizzati nella regione Campania. In: *atti del convegno AIRP "La radioattività nel contesto degli studi ambientali"* Isola del Giglio 9-10 maggio 2002
- [IT18] Grisanti G. *Data on radioactivity concentration in Italian building materials* (data not published). Rome: Istituto Superiore di Sanità; 1990
- [IT19] Trotti F, Zampieri C, Nuccetelli C and Risica S. Review of Italian NORM industries with specific reference to their environmental impact. In: *Proceeding of "EAN NORM workshop – European ALARA network for NORM"* 20–22 November 2007 Dresden – Germany; 2007.
- [LT1] Pilkyte L, Butkus D, Morkunas G. Assessment of the external dose indoors in Lithuania. *Radiat Prot Dosim* 2006;121(2):140-7.
- [LT2] Butkus D, Morkunas G, Pilkyte L. Ionising radiation in buildings: situation and dealing with problems. *J Environmental Engineering and Landscape Managements* 2005;13(2):103-7.
- [L1] Harpes N, Lecomte M. Radiation Protection Division, Ministry of Health, Luxembourg. Personal communication.
- [LV1] Riekstina D, Berzins J, Veveris O. Assessment of natural radionuclides level in building materials. Personal communication.
- [NL1] de Jong P, van Dijk W, van der Graaf ER, de Groot TJH. National survey on the natural radioactivity and ²²²Rn exhalation of building materials in the Netherlands. *Health Phys.* 2006. 91 (3), 200-210.
- [NL2] Hogeweg B, Bosnjakovic BFM, Willart WMAJ. Radiation aspects of indoor environments and related radioecological problems: a study of the situation in the Netherlands. *Radiat Prot Dosim* 1984;7(1-4):327-31.
- [NL3] Ackers JG, den Boer JF, de Jong P, Wolschrijn RA. Radioactivity and radon exhalation rates of building materials in the Netherlands. *Sci Total Environ* 1985;45:151-6.
- [NL4] van Dijk W, de Jong P. Determining the ²²²Rn exhalation rate of building materials using liquid scintillation counting. *Health Physics* 1991;61(4):501-9.
- [NW1] Stranden E, Strand T. Natural gamma radiation in a Norwegian area rich in thorium. *Radiat Prot Dosim* 1986;16(4):325-8.
- [NW2] Stranden E. Radioactivity of building materials and the gamma radiation in dwellings. *Phys Med Biol* 1979;24(5):921-30.
- [NW3] Stranden E. Assessment of the radiological impact of using fly ash in cement. *Health Phys* 1983;44(2):145-53.
- [PL1] Mamont-Ciesla K, Gwiazdowski B, Biernacka M, Zak A. Radioactivity of building materials in Poland. In: *Proceedings of the "Second Special Symposium on natural radiation environment"*, Bhabha Atomic Research Centre, 19-23 January 1981, Bombay, India. 1981. p. 551-6.
- [PL2] Skowronek J, Dulewski J. NORM in polish industry. In: *Proceedings of the "NORM III congress"*, 17-21 September 2001, Brussels, Belgium.
- [PL3] Zak A, Biernacka M, Jagielak J, Lipinski P. Investigations of radioactivity of building raws and materials. *Nukleonika* 1993;38(4):51-70.
- [PL4] Pensko J, Stipezynska Z, Blaton-Albicka K. Emanating power of radon-222 measured in building materials. In: Lowder WM, Gesell TF (Ed.). *Proceedings of Symposium "Natural Radiation Environment III"*. Houston, Texas, April 23-28, 1978. Oak Ridge: U.S. Dept. of Energy; 1980. p. 1407-14.

- [POR1] Faisca MC, Teixeira MMR. Different studies on building materials. In: *Proceedings of the "Radon in the Living Environment"*, 19-23 April 1999, Athens, Greece. p. 935-42.
- [POR2] Oliveira C. *Data on radioactivity concentration in Portugal building materials (data not published)*. Lisbon: Instituto Tecnológico e Nuclear, 2009.
- [RO1] Pantelica A, Georgescu II, Murariu-Magureanu MD, Margaritescu I, Cincu E. Thorium determination in intercomparisons samples and in some Romania building materials by gamma ray spectrometry. *Radiat Prot Dosim* 2001;97(2):187-91.
- [RO2] Gheorge R, Milu C, Gheorge D, Modoran G. Exposure due to phosphogypsum and fly-ash used as building materials. In: *Proceeding of the "5th International Conference on high levels of natural radiation and radon areas: Radiation dose and health effects"*, 4-7 September 2000, Munich, Germany. 2002, p. 331-4.
- [RO3] Botezatu E, Iacob O, Miron C, Gradinaru M. Increased indoor radiation exposures-consequences of NORMs contained in building materials. In: *Proceeding of the "5th International Conference on high levels of natural radiation and radon areas: Radiation dose and health effects"*, 4-7 September 2000, Munich, Germany. 2002, p. 355-8.
- [RO4] Botezatu E, Grecea C, Iacob O. Is coal ash and slags any useful or unloaded wastes? In: *Proceeding of the "European IRPA congress"*, October 8-11 2002, Florence, Italy.
- [RO5] Mocsy I, Onitiu T, Gorcea L. Radioactivity of the new building materials from Romania. In: *Proceedings of "Indoor Air '93"*, July 4-8 1993, Helsinki, Finland. 1993, p. 527-32.
- [SK1] Cabáneková H. Building materials as the source of radiation load of Slovak population. In: Seliga M, Sebesta (Ed.). *Proceedings of the 10. Banská Stiavnica Days 2008. Peaceful use of atomic energy. Application of nuclear technologies and determination of radionuclides in the environment. Environmental load and municipal wastes. Banská Stiavnica (Slovakia); 8-10 Oct 2008*. Bratislava: Slovak Nuclear Society; 2008. p. 53-6.
- [SK2] Holy K, Sykora I, Chudy M, Polaskova A, Fedja J, Hola O. Radionuclide content in some building materials and their radon exhalation. *J. Radioanal Nucl Chem Letters* 1995;199(4):251-63.
- [SLO1] Križman M. Exposure to natural radiation in dwellings and problems of high concentrations of ²²²Rn. In: Culibrk R (Ed.). *Proceedings of the Symposium on "Influence of Building Materials to the Microclimate of Residential Spaces"*, November 1990, Kanjiža (Serbia). Beograd: Yugoslavian Chamber of Economy; 1990. p. 24-40.
- [SP1] Cruz Alvarez M, Garzon L. Assessment of radiological emission from Spanish coal power plants: radioactive releases and associated risks. *Health Phys* 1989;57(5):765-9.
- [SP2] Garzon L, Fontenla P, Suarez A. Radioactivity of building materials- Adsorbed Doses. In: *Proceedings of the "Second Special Symposium on natural radiation environment"*, Bhabha Atomic Research Centre, 19-23 January 1981, Bombay, India. 1981, p. 544-6.
- [SP3] Martín Matarranz JL. *Concentraciones de radón en viviendas españolas. Otros estudios de radiación natural*. Madrid: Consejo de Seguridad Nuclear; 2004. (Colección Informes Técnicos 13.2004).
- [SP4] Chinchon-Paya S, Piedecausa B, Hurtado S, Sanjuan MA, Chinchon S. Radiological impact of cement concrete and admixtures in Spain. *Radiation Measurements* 2011;46:734-5.
- [S1] More H. *Radoiaktiva amnen I byggnadsmaterial*. Stockholm: Statens stralskyddsinstitut; 1985. (SSI-rapport 85-08).
- [S2] Swedjemark GA. *The ionizing radiation in dwellings related to the building materials*. Stockholm: National Institute of Radiation Protection; 1977. (SSI: 1977-004).
- [S3] Mjones L. Gamma radiation in Swedish dwellings. *Radiat Prot Dosim* 1986;15(2):131-40.

- [SW1] Schuler Ch, Cramieri R, Burkat W. Assessment of the indoor Rn contribution of Swiss building materials. *Health Phys* 1991;60(3):447-51.
- [TR1] Turhan S, Baykan UN, Sen K. Measurement of the natural radioactivity in building materials used in Ankara and assessment of external doses. *J Radiol Prot* 2008;28:83-91.
- [TR2] Akinci AN, Artir R. Characterization of trace elements and radionuclides and their risk assessment in red mud. *Mater Charact* 2008;59(4):417-21.

*Serie Rapporti ISTISAN
numero di dicembre 2017, 5° Suppl.*

*Stampato in proprio
Settore Attività Editoriali – Istituto Superiore di Sanità*

Roma, dicembre 2017